

Quicksilver Nevada
Castle Peak Mercury.

0990 0016-
Examined this one with Ralph Taylor on September 23, 1940. Located at 10.5 miles from Reno, the concentrating plant prepares ore mined by shovel and hauled by truck from Washington Hill, 5.3 miles to the southeast. Concentration has a ratio of about 100 to 1, and concentrates are furnaced at Castle Peak.

WAG

ITEM 96

Further interest depended on samples. These were poor. The zone of mineralization was very extensive and characterized by masses of opalite and could be traced for many thousands of feet. However material was definitely minus one pound. Property was in litigation. Went out with Mr. Louefeck.

D. L. EVANS