Camp Site Area:

Reference point is portal of bottom tunnel for all Camp Site drill holes; Elevation datum is rail at Ore bin, using 1000 feet.

Hole: 968-1

Location: 140-E, 240-S
Elevation 748

1.05
1.05
1.05

0- 20 : Brown soily unit with chert and some scattered HgS throughout. Sample 12-16 best show.

20-24 - 6.00
24-28 - 6.60
28-32 3.02

20-30: Very high grade cinnabar in loose chert.

32-36 - 0.00

30-36: Heavy chert without good shows.

0.08
0.33
0.08

36-48: Brown soily to loamy unit with HgS

nil

48-52: Andesite zone without values.

968-2

Hole 968-2

Location: 272-E, 160-S
Elevation 733

0.22
0.28
0.24
0.53
0.43
0.20
0.94

4- 32: Brown soily unit; scattered chart; no good obvious HgS.

1.81
0.92
0.90
1.48
1.15
1.23

32-49: Charts and only fair HgS

49-53: Soft, tan loamy unit with scattered HgS

0.08

53-59½: Andesite unit.

968-3

Hole 968-3

Location: 310-E, 225-S
Elevation: 720

0.66
0.33
0.24
0.08
0.33

0-20: Brown soily unit with chert and scattered HgS.

0.41

20-24: Increase in tan chert and HgS

50-54: Andesite

24-40: Charts with heavy HgS

24-32 - 4.13
32-36 9.58
36-40 3.30

40-50: Soft and loamy with heavy chert and heavy HgS

40-44 - 3.96
44-50 - 1.23
50-54 - 0.16

Hole 968-4

Location: zero E, and 150-S.
Elevation: 764

0.49	0 -8:	Road fill
0.33	8-12:	Brown zone with traces HgS in chert.
0.57	12-16:	Cherts and shows of HgS
1.65	16-24	" "
0.00	24-28	Andesite unit.

968-5

Hole 968-5:

Location: 300-W, 150-S

Elevation: 782

0 -4:	Road fill.
4-12:	Chert in brown soil
12-16:	Tan chert and buff colored fines.
16-20:	Brown chert in leamy fines.
20-30:	All leamy to soft granular and brown chert.
30-32:	Andesite unit.

Note: this is continuation of Camp Site area; critical zone has thickened and there exists HgS fragments in surface rubble, further west.

968-6

Hole 968-6

Location: 177-E, 307-S
Elevation: 718

0.95	0- 8:	Tinted cherts and HgS
0.57	8-20:	Brown loamy member with persistent cherts and shows of HgS
0.09	20-24:	The same but also with fragments of andesite.
0.08	24-32:	Andesite unit.

968-7

See next page

Hole968-7

Location: 404-E, 192-S
Elevation 703

0.24 0.10 0.18 — 0-12: Buff, powdery, earthy zone with minor HgS

0.16 0.77 0.41 0.16 — 12-28: Tan chert and definite HgS.

At 28' Top of Andesite zone.

968-8

Hole 968-8:

Location: 492-E, 240-S
Elevation: 696

0.24 0.08 0.28 0.16 0.16 0.33 — 4 -25: Fast penetration; samples small; all appear to be cherty, with some HgS.

0.00 — 25-28: Andesite zone.

968-60:

Hole 968-60:

Location: 38-E, 177-S
Elevation 756

0.67 — 0 - 4: Brown loose sand.

0.66 1.27 — 4 -12: Brown sand and scattered, stained cherts with shows of HgS

0.16 — 12-16: Gray and loose undetermined.

? 0.16 — 16-20: Andesite zone.

968-61

Hole 968-61

Location: 62-E, 235-S
Elevation 752

1.32 0.89 — 0 - 8: Brown loamy sand with traces chert and HgS.

0.41 — 8 -12: The same, chert increasing but no apparent good values.

0.46 0.47 — 12-20: As above.

0.25 — 20-24: New loose tan cherts with scattered HgS, but not rich.

0.16 0.16 — 24-32: Same cherts, but HgS in traces only.

0.16 — 32-36: Red andesite.

Hole 968-62

Location: 92-E, 295-S
Elevation: 747

0.92 0- 4: Brown loamy sand.

0.66 0.49 4-12: The same but with some chert.

0.64 12-16: As above.

0.09 16-20: Tan and brown cherts.

0.25 0.25 20-26: Same cherts with minor HgS

0.16 26-30: Red andesite.

968-63

Hole 968-63

Location: 102-E, 235-S
Elevation: 750

0.72 0- 4: Brown loamy sand.

0.49 4- 8: The same and increasing white chert.

0.86 0.92 8-16: White and tan cherts with traces of HgS.

0.49 0.25 16-24: The same and slight increase in HgS.

968-64 → ? ~~4.16~~ 24-28: Andesite zone. ? Check This.

968-64

Hole 968-64:

Location: 222-E, 212-S
Elevation: 743

0.23 0 - 4: Tan quartz sand with traces HgS

0.33 4 - 8: Porous detritus with very little sample.

0.74 8 -12: White cherts and no HgS

1.24 12-16: White and tan cherts; traces HgS

3.96 1.91 24-28 4.62 16-28: Powdery white material with good HgS and white cherts impregnated with sugary quartz and HgS.

2.55 3.05 0.80 28-40: As above and cherst with very strong HgS.

0.58 0.86 40-48: Tan cherts, persistent but less HgS

0.25 0.08 0.00 0.25 48-56: Cherts and low grade HgS

56-64: Red andesite and chert.

Hole 968-65:

Location: 233-E, 270-S
Elevation: 719

0 - 4: Brownish loamy sand, scattered cherts and coarse fragments of HgS

4 -12: White to tan clean chert;traces HgS

12-15: Cherts with minor HgS/

15: Andesite at 15

968-66

Hole 968-66

Location: 322-E, 330-S
Elevation: 752

0.49 0 - 4: Hard brittle, tan and gray, cherts with no HgS of con sequence

0.33 4 - 8: Softer tan cherts and traces HgS

0.25 0.25 8 -16: Soft cherts and fair scattered HgS

0.36 16-20: Soft; fines; fair HgS; andesitic appearence to some cherts.

0.49 20-24: Very soft, reddish material; suspect good HgS.

remad 0.33 0.16 24-32: Open ground, casing dropped through; no sample returns; probable old workings.

0.08 32-36: solid again, but mixed material with no definite character.

0.08 0.08 36-39: as above, and drilling stops in hard material at 39.

968-67:

Hole 968-67

Location: 374-E, 326-S
Elevation: 750

1.40 0.66 0 - 8: Dirt, white chert fragments, andesite and dominant chert with HgS.

1.32 8 -12: White to tan cherts and fines;good HgS.

0.66 12-16: Tan cherts;scattered coarse HgS

0.49 16-20: Tan glassy chert; traces HgS

28-32: Andesite 0.19

0.25 0.26 20-28: finely divided and chert;iron and weak HgSr

Hole 968-68

Location: 373-E, 238-S
Elevation: 719

2.56	0 - 4:	Mixture of soil and part of old stockpile, above old retort area.
1.85	4 -14:	Probably mixed stockpile and talus.
0.41 0.10	14-20:	Loamy sand and fragments of chert with HgS.
1.51 1.32	20-28:	White cherts with fair HgS in dominant tan fines.
0.77	28-32:	Cherts increase; HgS is fair.
0.43	32-36:	dominantly damp mass of yellowish broken cherts, some coarse cherts white and traces HgS.
1.05	36-39:	Cherts and high grade HgS.
	39:	Hole flowed water.
0.82	39-43:	Water flowed into hole, samples are gouge
0.72 0.40 0.20	43-52:	Clay to gougey andesite.

968-69

Hole 968-69

Location: 290-E, 187-S
Elevation: 726

0.58	0 - 4:	White fine cherts with trace HgS
0.25 0.75 0.99	4 -16:	Tan and brown sand, chert fragments and trace of HgS.
0.41 0.3[illegible]	16-24:	Increase in tan cherts and scattered coarse HgS fragments.
0.0[illegible] [illegible]	24-28:	cherts remain dirty and weathered, and HgS only scattered.
0.09	28-32:	Same dirty cherts; andesite fragments.
0.25 0.21	32-40:	Cleaner fine chert and slight increase HgS.
0.20	40-44:	As above and considerable clear tan chert.
0.20 0.25	44-52:	Dirty cherts; scattered weak HgS ; grainy broken cherts, trace HgS, last 4 feet
0.16	52- 56:	Andesite unit.

Hole 968-70

Location: 363-E, 185-S
Elevation: 720

0.20	0 - 4:	Tan loamy sand and scattered chert
0.13	4 - 8:	As above and some blue clay.
0.08	8 -12:	Poor recovery; more brown surface sand and some cherts.
0.16 0.33 0.33 0.16	12-27	Same brown formation and cherts with possible traces HgS.
.020	27-32:	Andesite.

Hole 968-71

Location: 117-E, 61-S
Elevation: 797

0.65	0 -16:	Soft mixed grayish tan fines and cherts from dump and talus.
1.07	16-20	Traces of heavy cherts with HgS
2.00	20-24:	Very heavy cherts and strong HgS
1.73	24-28:	finer tan cherts and good HgS
1.00	28-32:	sandier and finer cherts, also with HgS.
1.88	32-36:	As above with increasing HgS.
1.88 1.89 1.20	36-44:	Soft granular material loaded with HgS.
0.80	44-48:	Barren tan mottled chert with Fe only.
1.86	48-52:	Powdery yellow with strong pink discoloration; some evident HgS; and rotten cream cherts.
0.99 0.83	52-60:	Iron stained, typical andesite.
0.69	60-64:	return of soft,yellowish fines; trace HgS.
0.58	64-68:	yellowish very fine with traces HgS.
0.41	68-72:	As above and coarse chert last foot.
	72-74:	Ditto, with top of andesite @ 74 feet.

Hole 968-72:

Location: 1780E, 112-S.
Elevation: 795

9.18 1.57	0 -16:	Loose, light colored dump with abundant HgS.
61 0.76 21 0.74	16-24:	Brown, soily groundmass with fragments of HgS.
0.90 0.72	24-32:	As above.
0.74	32-36:	Same brown fines, and increasing fragments of HgS.
1.24 1.25	36-44:	Remains soft, but good increase in cherts and HgS.
2.01	44-48:	White sample; increase in chert and good HgS.
1.58	48-52:	Powdery with chert and persistent HgS.
2.15	52-56:	As above, more cherts and excellent HgS.
2.47 2.14	56-64:	Cherts, and very excellent HgS in cherts and fines.
2.23 1.85	64-72:	As above and vert strong HgS.
1.24	72-76:	Yellowish chert, persistent HgS of slightly lower grade.
3.08	76-80:	Extremely high grade, very strong HgS in broken clean cherts
9.00	80-82:	As above. Sharp contact with andesitic clays at 82.

968-73

Hole 968-73

Location: 195-E, 38-S
Elevation: 793

0.16	0 - 8:	Brown sandy material
0.20 0.33	8 -12:	As above and some clay andesite and fragments of chert with HgS.
0.48	12-16:	Brown unit with increase in chert fragments with HgS.
0.91 0.41	16-24:	Brown unit and traces HgS.
0.56 0.74 0.58	24-36:	Tan cherts with no shows to slight traces HgS.

Hole 968-73, concluded.

0.45	36-40:	Brown, soft weathered material with scattered chips of chert, and some HgS. Sample is damp.
0.92	40-44:	weathered with improving HgS in coarse chert fragments.
1.06	44-48:	Buff, finely broken cherts and scattered fair HgS.
1.15 1.67	48-56:	As above but powdery to minor HgS.
2.51	56-60:	Same, with good HgS.
	60-61:	Andesite unit.

968-74

Hole 968-74

Location: 44-E, 37-S.
Elevation 800

0.50 0.26	0 - 8:	Brown weathered unit with traces HgS.
1.32	8 -12:	As above with HgS fragments and chert increasing.
0.76 1.15	12-20:	Same brown weathered unit, with chert and HgS fragments.
1.09	20-27:	Tan cherts and scattered fair HgS
1.09	27-28:	Hard silica. mottled cherts, considered andesite base.

B and B Mine Area

Reference point is portal of bottom tunnel for all B and B drill holes. Elevation datum is rail of ore bin, using 1000 feet.

Hole 968-9:

Location: 158-W, 723-N
Elevation: 1056.

0- 8: White chert, HgS paint with HgS only average; neither high nor low grade.

8 -12: Chert; HgS increases.

12-16: Excellent HgS, with 75% fines and 25% cherts.

16-44: White powdery material without values.

44-104: Creamy, powdery material; no values.

104-112: Cherts with minor HgS in scattered amounts.

112-122: Cherts without apparent HgS

122-124: Andesite.

968-10

Hole 968-10

Location: 118-W, 755N
Elevation: 1043

0 -4: Loamy tan material;traces HgS

4 - 12: White and powdery material;No HgS

12-52: White and buff powderymaterial; traces of chert; no apparent HgS.

968-11

Hole 968-11

Location: 68-W, 630-N.
Elevation: 1036.

0 -16: Cherts and fines; no apparent HgS

16-20: Cherts with a trace HgS.

20-24: White, porous, soft powdery material without HgS.

Hole 968-12:

Location: zero-W, 558-N
Elevation: 1028

0 -12: Cherty section; fair HgS color but not exceptional.

12-20: Soft and porous, with faint pink color.

20-38: Very white and soft; no values.

968-13

Hole 968-13:

Location: 182-E, 488-N
Elevation: 993

0-12 Brown cherts and ground mass with high gradevHgS.

12-16: White soft, powdery material also with HgS.

16-40: All white and soft with no value.

968-14

Hole 968-14

Location: 235-E, 572-N.
Elevation 983

0.43
0.82
1.12
0.41

0 - 16: Brown soily and chert, possibly with some slight values.

0.41
0.35
0.49
0.35
0.40

16- 40: Massive, hard, creamy chert; no values.

Goering North and South Areas

Holes located on basis of Gardiner coordinate system, established on basis of magnetic north without correction. Elevation of 1000 for Hole 7, is datum from which all elevations have been worked out.

Hole 68-13

Location: 705N and 215E
Elevation: 1028

0 -40: White taley, powdery material without obvious value.

40-50: Same material, but with heavy pink color from contained mercury.

50-87: Mixture of taley, powdery fines; some white and yellowish cherts. No HgS

87-112: Massive blue-gray cherts laced with fine quarts, some iron oxides;

68-14

Hole 68-14

Location: 610N and 205E
Elevation: 998

0 -25: White, taley and powdery with no apparent HgS.

25-35: Same formation, but with about 30% cherts; samples very pink from HgS content.

35-55: Buff to white chert with traces of HgS, mostly as paint.

55-65: Solid white and tan cherts; no values.

65-75: Cherts and finer powdery material.

75-87: Pure white, taley,powdery material

87-90: Massive white and tan chert.

968-15

Hole 968-15:

Location: 1140N and 455E.
Elevation:1078

0 - 5: Brecciated rhyolite cap rock, heavily mineralized with iron and some HgS

Hole 968-15, concluded

5 -16: Buff, soft powdery material with traces of chert pebbles and some HgS

16-24: Good HgS in buff powdery type, and some sharp chert.

24-32: White chert with minor powdery material; average HgS at top, increasing at depth.

32-40: White powdery material, pink from HgS content towards base.

40-44: Brown soft, powdery material, mainly from iron oxide content, and possibly from some HgS.

44-52: 50/50 cherts and fines, white to gray, with iron oxide and traces HgS.

52-77: evenly divided cherts and fines, with HgS, good to fair.

77-81: Massive white chert.

81-112: Evenly divided white cherts and fines, with HgS scattered throughout.

112-132: solid white chert with traces HgS.

968-16

Hole 968-16

Location: 1095N and 608E
Elevation: 1072

1.40 0 - 4: Red soil with possible HgS.

1.58 4- 8 Cherts with HgS, about 60%; fines with HgS, about 40%.

1.73 8- 12: Finely divided material with good HgS.

2.31 12-16: Dominantly chert, laced with HgS, and fines, all with apparent excellent grade.

1.07 0.76 1.12 1.28 16- 36: Dominantly powdery fines, with persistent HgS, of lower value than above, but promising.

1.44 36-40: Heavy cherts with good HgS.

0.74 40-44: All white cherts with some HgS in fines.

0.16 0.10 0.08 44-56: White cherts with no shows.

Hole 968-17

Location: 1053N and 662E
Elevation: 1066.

0-12 0.16
12-16 — 0.86 0- 16: White powdery material with some cherts and without HgS; very poor recovery.

0.08
0.04
0.24
0.4 16-32: Evenly divided white cherts and fines, all with some HgS.

0.00 32-36: Increase in iron oxides; all cherts with minor fines; HgS in both.

0.00 36-40: As above.

0.08
0.07 40-46: Evenly divided cherts and fines with encouraging HgS.. Hole guage tighte nd; had difficulty coming out of hole; no further progress.

968-18

Hole 968-18

Location: 1362N, and 710E.
Elevation: 1085

NIL 0 -12: Silicified rhyolite porphyry (cap rock) with heavy iron oxide.

NIL 12-30: Brecciated rhyolite porphyry with increase in iron oxide.

NIL 30-44: Fresh rhyolite porphyry.

968-19

Hole 968-19:

Location: 1262N and 422E.
Elevation: 1092

0.20
0.15 0 - 8: Brown ferruginous material with chert fragments.

0.21
0.18
0.40
0.15 8 -20: Tan powdery material, 50% chert, without HgS.

0.20
0.20
0.18
0.23 20-36: Buff, very powdery material with traces HgS.

36-40 - ?

0.55
0.66
0.59
0.46
0.16
0.08 36-60: Evenly divded fines and tan cherts; fines with pale ferrous irin and possible traces HgS.

0.23
0.23 60-68: As above but with clay pellets, suggesting gouge zone.

Hole 968-19, concluded

0.49 68-72: Buff fines with pinkish color suggesting minor HgS.

0.24 72-76: Drilled harder; cherts now 30%; minor iron oxide with traces HgS; sample pinkish; more gougey pellets.

0.16 0.16 0.23 0.16 0.24 76-96: Evenly divided white fines and cherts; no suggestion of HgS.

0.24 96-104: 75% pure white chert, with some scattered weak HgS.

0.24 104-108: Softens slightly; 50% cherts; no definite HgS, but sample is pinkish.

0.08 0.16 108-118: Massive, creamy to white chert; traces of HgS in 25% of fines, and some paint on cherts.

968-20

Hole 968-20

Location: 705N and 170E
Elevation: 1028

0 - 8: White powdery material, with HgS in traces.

8 -24: Powdery at top with increasing HgS and cherts at base, and persistent HgS .

24-32: Heavy cherts, possibly slightly rhyolitic. No HgS.

32-40: Evenly divided fines and cherts; traces of HgS.

40-68: Yellowish and white powdery material; no HgS.

68-80: Heavy redirون, rhyolite breccia.

80-88: White powdery material with pinkish color.

88-89½: Hard cherts; no progress and hole stopped.

968-21

Hole 968-21

Location: 713N and 112E.
Elevation: 1029

0 -12: White chert and white powdery material scattered HgS

Hole 968-21, concluded.

12-26:	Mostly white powdery material, some chert and no obvious HgS.
26-38:	Red iron oxide zone; rhyolite breccia.
38-48:	Red with occasional white streaks, about 50/50; discolored cherts and fines; No HgS.
48-52:	Powdery buff material with a suggestin of HgS.
52-56:	Hard white chert with possibly some white powder. No HgS.
56-64:	Evenly divided white cherts and white powdery material, with reappearence of HgS in encouraging quantity.
64-68:	Hard red rhyolite breccia.
68-72:	Cherts with no value.

968-22

Hole 968-22:

Location: 747N and 292E
Elevation: 1035

0 -4:	Tan iron stained, powdery crumbd mass with pebbles of chert and mixed rock.
4 -8: 8 -12:	Evenly mixed white cherts and white powdery material, with traces HgS.
12-16:	About 80% white to cream cherts all with promising HgS coloration.
16-20:	Massive creamy cherts with no HgS.
20-24:	About 70% white fines, and 30% creamy cherts with no HgS.
24-32:	White powdery material with trace HgS.
32-40:	White and powdery, slightly tinted with fine HgS.
40-48:	50% cherts, all impregnated with pink HgS, and 50% white fines with HgS.
48-52:	All white powdery, with faint pink discoloration.
52-56:	Dominantly white powdery with HgS, and 20% cherts with light HgS.

Hole 968-22, concluded

56-64: Mostly white powdery material; scattered white chert.

64-80: White powdery material; no shows

80-92: White cherts, 40% and white powdery 60%

92-112: White cherts.

112-119: Hard creamy chert; no progress; stopped.

968-23:

Hole 968-23:

Location: 755N and 250E
Elevation: 1035.

0 -32: Pure white powdery material with complete lack of HgS.

32-56: As above with 20% white chert.

56-60: Dominantly tan fines with no shows: but with some cherts carry traces HgS.

60-72: Tannish soft and powdery material with traces of HgS.

72-76: Powdery and pinkish with possible values.

76-80: White powdery material.

80-84: Massive chert, slightly broken with traces of HgS.

84-92: Increase in broken and brecciated chert with HgS and iron oxide.

92-116: Creamy cherts and minor fines with scattered light HgS.

116-137: Massive yellowish and creamy cherts with slight traces HgS, Tough drilling and stopped.

968-24

Hole 968-24

Location: 760N and 200E
Elevation 1037

0 -20: Fine white powdery, traces chert; no HgS.

20-32: As above with traces of HgS

32-36: 50-50 fines and cherts; fair HgS.

Hole 968-24: Concluded:

36-40: Dominantly fines with minor chert with traces of HgS in both.

40-44: All tan to brown fines, gritty and not powdery, well mineralized with HgS and FeO.

44-48: As above with increased chert, Feo and HgS.

48-52: White powdery and chert with persistent HgS throughout.

52-60: Cherty with good pinkish color in abundant fines.

60-64: 75% creamy chert with traces HgS, and remainder fines with fair HgS.

64-68: Hard at start and then broke down; 50% verypowdery, dark gray fines with probably FeO and 50% gray, grainy chert, laded with FeO.

68-72: Very fine, powdery, gray, with suggestion of pink discoloration. No chert.

72-80: White to creamy powder; no obvious HgS.

80-92: 50% creamy chert with minute quartz stringers and HgS; and 50% pinkish, powdery fines.

92-96: Creamy powder with only traces HgS

96-100: 50% cherts and 50% fines all with minor HgS.

100-104: Chert with greatly increased HgS.

104-112: Mostly cherts with heavy HgS in chert and fines.

112-116: White cherts and scattered HgS, a little lower grade than above.

116-120: Dense creamy to tan cherts with traces of HgS.

120-126: Hard creamy chert.

968-25

Hole 968-25

Location: 765N and 150E
Elevation: 1038

0 - 4: White powdery material; no HgS.

Hole 968-25 Concluded

4 -20: Same fines and about 20% chert; no HgS

20-24: Fines and slight increase in chert; traces of HgS.

24-28: Tan fines, well loaded with HgS, and 10% barren cherts.

28-32: White fines with decrease in HgS

32-36: Pure white powdery material;no HgS

36-72: All powdery and minor white chert; no apparent HgS.

72-76: Mixed fines and chert; possinle trace of HgS.

76-88: 75% cherts and slight increase in fine HgS.

88-96: Pure white flourey and no HgS.

96-100: White,powdery and heavy HgS.

100-104: As above and 25% chert; laced with quartz, FeO and HgS.

104-108: Cherts with good HgS coloration.

108-112: Cherts and fines; lighter HgS.

112-116: Cherts with some HgS and FeO; abundant fines, heavily loaded with HgS.

116-120: As above, with cherts well mineralized with HgS and FeO.

120-121½: As above.

121½-122: Hard and no progress in white to gray chert without values; lost cutting shoe in hole and abandoned hole.

968-26

Hole 968-26

Location: 772N and 100E
Elevation: 1041.

0 - 4: Fine powdery material with minor chert and traces of HgS.

4 -12: Pure white powdery with no HgS

12-16: Gritty, white powder with fair HgS

16-20: White powdery with improving HgS

Hole 968-26, concluded

20-24: White powdery material with heavier HgS.

24-28: Same material with decreasing HgS.

28-32: Heavy red discoloration, probably from iron oxide, accompanied by some HgS; chert increasing slightly.

32-36: 50% fine chert and 50% gray to white fines; good HgS is persistent.

36-44: 80% chert with fair HgS; remainder is fines with HgS dropping off.

44-48: White powdery material is 70% and cherts about 30%; neither has HgS.

48-56: Fine powdery white material with good pink discoloration.

56-60: As above with obvious increase in HgS.

60-72: Start of possible change; dominantly cherty carrying HgS and some FeO.

72-80: Pure white powdery again with good HgS.

80-84: Pure white powdery material without HgS.

84-88: Powdery with good pink discoloration.

88-92: As above with increase in chert; trace HgS. No penetration in hard rock at 92.

968-27

Hole 968-27

Location: 783N and 50E
Elevation: 1041

0 - 8: White silty and gritty powder with minor cherts and no HgS.

8-16: As above.

16-20: 50% creamy cherts with no HgS in cherts or fines.

20-24: Fines and no HgS.

24-40: White powdery and cherts with no shows.

40-44: Iron oxide loaded cuttings; ground firms up; progress very slow; last two feet extremely slow; hole bottomed in probable rhyolite breccia.

Hole 968-28

Location: 608N and 112E
Elevation: 995

0 - 4:	Poor recovery; cherts and some HgS
4 - 8:	White powdery material.
8 -16:	Cherts with scattered HgS.
16-20:	Abrupt change to broken cherts with good HgS mineralization.
20-24:	As above and slightly richer in HgS.
24-32:	White chert and fines with only traces of HgS; drilling hard.
32-40:	Mineralized fines (cherts and powder), all good pink color.
40-44:	Cherts increase to 50%, but fines have good HgS.
44-48:	Persistent good HgS with dominant fines.
48-52:	Powdery white fines.
52-57:	Massive white to gray chert, laced with iron oxide, and perhaps a trace of HgS.

968-29

Hole 968-29

Location: 610N and 62E
Elevation: 992

0.08	0 - 4:	Heavy chert with strong FeO; probably rhyolite breccia capping.
0.33	4 - 8:	Abrupt change to fine white chert; scattered HgS.
? 0.08 0.00 0.00	8 -20:	Powdery material with strong HgS.
0.08	20-24:	50% gray to white chert, weakly laced with FeO and HgS; 50% fines with considerable HgS.
0.08 0.00 0.00 0.00 0.00	24-44:	Hard cherts with HgS throughout as fines and working through cherts.
0.00	44-50:	Massive cherts and HgS.
0.08	50-51:	Smooth gray to buff, hard chert, without shows; drilling slowed down to no progress; withdrew from hole.

Hole 968-30:

Location: 600N and zero E.
Elevation: 987.

0.00 0 - 4: White, slightly cherty with fair HgS.

0.08 4 -16: Mixed cherts and fines all white; HgS in traces to nil

0.00 0.08 0.16 16-20: As above with HgS in traces only.

0.25 20-24: Cherty and white with scattered HgS.

0.00 0.06 0.20 24-52: Heavy chert with good HgS.

36-40 1.71 0.08 0.42 0.66 52-56: Hard compact white to creamy dense chert with HgS in traces only. 0.00

0.13 56-60: Hard clean chert with good HgS.

0.08 0.00 60-68: Same compact chert with decrease in HgS.

0.00 68-72: Pure chert as above with trace to nil of HgS.

968-31

Hole 968-31:

Location: 580N and 100W.
Elevation: 978

0.23 0 - 4: Clean white chert with minor HgS; slightly tan fines; minor HgS in chert and very minor HgS in fines.

0.96 0.16 4 -12: Very hard white chert with HgS in traces only.

0.16 12-16: Clean white to buff chert with traces HgS.

0.33 0.00 16-24: Cherts as above with HgS increasing.

0.08 24-28: Sharp change to tan cuttings in chert and abundant HgS.

0.08 0.00 0.40 0.23 28-44: Persistent chert and fair to good HgS.

0.25 0.32 0.08 0.23 44-62: Cherts and scattered HgS throughout.

60-64 62-72: White powdery material with no HgS

0.00 0.08 0.00 0.08 72-76: Powdery material with pink coloration.

0.08 76-85: Heavy cherts, red, brown, black, orange and white; tentatively set as rhyolite.

Hole 968-32

Location: 530N and zero E
Elevation: 976

0.8 0 - 4: Tan soil and chert fragments and some scattered HgS.

0.16 0.08 0.26 4 -16: Broken white chert with traces HgS

0.25 16-22: As above and a very slight increase HgS.

0.08 0.08 22-28: Very hard, glassy, white to yellowish
0.40 28-30: chert with traces HgS.

0.79 30-32: Cuttings show some increase in HgS, especially in fines, which amounts to about 10%.

0.99 0.25 32-44: Change to much finer chert particles, and an abrupt increase, fair to good HgS.

Forced to discontinue hole because of loss of hole guage.

968-33

Hole 968-33:

Location: 520N and 52E
Elevation: 998

0.44 0 - 4: Tan grit and fine fragments of chert with traces of HgS.

0.59 4 - 8: As above with fair HgS.

0.25 8 -12: Tan to white fines, and minor chert;. scattered HgS throughout but weak.

0.08 12-16: Still tan, gritty and fine, with increase in chert and sharp increase in HgS.

0.16 16-20: All white, brittle chert; some stained and some dark, with fair HgS throughout.

OK 0.10 0.00 20-28: Same cherts and decrease in HgS to fairly low-grade.

0.08 0.08 28-36: Cherts and very poor HgS.

0.08 0.08 0.08 36-44: Cherts and abrupt increase in HgS.

0.10 0.16 0.08 44-56: Same cherts with decreased HgS.

0.08 0.08 56 -62: Cherts with increase HgS; some crystalline.

62-64: Pure white chert with no obvious value.

0.28 0.23 0.12 64-76: As above with traces of HgS.

Hole 968-34:

Location: 380 N and 492 E
Elevation 949949

0.08 0.41 0 - 8: Tan, soft, damp, iron-stained (ferruginous) soil with chert fragments.

0.66 0.58 0.24 8 -20: 100% white, powdery ash with no value.

0.41 20-24: Tan to white powdery material with traces HgS.

0.41 24-28: Hard cherts and slight increase HgS.

0.09 28-32: Cherts and minor fines; all white; traces of HgS.

0.16 0.41 32-40: White powderymaterial; no HgS.

0.36 40-44: White cherts and 25% fines; some HgS in fines.

0.16 44-48: Very hard white chert.

0.38 48-51: As above.

0.08 51-56: Slight increase in fines and HgS in fines.

0.08 0.41 0.33 56-68: Cherts; about 40% of cuttings are light brown, probably iron stained silica. Remainder are white cherts and fines with traces of HgS.

0.36 0.16 68-76: Pure white, clean chert.

0.66 0.41 0.21 76-88: Cherts and fines, carrying fair HgS.

0.82 88-92: Slight decrease in HgS to very low grade.

0.08 1.28 92-97½: Very hard and same as above.

968-35

Hole 968-35:

Location: 358N and 600E
Elevation: 935.

0.30 0 - 4: Broken ground with sand and pebbles.

0.30 4 - 6½: Red Rhyolite Breccia cap-rock

0.36 0.41 6½-16: White cherts with trace HgS.

1.24 16-20: 50-50 cherts and fines; white; abrupt HgS increase; encouraging amount in fines.

0.26 20-24: Increase in finely divided material with tannish color; slight HgS decrease.

Hole 968-35 (concluded)

0.38 24-28: Same and abundant buff, gritty material tan in color, and some improvement in HgS.

0.40 0.08 28-36: Chert and HgSnow cutting thru chert.

0.08 0.28 0.08 0.08 0.28 0.08 0.08 36-61: Hard, tan cherts without shows. Hardness stopped progress.

968-36:

Hole 968-36:

Location: 495N and 100E.
Elevation: 973

0.43 0 - 4 Clean, tan, gray and tinted cherts, with HgS throughout and minor tan fines with HgS.

0.69 4 - 8 Considerable less sample; some chert with HgS, but dominantly soft, white material without value.

0.56 8 -12: All white and tinted, sharp chert with fair to good HgS in seams and disseminations.

? 0.91 0.41 0.36 12-24: All clean cherts with strong, brilliant HgS and silica cutting into cherts.

0.0 24-28: Increase in gray and yellowish chert; slightly decreasing HgS.

0.20 0.74 0.10 28-36: As above with fair HgS.

@ 36½ drill penetrated underlying tunnel.

968-37

Hole 968-37:

Location: 460N and 150E
Elevation: 969

0.87 0 - 4: Ferruginous fines and some chert; No HgS.

0.16 4 - 8: White to cream chert and scattered HgS and red iron oxides.

0.69 8 -12: As above but no oxide; silica becoming locally glassyl Hgs slightly more.

0.16 0.73 12-20: White to cream chert; traces HgS

0.40 0.16 20-28: Sharp change to cherts with considerable HgS and iron oxide.

0.08 28-32: Cherts with increase FeO. and some minor HgS.

Hole 968-37, concluded

	32-36:	Creamy cherts and some faint HgS stain.
1.04	36-40:	As above and slight increase in HgS
0.70	40-44:	Creamy, clean chert with trace HgS
0.70 0.21 0.21	44-52:	Soft, powdery, white, material; no HgS.
0.16	52-56:	Hard, white opaque chert.

This hole also penetrated the underlying tunnel.

968-38

Hole 968-38:

Location: 345N and 700E
Elevation: 924

0.74 0.16 0.10	0 - 4 4 -12	Fine, buff to white, powdery material with good HgS
0.39 0.48	12-20:	White powdery and soft with persistent traces of HgS.
0.41	20-24:	Increasing chert, and traces HgS.
1.09	24-28:	All fine with slight increase in fine HgS.
1.32	28-32:	Heavy tan to buff chert and abrupt increase in good HgS.
1.29	32-36:	Cherts but considerably less HgS.
0.00 0.59	36-44:	Massive tan chert; only slight HgS discoloration.
44-48 - 1.24 0.76 0.25 0.49 0.18 0.12	44-70:	All chert with traces HgS.

968-39

Hole 968-39

Location: 350N and 800E
Elevation: 914

0.16 0.59 0.50	0 - 8: 8 -12:	Mixed fines and buff cherts with scattered HgS As above and slight increase HgS.
0.46 0.52	12-20:	Cherts and fines with traces HgS
0.41	20-24:	Light tan cherts, almost glassy; traces HgS
0.09 0.08 0.08 0.16 0.09	24-44:	Cherts and powdery mixed; no apparent HgS.
0.06	44-48:	Soft powdery and chert; slight FeO discoloration.

Hole 968-40

Location: 645N and 632E
Elevation: 1020

0.16 0 - 4: Fill;

0.34 0.08 0.50 0.09 0.16 4 -24: Mixed cherts and light tan, iron oxide stained; ferruginous matrix with traces HgS

0.22 0.34 24-32: White, powdery, tuffaceous with scattered tan and pink discoloration.

0.00 0.08 32-38: Pure, white powdery, with less pinkish discoloration.

0.18 0.08 38-48: Creamy to white chert and no HgS.

0.18 48-52: Dominant white powdery, with minor chert and no HgS.

0.00 0.00 52-64: Powdery white material with return of minor HgS, slightly pink.

0.00 0.00 0.00 64-76: Increasing HgS in fines; some chert and some rotten material with considerable iron oxide.

0.17 0.00 0.00 0.00 76-92: About 75% fines and 25% cherts; heavy HgS in fines; chert has possible traces.

0.00 92-96: [redacted] with [redacted], FeO, groundmass, possibly with HgS.

0.16 96-100: Finely fragmented chert with promising HgS color.

0.08 100-104: Same fine cherts and good HgS.

0.00 104-108: Cherts; scattered fine HgS; and Hgs and FeO working into cherts.

0.08 108-112: Cherts and fines; possibly slightly less HgS and clusters of rotten chert in watery red oxidation and soft material; this was depth limit for casing at hand; preferred not to drill deeper with tri-cone rock bit.

968-41

Hole 968-41:

Location: 700N and 685E.
Elevation: 1020

0.16 0.16 0 - 9: Dump material

0.08 9 -20: Red rhyolite breccia, cap rock; hard drilling; abandoned location.

Hole 968-42

Location: 1075N and 700E
Elevation: 1026

0.00 0 - 4: Brownish soil and mixed cherts, including some possible rhyolite cap rock.

0.08 4x-12: Buff to white cherts with traces HgS.

0.41 0.25 12-30: Creamy to light tan hard chert and no shows.

0.00 0.00 30-38: Hard, tan massive chert, laced, erratically with red to pinkish streaks and microveinlets of clear quartz.

Progress slowed down; put on tri-cone rock bit, and drill rotary from bottom of larger casing.

0.00 0.00 38-41: Tan chert with weak HgS.

0.00 41-52: As above.

0.00 52-56: Softer; drills faster; more porous chert with possibly, finely divided cinnabar.

56-67: Same cherts but gradual decrease in pink coloration.

no sample 67-74: Material softer; a sharp change with very strong, pink coloration.

0.20 74-78: Lighter pink coloration.

0.16 78-82: Strong pink coloration.

82-86 0.16 82-96: White cherts with only a trace HgS

93-96 0.41

0.00 96-100: Return to pink coloration of cherts.

0.00 100-104: Strong pink coloration.

0.08 104-108: White cherts with decreasing pink.

0.00 108-112: Pink coloration; note: all of above is from fine cuttings; separation of powdery tuff from chert is difficult.

0.00 112-116: Light pink persists; material seems chertier.

0.00 0.00 116-127: White chert with HgS in traces; lost air circulation; abandoned hole.

Hole 968-43

Location: 965N and 765E
Elevation: 1021

0.00 0.09	0 - 7:	Hard, red, brecciated-rhyolite cap.
0.08 0.08	7 -16:	Hard white opaque chert; some buff chert; No HgS.
0.00	16-20:	Same tan, buff cherts and traces HgS.
0.00 0.02	20-30:	Massive, brown solid cherts; traces HgS.
	30:	Changed to rotary tri-cone drilling.
0.00	30-34:	Tan and cherty.
0.00	34-38:	Powdery and faint pink color.
0.09 0.19	38-46:	Powdery and white.
0.33 0.49	46-54:	Very powdery and faint pink.
0.46	54-58:	Sharp change to heavy pink discoloration in powdery formation.
0.24 0.33	58-66:	As above, but much lighter pink to white.
0.24 0.24	66-74:	Excellent HgS; pink color on powdery.
0.08 0.08	74-82:	Chert increasing and HgS seems good to excellent; this on basis of color.
0.16	82-86:	HgS in cherts and fines.
0.08	86-90:	Fines and good chert, and heavy pink coloration.
0.08	90-94:	Change to all white chert, with only possible traces HgS.
0.49	94-98:	Back to fines and chert and good color.
0.33 0.49 0.41	98-110:	Cherts with no HgS.
0.24	110-118:	Cherts with HgS throughout.
0.41	118-122:	White cherts; lost circulation and stopped hole.

0.01

0.33

0.10

0.39

Hole 968-44

Location: 995N and 600E
Elevation: 1071:

0 - 4: Tan dirty soil.

4 - 8: White and gray opaque chert and scattered white fines with traces HgS.

8 -16: Dominant soft powdery, mixed with chert with fair shows of disseminated HgS.

16-20: 50% massive gray chert and 50% fines with pinkish discoloration; some FeO cutting cherts with traces HgS.

20-24: Massive cherts and traces.

20-24: Put on rock bit and described samples as follows:

24-32: Cherty and suggestion of pink

32-36: White powdery; traces HgS

36-40: As above and slightly cherty

40-44: White powder.

44: came out of hole, and returned to hammer drill, with idea of breaking material to hole drilled at center.

24-28: White and gray cherts; some fines and pink discoloration.

28-32: Massive gray cherts, with FeO in streaks; also probable HgS; sample has pinkish tinge from fines.

32-40: Cherty and fines with no HgS.

40-44: White powdery and some chert; no HgS.

968-45

Hole 968-45:

Location: 892N and 548E
Elevation: 1054

0 - 4: Dark tan, ferruginous, iron oxide zone; fines and fine cherts.

4 - 8 White and gray opaque chert, and scattered white fines with traces HgS.

8-12: D[illegible] with [illegible] of pinkish quartz.

Hole 968-45: concluded

12-20: White, powdery and scattered white chert with traces HgS.

20-28: White, pure powder, with traces of pink.

28-32: New orange-pink, heavy coloration, in white, powdery material.

32-40: Heavy orange-pink discoloration; mostly iron with possible traces HgS.

40-48: Change to pink; HgS is strong, and FeO minor.

48-52: Same heavy pink, and minor orange with traces of chert.

52-60: Increase in white chert, with scattered pink and orange fines.

60-72: Dominantly chert, and new clusters of rotten oxides with chert fragments, and strong HgS.

72-76: Massive white chert and traces HgS.

968-46

Hole 968-46:

Location: 1030N and 458E.
Elevation: 1088.

0 - 4: Surface rubble.

4 -20: 50-50 white chert and fines with some scattered HgS.

20-32: Cherts and traces of HgS.

32-36: Crushed material; pastey balls of iron stained clay, carrying chert fragments. Start of fault zone.

36-40: Same material and perhaps increased fines.

40-46: As above and traces of HgS.

46-52: Abrupt change to tan ferruginous and fine white, cherty to powdery; scattered HgS; continuing gouge.

52-60: As above, and especially gouge nodules.

Hole 968-46, concluded

60-64: Evenly mixed cherts and gouge clusters.

64-68: Same mixture with some fines and traces HgS.

68-72: Gouge and chert.

72-76: Increase in gouge to 60% and chert fragments in gouge about 40%.

76-80: Increasing fines, cherts, and tapering off of gouge; slight increase in HgS.

80-84: Possibly fair HgS; fines with pink discoloration.

84-102: White cherts with traces crushed material; traces of HgS.

968-47

Hole 968-47:

Location: 1040N and 530E
Elevation: 1081.

Collared in rhyolite-breccia, cap rock. Not drilled, in view of time to penetrate and a worked out schedule, with time getting short.

968-48

Hole 968-48:

Location: 1192N and 582E.
Elevation: 1072.

0-16: Mixed ferruginous, cherts and white fines, with scattered pellets of soft crushed material with FeO; possible faulting.

16-20: Heavy cherts, loaded with average pink coloration.

20-28: All fines with scattered HgS; light from ferrous content.

28-32: As above and some gougey clusters; traces HgS.

32-40: light tan fines; no HgS.

40-44: White fines with minor tan fines.

44-48: White powdery with slight pink coloration

48-52: Same with fair to good pink coloration.

Hole 968-48 . concluded

52-56: Light tan powdery material.

56-60: increasing tan powdery without HgS .

60-68: Light tan powdery, with traces HgS .

68-84: White opaque cherts.

968-49

Hole 968-49:

Location: 1153N and 650E
Elevation: 1064.

0 - 4: Mixed white to reddish chert and dirty, gritty soil.

4 - 8: Yellowish fines, white cherts and traces of gouge fragments, with iron oxide.

8 -12: Dominant white fines with new light pink coloration and traces pink quarts; also pieces of gouge clusters.

12-16: Increase in gouge clusters; new chert, tinted and laced with HgS.

16-20: Hard creamy cherts, minor fines; Traces HgS/

20-24: Fines and cherts, abrupt shift to tannish pink with scattered HgS.

24-44: Dominant fines with good pink and HgS, first
44-48: four feet and fair discoloration and HgS? last 8 feet.

48-52: Dominant chert with good HgS throughout.

52-66: Chert with scattered HgS.

66-68: Massive chert; slow penetration.

968-50

Hole 968-50

Location: 1200N and 458E
Elevation: 1089

0.16 0 - 2: Surface dirt and cherts.

0.41 0.66 2 -12: Dark tan, ferruginous unit.

0.74 12-16: As above and traces of white fines and HgS.

0.66 0.47 0.78 16-28: Buff fines;white cherts; traces HgS

Hole 968-50 concluded.

0.33	28-32:	Increase in white chert, some rusty iron chert, and balls of gouge.
0.44	32-36:	Abrupt change to ferrous cherts, similar to cap rock, rhyolite cherts; no HgS.
0.33 0.49	36-44:	All red, tan, brown cherts and mottled cherts, probably cap rock rhyolite.
0.41 0.49 0.33	44-56:	Massive, tan cherts and no HgS.

968-51

Hole 968-51

Location: 525N and 205E
Elevation: 1002

0.00 0.41	0 - 8:	Fill and rubble.
0.58 0.49	8 -16:	Finely divided, gritty to powdery, with some white chert, and persistent low-grade HgS.
0.41	16-20:	As above with HgS showing slight increase.
0.41 0.25 ~~0.49~~	20-28:	20-27: as above but HgS in traces; at 27-28----tough drilling in tough, unaltered rhyolite-breccia cap rock.
0.17 0.16	28-38:	Red, rhyolite breccia, cap rock.
0.33 0.41	38-44:	white, finely fragmented chert and minor fines with traces HgS.
0.44	44-48:	Tan cherts with traces HgS.
0.16	48-52:	Abrupt change to brittle cherts, loaded with reds, oranges etc., and probably scattered HgS.
0.91	52-56:	Cherts and fair to good HgS with minor iron oxide.
1.48	56-60:	Cherts and very high grade HgS.
1.65	60-64:	As above with persistent but lower grade HgS.
0.41	64-68:	Buff to tan chert with minor HgS
0.25	68-70:	Return to hard red, cherty cap rock.
0.08 0.08	70-76:	Dark red, rhyolite breccia cap rock.

Hole 968-51: concluded.

0.16	76-82:	Cherts, heavy with red FeO and pink HgS.
0.41 0.16 0.49	82-94:	Pure white to slightly tan cherts with scattered clear HgS.
0.49 0.49	94-102:	As above with slight decrease in HgS.

968-52

Hole 968-52:

Location: 562N and 49W
Elevation: 981.

0.16 0.26	0 - 8:	Finely divided chert and soil with scattered weak HgS.
0.16 0.08	8 -12:	Granular material and cherts, 50-50 with increase in HgS.
0.08 0.08	12-20:	50-50 soft powdery and cherts, tan from iron oxide; traces HgS.
0.16	20-24:	Abrupt change to dark red to tan to black glassy cherts, similar to those at bottom of 968-31.
0.08	24-28:	Loose white cherts, heavily impregnated with tan iron oxide and pink HgS.
0.26	28-32:	As above but cleaner HgS.
1st day 0.16	32-36:	As above but less HgS.
0.25 0.08 0.49	36-48:	White to creamy tan cherts with minor HgS throughout.
2d day 0.26 0.49	48-56:	white chert and increase in clean HgS but still low-grade.
0.15	56-60:	As above.
0.08 0.26	60-68:	Same cherts and increase in HgS
0.16	68-72:	Heavy tan chert; trace of HgS.
0.33 0.16 0.08	72-82:	Aas above with slight increase HgS
0.25	82-86:	Trisene drilling from78; white chert and trace HgS.
0.41	86-90:	As above and slight increase HgS and FeO.
0.08 0.24	90-98:	White opaque chert with no shows.

Hole 968-53

Location: 570N and 150E
Elevation: 986.

0.08	0 - 4:	Fine and white powdery; no shows.
1.65 0.58	4 -12:	As above.
0.25	12-16:	Powdery and slightly pink
0.75	16-20:	Fine white powdery without shows.
0.16	20-24:	Change to white chert with no shows.
0.33	24-30:	Cream to tan cherts with HgS of low grade.
0.74	30-32:	Very fine white powdery and traces HgS.
0.74	32-36:	Powdery with sharp increase in HgS
2.47	36-40:	White to cream cherts, and fair to good HgS.
2.47	40-44:	Cherts and excellent HgS.
0.91 0.66	44-52:	White cherts without value to traces in lower four feet.
2.80	52-56:	Massive, hard gray chert, with considerable FeO and abundant HgS.
1.40	56-60:	Hard creamy chert without shows; softer drilling lower two feet.
0.82 0.74	60-68:	As above with minor amounts of light HgS.

968-54:

Hole 968-54:

Location: 330N and 32E
Elevation: 874.

0.16	0 - 4:	Mostly fines with scattered HgS; some white chert with trace HgS.
0.38	4 -8	As above and slight increase HgS.
0.25	8 -12:	Cherts increasing to 40%, and HgS of low grade scattered throughout.
1.28	12-16:	Fines heavily mineralized and cherts with iron oxide and HgS pink.
? 0.64	16-20:	As above with very good HgS; some iron; fines are dominant.
0.25 0.16	20-28:	same dominant fines; slight decrease in overall mineralization.

Hole 968-54 concluded

0.16 28-32: White to buff fines with scattered HgS.

0.08 32-36: Fines and minor chert; strong mine ralization, especially very good HgS.

0.17 36-40: As above with slight decrease in Feo and HgS.

0.17 40-44: White fines and cherts; trace HgS.

? 0.50 44-48: Abrupt change to rusty red, rhyolie breccia cap rock.

0.25 48-52: White cherts with traces HgS.

0.17 0.33 52-60: Hard red breccia.

0.00 60-64

968-55

Hole 968-55

Location: 360N and 11W.
Elevation: 874

0.00 0 - 4: White fines and traces HgS.

0.08 4 - 8: White cherts and fines; increase in HgS.

0.16 8 -12: Evenly divided cherts and fines; good HgS in both.

0.16 0.00 12-20: Soft white, fine materal with Feo and HgS.

0.08 20-26: Red, brecciated cap rock.

-24-28 0.00
28-32 - 0.00 0.00 26-36: White cherts, good HgS, and persistent orange FeO.

0.08 0.08 0.25 36-48: White cherts and strong, scattered HgS.

48-52 0.00 48-52: As above with some red breccia.

56-60 0.08 0.25 52-64: Hard red breccia.

968-56

Hole 968-56:

Location: 320N and 10E
Elevation: 873

0.00 0 - 8: Rubble and fill.

0.00 0.00 0.16 0.00 8 -24: White fines and cherts and fair HgS.

0.08 24-28: As above and slight increase in Hgs.

0.08 28-32: Hard white cherts and persistent HgS.

0.08 0.08 32-40: Cherts and increase in HgS

Hole 968-56: concluded.

0.24 40-44: Heavy gouge with FeO

0.00 44-52: Same gouge with some included fines, dominantly iron but traces HgS.

968-57

Hole 968-57

Location: 290N and 10W
Elevation: 871.

0.13 0.16 0.00 0 -12: Dump and fill.

0.08 0.00 12-20: White cherts and scattered Fee and HgS.

0.23 0.00 20-28: As above and minor amounts of possible cap rock breccia; but still good white cherts, FeO and traces HgS.

0.43 28-32: As above and some gouge pellets.

0.44 0.00 0.00 32-44: Heavy red cap rock type with traces white chert.

0.00 0.00 44-52: All soft, shaley, grayish green, mass with pellets of soft gougey rock, heavily iron stained.

0.00 52-56: Same gouge with prounced increase in reddish material, and some dragged silica with pink coloration.

0.00 0.00 56-64: Gougey material; dominantly grayish-green, and suggestive of some rotten cherts in mass.

0.00 64-68: Red Cap rock.

968-58:

Ho 968-58:

Location: 250N and 100E
Elevation: 873

0.41 0 - 4: Dominant gray chert and shows HgS

0.00 4 - 8: gray fines and no shows.

0.00 8 -12: White fines and traces HgS.

0.08 0.00 12-20: Rusty-red fines, red cherts, with some later white and tan; heavy FeO; trace HgS.

0.00 20-24: Increased white cherts; FeO and some positive HgS

Hole 968-58: Concluded

0.08 0.08 24-32: Dominant soft, rusty red; poss traces HgS.

0.08 32-36: Same soft red formation

0.08 36-44: Hard, dark red cap rock.

0.08 44-46: Gouge with cap rock and some white chert.

968-59

Hole 968-59:

Location: 220N and 545E
Elevation: 874

0.16 0.33 0 - 8: Buff, powdery, soft, with traces of chert and no shows.

0.16 8 -12: Soft, tan, broken, gougey and damp; possibly gouge; FeO in abundance and traces HgS.

0.58 12-16: Rusty red fines; all iron; black and red cherts.

0.66 16-20: Clear cherts, white to tinted with definite HgS; some in fines.

0.40 0.16 20-32: Cherts, heavily tinted with pink.

0.16 32-36: Brown, soft, damp, crushed with white chert, FeO colored, and possible HgS.

0.08 36-40: Damp, reddish-brown; heavy FeO; possible crushed zone.

0.08 40-44: Change to white glassy chert; dominant fines; Fee and fair HgS.

0.16 0.49 44-52: Same white cherts, buff fines, FeO and persistent HgS.

0.16 52-56: Cleaner cherts and persistent HgS.

0.09 56-60: Very white, sharp cherts with weaker HgS.

0.08 60-64: Hard, glassy, brittle chert without shows.

ANALYSES

68-13

Depth	Pounds
0 - 5	1.02
5 -10	0.89
10-15	0.69
15-20	0.73
20-25	0.74
25-30	1.56
30-35	3.13
35-40	0.56
40-45	0.49
45-50	0.66
50-55	0.46
55-60	0.16
60-65	0.46
65-70	0.82
70-75	0.08
75-80	0.57
80-85	0.24
85-90	0.24
90-95	Lost
95-100	Lost
100-105	0.16
105-110	0.10
110-112	0.08

68-14

Hole 68-14, on same section and similar to 68-13 lost between hole and laboratory.

DAVID LeCOUNT EVANS, CONSULTING GEOLOGIST

ASSAY ANALYSES

968-1

Depth	Pounds
0 - 4	1.05
4 - 8	1.05
8 -12	Lost
12-16	1.05
16-20	0.79
20-24	6.00
24-28	6.60
28-32	3.02
32-36	0.00
36-40	0.08
40-44	0.33
44-48	0.08
48-51	0.09
51-52	Nil

968-2

Depth	Pounds
0 - 4	0.22
4 - 8	0.20
8 -12	0.24
12-16	0.53
16-20	0.43
20-24	0.20
24-32	0.94
32-36	1.81
36-40	0.92
40-44	0.90
44-48	0.90
48-52	1.48
52-56	1.14
56-60	1.23
60-64	0.08

968-3

Depth	Pounds
0 - 4	0.66
4 - 8	0.33
8 -12	0.24
12-16	0.08
16-20	0.33
20-24	0.41
24-32	4.13
32-36	9.58
36-40	3.30
40-44	3.96
44-50	1.23
50-54	0.16
54+	0.08

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ASSAY ANALYSES

964-4

0 - 4	0.49
4 - 8	0.49
8 - 12	0.33
12-16	0.57
16-24	1.65
24-28	Nil

964-5

0 - 4	0.36
4 - 8	0.20
8 -12	0.33
12-16	1.07
16-20	0.49
20-24	0.08
24-28	0.08
28-32	Nil

968-6

0 - 4	0.95
4 - 8	Lost
8 -12	0.57
12-16	0.00
16-20	0.00
20-24	0.09
24-28	0.08
28-32	0.00

968-7

0 - 4	0.24
4 - 8	0.10
8 -12	0.08
12-16	0.16
16-20	0.77
20-24	0.41
24-28	0.16

968-8

0 - 4	0.24
4 - 8	0.08
8 -12	0.24
12-16	0.16
16-20	0.16
20-24	0.33
24-28	Nil

DAVID LeCOUNT EVANS, CONSULTING GEOLOGIST

ANAKYSES

968-9

0 - 4	1.07
4 - 8	0.74
8 -12	1.07
12-16	4.95
16-20	0.49
20-24	0.20
24-28	0.76
28-32	0.90
32-36	0.33
36-40	0.08
40-44	0.09
44-48	0.09
48-52	0.82
52-56	0.92
56-60	0.16
60-64	0.33
64-68	0.66
68-72	0.66
72-76	0.74
76-80	1.40
80-84	0.41
84-88	0.53
88-92	0.16
92-96	0.08
96-100	0.16
100-104	Nil
100-108	Nil
108-112	Nil
112-116	Nil
116-120	Nil
120-124	Nil

968-10

0 - 4	0.08
4 - 8	0.16
8 -12	0.24
12-16	0016
16-20	0.13
20-24	0.41
24-28	0.20
28-32	0.33
32-36	0.82
36-40	Nil
40-44	Nil
44-48	0.16
48-52	0.22

DAVID LECOUNT EVANS, CONSULTING GEOLOGIST

DAVID LECOUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-11

0 - 4	0.59
4 - 8	0.16
8 -12	0.08
12-16	0.16
16-20	0.90
20-24	0.59
24-28	0.49
28-32	0.38
32-36	0.23
36-40	0.19

968-12

0 - 4	0.76
4 - 8	1.63
8 -12	1007
12-16	0.49
16-20	0.66
20-24	0.33
24-28	0.41
28-32	0.92
32-36	0.79
36-38	0.66

968-13

0 - 4	3.30
4 - 8	3.96
8 -12	2.77
12-16	2.55
16-20	0.56
20-24	0.24
24-28	0.16
28-32	0.26
32-36	0.76
36-40	0.57

968-14

0 - 4	0.43
4 - 8	0.82
8 -12	1.12
12-16	0.41
16-20	0.41
20-24	Lost
24-28	0.35
28-32	0.49
32-36	0.35
36-40	0.40

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-15

0 - 4	0.25
4 -12	0.80
12-16	1.47
16-20	4.83
20-24	3.18
24-28	0.70
28-32	3.30
32-36	3.30
36-40	1.00
40-44	1.27
44-48	0.34
48-52	0.34
52-56	0.84
56-60	0.84
60-64	0.84
64-68	0.50
68-72	0.34
72-76	0.50
76-80	0.34
80-84	0.50
84-88	0.17
88-92	0.17
92-96	0.84
96-100	0.63
100-104	0.63
104-108	0.42
108-112	0.42
112-120	0.63
120-124	0.42
124-128	0.42
128-132	0.42

968-16

0 - 4	1.40
4 - 8	1.58
8 -12	1.73
12-16	2.31
16-20	1.07
20-24	0.99
24-28	0.76
28-32	1.12
32-36	1.28
36-40	1.45
40-44	0.74
44-48	0.16
48-52	Nil
52-56	0.08

ANALYSES

968-17

0 - 12	0.16
12-16	0.86
16-20	0.08
20-24	0.09
24-28	0.25
28-32	0.41
32-36	0.00
36-40	0.00
40-44	0.08

968-18

0 - 4	Nil
4 - 8	Nil
8 -12	Nil
12-16	Nil
16-20	Nil
20-24	Nil
24-28	Nil
28-32	Nil
32-36	Lost
36-40	Nil

968-19

0 - 4	0.20		
4 - 8	0.15		
8 -12	0.18		
12-16	0.40		
16-20	0.15		
20-24	0.20		
24-28	0.20		
28-32	0.18		
32-36	0.23		
36-40	Lost		
40-44	0.66		
44-48	0.59		
48-52	0.41		
52-56	0.16		
56-60	0.08		
60-64	0.33		
64-68	0.33		
68-72	0.49		
72-76	0.24		
76-80	0.16		
80-84	0.16		
84-88	0.23	100-104	0.24
88-92	0.16	104-108	0.24
92-96	0.24	108-112	0.08
96-100	Lost	112-116	0.16

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-20

0 - 8	0.00
8 -16	0.24
16-24	Lost
24-32	0.00
32-40	0.08
40-48	0.24
48-56	1.07
56-64	0.74
64-68	0.20
68-72	0.33
72-80	0.00
80-88	0.24

968-21

0 - 4	0.82
4 - 8	0.82
8 -12	0.41
12-16	0.41
16-20	0.13
20-24	0.09
24-28	0.24
28-32	0.00
32-36	0.16
36-40	Lost
40-44	0.16
44-48	0.16
48-52	0.08
52-56	0.00
56-60	0.09
60-64	0.08
64-68	0.08

968-22

0 - 4	0.16
4 - 8	0.16
8 -12	0.08
12-16	0.69
16-20	0.89
20-24	0.92
24-28	0.57
28-32	0.74
32-36	0.74
36-40	0.66
40-46	0.90
46-48	0.24

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-22

48-52	0.33
52-56	0.49
56-60	0.66
60-64	0.41
64-68	4.13
68-72	1.81
72-76	0.57
76-80	0.16
80-84	0.08
84-88	0.09
88-92	0.41
92-96	0.41
96-100	0.33
100-104	0.08
104-108	0.00
108-112	0.08
112-116	0.08
116-119	1.01

968-23

0 - 4	0.08
4 - 8	0.08
8 -12	0.00
12-16	0.09
16-20	0.16
20-24	0.09
24-28	0.09
28-32	0.09
32-36	0.09
36-40	0.09
40-44	0.08
44-48	Lost
48-52	0.00
52-56	0.00
56-60	0.00
60-64	0.16
64-68	0.00
68-72	0.00
72-76	0.00
76-80	0.00
80-84	0.00
84-88	0.00
88-92	0.08
92-96	0.09
96-100	Lost
100-104	0.16
104-108	0.16
108-112	0.00
112-116	0.08
116-120	0.00
120-124	0.16
124-128	0.08
128-132	0.36
132-137	0.24

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-24

0 - 4	0.09
4 - 8	0.16
8 -12	0.08
12-16	0.08
16-20	0.26
20-24	0.16
24-28	0.57
28-32	1.23
32-36	0.63
36-40	0.08
40-44	0.24
44-48	0.09
48-52	0.08
52-56	0.00
56-60	0.08
60-64	0.00
64-68	0.08
68-72	0.08
72-76	0.08
76-80	0.00
80-84	0.00
84-88	0.00
88-92	0.00
92-96	0.00
96-100	0.08
100-104	0.00
104-108	0.24
108-112	0.16
112-116	0.08

968-25

0 - 4	0.00	64-68	0.16
4 - 8	0.08	68-72	0.24
8 -12	0.16	72-76	0.00
12-16	0.16	76-80	0.08
16-20	0.20	80-84	0.16
20-24	Lost	84-88	Lost
24-28	LOst	88-92	Lost
28-32	0.16	92-96	0.08
32-36	1.22	96-100	0.33
36-40	0.24	100-104	Lost
40-44	0.08	104-108	Lost
44-48	0.16	108-112	Lost
48-52	Missing	112-116	0.16
52-56	0.08	116-120	0.00
56-60	0.08		
60-64	0.00		

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-26

0 - 4	0.74
4 - 8	1.73
8 -12	1.02
12-16	1.07
16-20	0.41
20-24	0.00
24-28	0.16
28-32	0.00
32-36	0.41
36-40	0.16
40-44	0.33
44-48	0.16
48-52	0.16
52-56	0.20
56-60	0.36
60-64	0.24
64-68	0.16
68-72	0.41
72-76	0.24
76-80	0.43
80-84	0.00
84-88	0.23
88-92	0.16
92-95	0.16

968-27

0 - 4	0.24
4 - 8	0.13
8 -12	0.08
12-16	0.43
16-20	0.08
20-24	0.09
24-28	0.33
28-32	0.16
32-36	0.08
36-40	0.08
40-44	0.16
44-46	0.00

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-28

0 - 4	1.21
4 - 8	
8 -12	0.40
12-16	0.25
16-20	0.08
20-24	0.11
24-28	0.08
28-32	0.16
32-36	0.08
36-40	0.08
40-44	0.33
44-48	0.08
48-52	0.00
52-57	0.00

968-29

0 - 4	0.08
4 - 8	0.33
8 -12	0.08
12-16	0.00
16-20	0.00
20-24	0.08
24-28	0.08
28-32	0.00
32-36	0.00
36-40	0.00
40-44	0.00
44-48	0.00
4851	0.08

968-30

0 - 4	0/00		
4 - 8	0.08		
8 -12	0.00		
12-16	0.08		
16-20	0.16		
20-24	0.25		
24-28	0.00		
28-32	0.08		
32-36	0.20		
36-40	1.71		
40-44	0.38		
44-48	0.42		
48-52	0.66		
52-56	0.00		
56-60	0.13		
60-64	0.08	72-80	Lost
64-68	0.00	80-84	0.00
68-72	0.00		

DAVID LeCOUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-31

0 - 4	0.23
4 - 8	0.96
8 -12	0.16
12-16	0.16
16-20	0.33
20-24	0.00
24-28	0.08
28-32	0.08
32-36	0.00
36-40	0.40
40-44	0.23
44-48	0.25
48-52	0.35
52-56	0.09
56-60	0.23
60-64	0.00
64-68	0.08
68-72	0.00
72-76	0.08
76-80	0.08

968-32

0 - 4	0.82
4 - 8	0.16
8 -12	0.08
12-16	0.26
16-20	0.25
20-24	0.08
24-28	0.08
28-32	0.40
32-36	0.79
36-40	0.99
40-44	0.25

968-33

0 - 4	0.58
4 - 8	0.58
8 -12	0.25
12-16	0.08
16-20	0.16
20-24	0.10
24-28	0.00
28-32	0.08
32-36	0.08
36-40	0.08
40-44	0.08
44-48	0.10
48-52	0.16
52-56	0.08
56-60	0.08
60-64	0.08
64-68	0.20
68-72	0.25
72-76	0.12

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-34

0 - 4	0.08
4 - 8	0.41
8 -12	0.66
12-16	0.58
16-20	0.24
20-24	0.41
24-28	0.41
28-32	0.69
32-36	0.16
36-40	0.41
40-44	0.36
44-48	0.16
48-52	0.36
52-56	0.08
56-60	0.08
60-64	0.41
64-68	0.33
68-72	0.36
72-76	0.16
76-80	0.66
80-84	0.41
64-68	0.33
68-72	0.36
72-76	0.16
76-80	0.66
80-84	0.41
84-88	0.25
88-92	0.82
92-96	0.08
96-98	1.25

968-35

0 - 4	0.30
4 - 8	0.30
8 -12	0.36
12-16	0.41
16-20	1.24
20-24	0.36
24-28	0.38
28-32	0.40
32-36	0.08
36-40	0.08
40-44	0.25
44-48	0.08
48-52	0.00
52-56	0.25
56-60	0.08

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-36

0 - 4	0.43
4 - 8	0.69
8 -12	0.56
12-16	0.91
16-20	0.41
20-24	0.36
24-28	0.00
28-32	0.20
32-34	0.74
34-36	0.10

968-37

0 - 4	0.87
4 - 8	0.16
8 -12	0.69
12-16	0.16
16-20	0.73
20-24	0.40
24-28	0.16
28-32	0.08
32-36	Lost
36-40	1.04
40-44	0.70
44-48	0.25
48-52	0.25
52-56	0.16

968-38

0 - 4	0.74
4 - 8	0.16
8 -12	0.10
12-16	0.39
16-20	0.48
20-24	0.41
24-28	1.09
28-32	1.32
32-36	1.29
36-40	0.00
40-44	0.59
44-48	1.24
48-52	0.76
52-56	0.25
56-60	0.49
60-64	0.16
64-68	0.12

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

268-39

0 - 4	0.16
4 - 8	0.69
8 -12	0.50
12-16	0.46
16-20	0.52
20-24	0.41
24-28	0.09
28-32	0.08
32-36	0.08
36-40	0.16
40-44	0.08
44-48	0.00

968-40

0 - 4	0.16
4 - 8	0.34
8 -12	0.08
12-16	0.50
16-20	0.09
20-24	0.16
24-28	0.22
28-32	0.34
32-36	0.00
36-40	0.08
40-44	0.18
44-48	0.00
48-52	0.18
52-56	0.00
56-60	0.00
60-64	0.00
64-68	0.00
68-72	0.00
72-76	0.00
76-80	0.17
80-84	0.00
84-88	0.00
88-92	0.00
92-96	0.00
96-100	0.16
100-104	0.08
104-108	0.00
108-112	0.08

968-41

0 - 8	0.16
8 -12	0.16
12-16	0.08
16-20	0.08

DAVID LECOUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-42

0 - 4	0.00
4 - 8	0.[illegible]
8 -12	[illegible]
12-16	0.[illegible]
16-20	0.25
20-24	0.00
24-28	0.00
28-32	0.00
32-36	0.00
36-[illegible]	0.00
38-42	0.00
42-46	0.00
46-50	0.00
50-54	0.00
54-58	0.00
58-62	0.00
62-66	0.00
66-70	Lost
70-74	Lost
74-78	0.20
78-82	0.16
82-86	0.16
86-92	Lost
92-96	0.41
96-100	0.00
100-104	0.00
104-108	0.08
108-112	0.00
112-116	0.00
116-120	0.00
120-124	0.00
124-127	0.00

968-43

0 - 4	0.00
4 - 8	0.09
8 -12	0.08
12-16	0.08
16-20	0.00
20-24	0.00
24-28	0.00
28-30	0.00
30-34	0.00
34-38	0.00
38-42	0.09
42-46	0.19
46-50	0.33
50-54	0.49
54-58	0.46
58-62	0.24
62-66	0.33
66-70	0.24
70-74	0.24
74-78	0.08
78-82	0.08
82-86	0.16
86-90	0.08
90-94	0.08
94-98	0.49
98-102	0.33
102-106	0.49
106-110	0.41
110-116	0.24
116-122	0.41

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

968-44

	Hammer Drill	Rock Bit
0 - 4	0.16	
4- 8	0.09	
8 -12	0.41	
12-16	0.08	
16-20	0.53	
20-24	0.16	
24-28	0.24	0.24
28-32	0.53	0.24
32-36	0.66	0.33
36-40	0.33	0.33
40-44	0.33	0.26
24-44 Average	0.42	0.29

0.29/0.42 = 1/1.45

968-45

0 - 4	0.33
4 - 8	0.08
8 -12	0.08
12-16	0.08
16-20	0.33
20-24	0.16
24-28	0.57
28-32	0.16
32-36	0.00
36-40	0.16
40-44	0.49
44-48	0.66
48-52	0.99
52-56	0.74
56-60	0.90
60-64	0.74
64-68	0.57
68-72	0.49
72-76	0.24

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-46

0 - 4	0.82
4 - 8	0.49
8 -12	0.57
12-16	0.24
16-20	0.24
20-24	0.24
24-28	0.33
28-32	0.24
32-36	0.82
36-40	0.99
40-44	1.65
44-48	0.33
48-52	0.24
52-56	0.24
56-60	0.33
60-64	0.16
64-68	0.16
68-72	0.33
72-76	0.84
76-80	0.33
80-84	0.16
84-88	0.16
88-92	0.16
92-96	Nil
96-100	Nil

DAVID LECOUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-47

0 -10	0.08	(cap rock)

968-48

0 - 4	0.08
4 - 8	0.24
8 -12	0.24
12-16	0.24
16-20	0.41
20-24	0.74
24-28	0.79
28-32	0.49
32-36	0.41
36-40	0.99
40-44	1.73
44-48	4.16
48-52	5.28
52-56	1.70
56-60	0.57
60-64	1.07
64-68	0.53
68-72	0.24
72-76	0.00
76-80	Lost
80-84	0.00

968-49

00-44	0.57
4 - 8	0.57
8 -12	0.66
12-16	1.23
16-20	0.57
20-24	2.14
24-28	1.40
28-32	0.66
32-36	0.44
36-40	1.63
40-44	1.40
44-48	1.73
48-52	2.14
52-56	0.57
56-60	0.41
60-64	0.33
64-68	0.24

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-50

0 - 4	0.16
4 - 8	0.41
8 -12	0.66
12-16	0.74
16-20	0.66
20-24	0.41
24-28	0.33
28-32	0.33
32-36	0.44
36-40	0.33
40-44	0.49
44-48	0.41
48-52	0.49
52-56	0.33

968-51

0 - 4	0.00
4 - 8	0.41
8 -12	0.58
12-16	0.49
16-20	0.41
20-24	0.41
24-28	0.26
28-32	0.17
32-36	0.16
36-40	0.33
40-44	0.41
44-48	0.44
48-52	0.16
52-56	0.91
56-60	1.48
60-64	1.65
64-68	0.41
68-70	0.25
70-74	0.08
74-78	0.08
78-82	0.16
82-86	0.41
86-90	0.16
90-94	0.49
94-98	0.49
98-102	0.49

DAVID LECOUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-52

0 - 4	0.16
4 - 8	0.26
8 -12	0.16
12-16	0.08
16-20	0.08
20-24	0.16
24-28	0.08
28-32	0.26
32-36	0.16
36-40	0.25
40-44	0.08
44-48	0.43
48-52	0.66
52-56	0.49
56-60	1.15
60-64	0.58
64-68	0.26
68-72	0.16
72-76	0.33
76-98	0. 10
78-82	0.08
82-86	0.25
86-90	0.41
90-94	0.08
94-98	0.24

968-53

0 - 4	0.08
4 - 8	1.65
8 -12	0.58
12-16	0.25
16-20	0.25
20-24	0.16
24-28	0.33
28-32	0.74
32-36	0.74
36-40	0.47
40-44	2.47
44-48	0.91
48-52	0.66
52-56	2.80
56-60	1.40
60-64	0.82
64-68	0.74

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-54

0 - 4	0.16
4 - 8	0.38
8 -12	0.25
12-16	1.28
16-20	0.00
20-24	0.25
24-28	0.16
28-32	0.16
32-36	0.08
36-40	0.17
40-44	0.17
44-48	0.50
48-52	0.25
52-56	0.17
56-60	0.33
60-64	0.00

968-55

0 - 4	0.08
4 - 8	0.08
8 -12	0.16
12-16	0.16
16-20	0.00
20-24	0.08
24-28	0.00
28-32	0.00
32-36	0.00
36-40	0.00
40-44	0.08
44-48	0.25
48-52	0.00
52-56	0.08
56-60	0.25

968-56

0 - 4	0.00
4 - 8	0.00
8 -12	0.00
12-16	0.16
16-20	0.00
20-24	0.00
24-28	0.08
28-32	0.08
32-36	0.08
36-40	0.08
40-44	0.24
44-52	0.00

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

968-57

0 - 4	0.13
4 - 8	0.16
4 -12	0.00
12-16	0.08
16-20	0.00
20-24	0.23
24-28	0.00
28-32	0.43
32-36	0.41
36-40	0.00
40-44	0.00
44-48	0.00
48-52	0.00
52-56	0.00
56-60	0.00
60-64	0.00
64-68	0.00
68-T.D.	0.00

968-58

0 - 4	0.41
4 - 8	0.00
8 -12	0.00
12-16	0.08
16-20	0.00
20-24	0.00
24-28	0.08
28-32	0.08
32-36	0.00
36-40	0.00
40-44	0.08
44-48	0.08

968-59

0 - 4	0.16
4 - 8	0.33
8 -12	0.16
12-16	0.58
16-20	0.66
20-24	0.40
24-28	0.16
28-32	0.25
32-36	0.16
36-40	0.08
40-44	0.08
44-48	0.16
48-52	0.49
52-56	0.16
56-60	0.09
60-64	0.08

ANALYSES

DAVID LECOUNT EVANS, CONSULTING GEOLOGIST

968-60

0 - 4	0.67
4 - 8	0.66
8 -12	1.27
12-16	0.16
16-20	0.16

968-61

0 - 4	1.32
4 - 8	0.89
8 -12	0.41
12-16	0.46
16-20	0.49
20-24	0.25
24-28	0.16
28-32	0.16
32-36	0.16

968-62

0 - 4	0.92
4 - 8	0.66
8 -12	0.49
12-16	0.64
16-20	0.09
20-24	0.25
24-28	0.25
28-32	0.16

968-63

0 - 4	0.72
4 - 8	0.49
8 -12	0.86
12-16	0.92
16-20	0.49
20-24	0.25
24-28	Nil

968-64

0 - 4	0.23		
4 - 8	0.93		
8 -12	0.74		
12-16	1.24		
16-20	3.96		
20-24	1.91		
24-28	4.62		
28-32	2.55	52-56	0.08
32-36	3.05	56-60	0.08
36-40	2.80	60-64	0.25
40-44	0.58		
44-48	0.86		
48-52	0.25		

DAVID LECOUNT EVANS, CONSULTING GEOLOGIST

968-65

0 - 4	0.74
4 - 8	0.79
8 -12	0.24
12-16	0.00

968-66

0 - 4	0.49
4 - 8	0.33
8 -12	0.25
12-16	0.25
16-20	0.36
20-24	0.49
24-28	0.33
28-32	0.16
32-36	0.08
36-40	0.08
40-44	0.08

968-67

0 - 4	1.40
4 - 8	0.66
8 -12	1.32
12-16	0.66
16-20	0.49
20-24	0.25
24-28	0.26
28-32	0.19

968-68

0 - 4	2.56
4 -14	1.85
14-16	0.41
16-20	0.10
20-24	1.51
24-28	1.32
28-32	0.77
32-36	0.43
36-40	1.05
40-44	0.82
44-48	0.72
48-52	0.49
52-55	0.20

Note: 0-4 probably is stockpile

ANALYSES

968-69

0 - 4	0.58
4 - 8	0.25
8 -12	0.72
12-16	0.99
16-20	0.41
20-24	0.33
24-28	0.13
28-32	0.09
32-36	0.25
36-40	0.25
40-44	0.20
44-48	0.25
48-52	0.16

968-70

0 - 4	0.20
4 - 8	0.13
8 -12	0.08
12-16	0.16
16-20	0.33
20-24	0.33
24-28	0.16
28-32	0.00

968-71

0 - 16	0.66
16-20	1.16
20-24	1.98
24-28	1.57
28-32	0.96
32-36	1.59
36-40	1.82
40-44	1.57
44-48	0.93
48-52	1.75
52-56	1.07
56-60	0.33
60-64	0.69
64-68	0.58
68-72	0.41

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST

ANALYSES

968-72

0 - 8	9.50	(Dump)
8 -16	1.78	(Dump)
16-22	0.77	
22-24	0.74	
24-28	0.87	
28-32	0.66	
32-36	0.91	
36-40	1.24	
40-44	1.45	
44-48	2.23	
48-52	1.73	
52-56	2.31	
56-60	2.80	
60-64	2.31	
64-68	2.03	
68-72	1.85	
72-76	1.24	
76-80	3.08	
80-82	9.00	Note: High grade against gouge

968-73

0 - 4	0.16	
4 - 8	0.20	
8 -12	0.33	
12-16	0.48	
16-20	0.91	
20-24	0.41	
24-28	0.56	
28-32	0.74	
32-36	0.58	
36-40	0.45	
40-44	0.92	
44-48	1.06	
48-52	1.15	
52-56	1.67	
56-61	2.51	Note: High grade atop gouge

968-74

0 - 4	0.50
4 - 8	0.26
8 -12	1.32
12-16	0.76
16-20	1.15
20-24	1.09
24-28	1.09

DAVID LE COUNT EVANS, CONSULTING GEOLOGIST