

3070 0057

282
Item #60



FOREST OIL CORPORATION

1816 -1203 First National Bank and Trust Co. Bldg.

Tulsa, Oklahoma 74103

June 17, 1970

Mr. John H. Schilling
Nevada Bureau of Mines
Reno, Nevada 89507

Dear John:

Enclosed is a copy of the assay report from the Mill City district.

Sample 2951 - The east-west (no. 2) adit up the arroya.

Sample 2952 - Chip samples from the skarn in the no. 2 adit.

Sample 2953 - The north-south (no. 1) adit, near the alluvium contact.

Sample 2954 - Grab sample of outcropping skarn above the no. 2 adit.

This assay agrees fairly well with the Union Assay Company report, the former being about 14% higher in WO_3 . The Mo is considerably less in the Montana assay. This tends to confirm the .07% WO_3 which we assumed to be the value.

With best personal regards to you and Harold.

Sincerely,

Murray A. Bennett

MAB:kp


P.S. I spoke with Warren Ervine who said his thesis of the Barcelona area will not be completed until about September.

Comparative Assay Results

| Sample No. | Description | Hawley and Hawley | | | | Oz. Ton | | Union | |
|------------|-----------------|-------------------|------|------|-------|---------|------|---------|-----|
| | | % Cu | % Pb | % Zn | % Bi | Au | Ag | Au | Ag |
| | | | | | | Oz. Ton | | Oz. Ton | |
| 2951 | No. 2 Adit dump | 0.02 | 0.04 | 0.08 | <0.01 | | | Tr. | Nil |
| 2952 | No. 2 Adit chip | | | | | | | | |
| 2953 | No. 1 Adit dump | 0.02 | 0.04 | 0.10 | 0.02 | Nil | Nil | 0.040 | 1.5 |
| 2954 | Grab sample | | | | | Nil | 0.04 | | |

| Sample No. | Union Assay | | | Hawley & Hawley | | | Eldridge | Met. Lab. |
|------------|-------------------|-------------------|-------|-------------------|-------------------|-------|-------------------|-------------------|
| | % WO ₃ | % WO ₃ | % Mo | % WO ₃ | % WO ₃ | % Mo | % WO ₃ | % WO ₃ |
| 2951 | 0.063 | 0.07 | 0.024 | 0.197 | 0.213 | 0.028 | 0.13 | 0.053 |
| 2952 | | | | 0.179 | | 0.036 | 0.11 | |
| 2953 | 0.063 | 0.08 | 0.011 | 0.188 | 0.207 | 0.009 | 0.12 | 0.038 |
| 2954 | | | | 0.152 | | 0.095 | | |

Cannot locate?




SKETCH MAP
ADIT NO. 1

WORKINGS & DUMP

T. MENDIETA TUNGSTEN PROSPECT

MILL CITY DISTRICT PERSHING CO., NEVADA

SCALE: 1 in = 40 ft



SKETCH MAP
ADIT NO. 2
WORKINGS & DUMP

T. MENDIETA TUNGSTEN PROSPECT
MILL CITY DISTRICT PERSHING CO., NEVADA

SCALE: 1 in. = 40 ft.

MONTANA LABORATORY COMPANY

CHEMISTS AND ASSAYERS

Phillipsburg, Montana, June 4, 1970

The Following Analyses Were Made For **Chapman, Wood and Griswold, Inc.**

| Sample No. | Per Cent H ₂ O | Ozs. Silver Per Ton | Ozs. Gold Per Ton | ¢ Gold Per Ton | Per Cent Copper | Per Cent WO ₃ | Per Cent Iron | Per Cent Lead | Per Cent Mo | Per Cent Silica | Per Cent Zinc |
|------------|---------------------------|---------------------|-------------------|----------------|-----------------|--------------------------|---------------|---------------|-------------|-----------------|---------------|
| 2951 | Adit | 0.05 | | | | 0.082 | | | 0.010 | | |
| 2952 | chips | None | | | | 0.078 | | | 0.022 | | |
| 2953 | Adit | None | | | | 0.090 | | | 0.003 | | |
| 2954 | Grab Sample | 0.05 | | | | 0.052 | | | 0.083 | | |

MONTANA LABORATORY COMPANY

By

W. J. Regenhart