

3100 0040

Iron-Nevada
Buena Vista
Deposit

283

ITEM 40

(Pershing County, Nevada) On March 4 Gustafson and Evans made an examination of this area and took a number of samples which were sent to Lerch Brothers, Crosby, Minnesota for analyses.

Analyses of ten samples taken by Mr. Evans have been received. The average of these assays is as follows: 64.99% Fe; 0.40% Phos.; 0.24% Mn; 2.18% SiO₂; 1.00% Al₂O₃; 0.72% Lime; 0.057% S, and 0.35% Moisture. Each of these ten samples represents widths of 100 feet or more and they were cut on various outcrops of the deposit which extends for over a mile in length. A report will be issued on this deposit as soon as a price on the land is obtained from the Southern Pacific Railroad.

D.C. EVANS