60001627

Mining District File Summary Sheet

DISTRICT	Rosebud
DIST_NO	4010
COUNTY If different from written on document	Pershing
TITLE If not obvious	Rosebud Drill Hole File - Hole No. RL-249
AUTHOR	R. Stoeber; P. Baker; T. Kuhl
DATE OF DOC(S)	199:
MULTI_DIST Y / (N?) Additional Dist_Nos:	
QUAD_NAME	Sulphur 7.5'
P_M_C_NAME (mine, claim & company names)	Rosebud Mine; Rosebud Project; Stevens Drilling; Lac Minerals (USA) Inc; Far East Bondar-Clegg, Inc.
COMMODITY If not obvious	gold silver
NOTES	Drill log; geology; assay; total depth 785' handwritten notes ~~18~~ p. 17

Keep docs at about 250 pages if no oversized maps attached (for every 1 oversized page (>11x17) with text reduce the amount of pages by ~25)

SS: DD 6/2/08
Initials Date

DB: mah
Initials Date

SCANNED: NI Blue
Initials Date

Revised: 1/22/08

ROSEBUD
Drill Log

RL-249
FAR EAST

6GG1627 4010

60001627

LAC MINERALS (U.S.A.) INC.

DRILL LOG SUMMARY SHEET

PROJECT Rosebud

HOLE NUMBER RL 249 TOTAL DEPTH 785' LOGGED BY RKS

Date started 11/16/91

Date completed 11/18/91

Initial bearing —

Initial inclination -90°

Elevation

Collar coordinates:

N

E

Contractor: Stevens

Drill Type: RC

Hole Size: 5½"

Drilling Conditions: Bueno

Footage: Wet / Dry 0 - 405 Dry

405 - 785 Wet

Comments:

DOWN HOLE SURVEY INFORMATION

FROM	TO	SURVEY POINT	INCLI-NATION	BEARING	X (Northing)	Y (Easting)	Z (Elevation)

LAC MINERALS (U.S.A.) INC.
ROSEBUD PROJECT

CHOCOLATE TUFF
BUD BRECCIA
BUD TUFF
BUD EPICLASTIC
BUD TUFF BRECCIA
DT DOZER WELDED TUFF

ARGILLIC
XX SILICIFICATION
OX OXIDIZED
DRUZY QUARTZ
XC CHALCEDONIC QUARTZ
XK STOCKWORK QUARTZ
P P P PROPYLITIZATION
Ca CALCITE

DRILL HOLE RL-249

Page 1 of ____

LOGGED BY _____

	LITH.	ALT.	% ARG. ALT. W	M	S	% SIL'N W	M	S	COLOR	% FeOx W	M	S	% SULF.	COMMENTS	Au	Ag	CHECK
									Brn-red Brn red org					Bedrock 3½ ft			
														Ct - (un-alt. Choc.)			
05									Brn-red red								
10																	
15																	
20																	
25																	
30																	
35																	
40									& lt Grey					(Trace Bleaching on edges of Frax)			
45																	
50																	
55									Org Yllw Brn-red					(Bleached & FeOx Stained)			
60									Org Yllw lt Grey					(Slight incr. FeOx)			
65																	
70																	
75																	
80									Org Yllw Brn-red					(Decr. alt.)			
85									Org Yllw lt Grey					(Incr FeOx & alt)			
90																	
95														Ox [Redox] Sulf			
100		22							Org Yllw lt Grey-Grn				.5	(1st sulfides)			

LAC MINERALS (U.S.A.) INC.
ROSEBUD PROJECT

CHOCOLATE TUFF
BUD BRECCIA
BUD TUFF
BUD EPICLASTIC
BUD TUFF BRECCIA
DT DOZER WELDED TUFF

ARGILLIC
XX SILICIFICATION
OX OXIDIZED
DRUZY QUARTZ
XC CHALCEDONIC QUARTZ
XK STOCKWORK QUARTZ
P P P PROPYLITIZATION
Ca CALCITE

DRILL HOLE RL-249

Page 2 of ____

LOGGED BY _____

	LITH.	ALT.	% ARG. ALT. W	M	S	% SIL'N W	M	S	COLOR	% FeOx W	M	S	% SULF.	COMMENTS	Au	Ag	CHECK
		N							Brn-red lt Green				.1	C+ (weaker alt)			
105		N							lt Green dt Grey				.5	(Incr. alt & Bleach)			
110		N N							lt Green lt Grey Flesh-Brn								
115		N							Purp-red Brn-red lt Grey					(v.w. alt) (Bleach only on Frax)			
120													.1				
125																	
130									Brn-red Purp-red red				0	(un-alt)			
135																	
140																	
145																	
150																	
155																	
160																	
165																	
170																	
175																	
180																	
185																	
190																	
195																	
200																	

Small fault?

LAC MINERALS (U.S.A.) INC.
ROSEBUD PROJECT

DRILL HOLE RL-248

Page 3 of ____

LOGGED BY _____

- CHOCOLATE TUFF
- BUD BRECCIA
- BUD TUFF
- BUD EPICLASTIC
- BUD TUFF BRECCIA
- DT DOZER WELDED TUFF
- ARGILLIC
- XX SILICIFICATION
- OX OXIDIZED
- DRUZY QUARTZ
- XC CHALCEDONIC QUARTZ
- XK STOCKWORK QUARTZ
- P P P PROPYLITIZATION
- Ca CALCITE

	LITH.	ALT.	% ARG. ALT. W	M	S	% SIL'N W	M	S	COLOR	% FeOx W	M	S	% SULF.	COMMENTS	Au	Ag	CHECK
									Bon-red red Purp-red				0	Ct - (un-alt)			
205																	
210																	
215																	
220																	
225																	
230																	
235																	
240																	
245																	
250																	
255																	
260																	
265																	
270																	
275																	
280																	
285																	
290																	
295																	
300																	

LLt

Fg

LAC MINERALS (U.S.A.) INC.
ROSEBUD PROJECT

CHOCOLATE TUFF
BUD BRECCIA
BUD TUFF
BUD EPICLASTIC
BUD TUFF BRECCIA
DT DOZER WELDED TUFF

ARGILLIC
XX SILICIFICATION
OX OXIDIZED
DRUZY QUARTZ
XC CHALCEDONIC QUARTZ
XK STOCKWORK QUARTZ
P P P PROPYLITIZATION
Ca CALCITE

DRILL HOLE RL-249

Page 4 of ____

LOGGED BY _____

	LITH.	ALT.	% ARG. ALT. W	M	S	% SIL'N W	M	S	COLOR	% FeOx W	M	S	% SULF.	COMMENTS	Au	Ag	CHECK
									Brn-red red purp-red				0	Ct			
305																	
310																	
315																	
320																	
325																	
330																	
335																	
340																	
345																	
350																	
355																	
360																	
365																	
370																	
375																	
380																	
385																	
390																	
395																	
400																	

LAC MINERALS (U.S.A.) INC.
ROSEBUD PROJECT

CHOCOLATE TUFF
BUD BRECCIA
BUD TUFF
BUD EPICLASTIC
BUD TUFF BRECCIA
DOZER WELDED TUFF

ARGILLIC
XX SILICIFICATION
OX OXIDIZED
DRUZY QUARTZ
XC CHALCEDONIC QUARTZ
XK STOCKWORK QUARTZ
P P P PROPYLITIZATION
Ca CALCITE

DRILL HOLE RL-249

Page 5 of ____

LOGGED BY _____

	LITH.	ALT.	% ARG. ALT. W	M	S	% SIL'N W	M	S	COLOR	% FeOx W	M	S	% SULF.	COMMENTS	Au	Ag	CHECK
									Brn-red red				0	Ct - unalt.			
405		N							Brn-red lt Green Flesh				.1	sharp Δ color and alt (wk. to mod clay alt.)			
410		N N N							lt Green Flesh				.1	(slight Incr sulf.)			
415		N N N N											.5	(slight Incr sulf.)			
420		N N N N											.5				
425		N N N											.5				
430		N N							Green Flesh				.1	(Decr. sulf.)			
435		N N							lt Green Green Flesh				.5	(slight incr sulf.)			
440		N N											.5				
445		N N N											.5				
450		N N N											.1	(Decr sulf.)			
455		N N							lt Green Green Brn-red				.1	(wk alt)			
460		N N											.1				
465		N N N							lt Green Green Flesh-red				.1				
470		N N N											.5	(Slight Incr sulf.)			
475		N N N							lt Grey Flesh lt Green				.5	(Incr sulf & Bleaching) (w/ sulf vns.) (trace wht Kaolin)			
480		N N N							& Flesh-red				.5				
485		N N							lt Green Flesh					(slight Decr. bleach & sulf)			
490		N N N															
495		N N							lt Grey lt Green Flesh Wht					(mod Bleaching minor silic Incr. sulf.)			
500																	

Alt TC

Fault ?

LAC MINERALS (U.S.A.) INC.
ROSEBUD PROJECT

CHOCOLATE TUFF
BUD BRECCIA
BUD TUFF
BUD EPICLASTIC
BUD TUFF BRECCIA
DT DOZER WELDED TUFF

ARGILLIC
XX SILICIFICATION
OX OXIDIZED
DRUZY QUARTZ
XC CHALCEDONIC QUARTZ
XK STOCKWORK QUARTZ
P P P PROPYLITIZATION
Ca CALCITE

DRILL HOLE RL-249

Page 6 of ____

LOGGED BY _____

	LITH.	ALT.	% ARG. ALT. W	M	S	% SIL'N W	M	S	COLOR	% FeOx W	M	S	% SULF.	COMMENTS	Au	Ag	CHECK
									lt Grey lt Green flesh				.5	Ct - (trace slfd; slight decr. bleach & alt)			
505									lt Green flesh Brn-red				.5	(Decr. alt.)			
510									Brn-red red Purp-red				.1	(w/ trace calc.)			
515																	
520																	
525													0				
530																	
535																	
540																	
545																	
550																	
555																	
560																	
565																	
570																	
575														(trace Calc) (trace bleaching on Frag)			
580									& Grey								
585																	
590																	
595																	
600																	

LAC MINERALS (U.S.A.) INC.
ROSEBUD PROJECT

DRILL HOLE R1-249

Page 7 of ____

LOGGED BY _____

- CHOCOLATE TUFF
- BUD BRECCIA
- BUD TUFF
- BUD EPICLASTIC
- BUD TUFF BRECCIA
- DT DOZER WELDED TUFF
- ARGILLIC
- XX SILICIFICATION
- OX OXIDIZED
- DRUZY QUARTZ
- XC CHALCEDONIC QUARTZ
- XK STOCKWORK QUARTZ
- P P P PROPYLITIZATION
- Ca CALCITE

	LITH.	ALT.	% ARG. ALT. W	M	S	% SIL'N W	M	S	COLOR	% FeOx W	M	S	% SULF.	COMMENTS	Au	Ag	CHECK
									Purp-red Brn-red lt Grey				0	Ct - trace bleach on Frax			
605																	
610																	
615																	
620																	
625														11/17 11/18			
630																	
635																	
640																	
645																	
650																	
655																	
660																	
665																	
670																	
675																	
680																	
685																	
690																	
695																	
700																	

LAC MINERALS (U.S.A.) INC.
ROSEBUD PROJECT

CHOCOLATE TUFF
BUD BRECCIA
BUD TUFF
BUD EPICLASTIC
BUD TUFF BRECCIA
DT DOZER WELDED TUFF

ARGILLIC
XX SILICIFICATION
OX OXIDIZED
DRUZY QUARTZ
XC CHALCEDONIC QUARTZ
XK STOCKWORK QUARTZ
P P P PROPYLITIZATION
Ca CALCITE

DRILL HOLE RL-249

Page 8 of ____

LOGGED BY _____

	LITH.	ALT.	% ARG. ALT. W	M	S	% SIL'N W	M	S	COLOR	% FeOx W	M	S	% SULF.	COMMENTS	Au	Ag	CHECK
									Brn-red purple red				0	Ct			
705													0				
710									s Green				.1				
715		N							lt Green Green Brn-red				.1				
720		NW							lt Green Green wht				.1	(w/ sticks & calc.)			
Fault 725		N							lt Green Green purple Brn-red				.1				
730									red Brn-red Grey				.1	(w/ calc vn)			
735									red Brn-red lt Grey				.1	(trace Bleaching & calc vn)			
740									Brn-red red lt Grey				.1				
745		N							Pink red wht				.1	mod Bleaching but still very dry for sulfides			
750		N											.1				
755									red Pink lt Grey					trace to minor Bleaching			
760																	
765									Brn-red red lt Grey				0				
770																	
775																	
780														[2 gpm]			
785																	
790														TD 11/18/91			
														Last Hole in 1991			
795														Drilling Program			
800																	

RL249 DEC 07 1991

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R91-12473.4 (COMPLETE)

REFERENCE INFO: RL 249 H - 785

CLIENT: IAC MINERALS (USA) INC.
PROJECT: ROSEBUD

SUBMITTED BY: STOHBERI
DATE PRINTED: 3-DEC-91

ORDER	ELEMENT	NUMBER OF ANALYSES	LOWER DETECTION LIMIT	EXTRACTION	METHOD
1	Au DUP Gold Duplicate	19	0.002 OPT		Fire Assay
2	Au Gold	164	0.002 OPT		Fire Assay
3	AG DUP AG DUPLICATE	19	0.02 OPT		Fire Assay
4	Ag Silver	164	0.02 OPT		Fire Assay

SAMPLE TYPES	NUMBER	SIZE FRACTIONS	NUMBER	SAMPLE PREPARATIONS	NUMBER
Z OTHER DRILL TYPES	157	2 -150	157	CRUSH,PULVERIZE -150	157
P PREPARED PULP	7	4 AS REC'D	7	AS RECEIVED, NO SP	7

REPORT COPIES TO: MR. TIM KUHN
MR. TIM KUHN

INVOICE TO: MR. TIM KUHN

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 3-DEC-91

REPORT: R91-12473.4 (COMPLETE)

PROJECT: ROSEBUD

STANDARD NAME	ELEMENT UNITS	Au DUP OPT	Au OPT	AG DUP OPT	Ag OPT	STANDARD NAME	ELEMENT UNITS	Au DUP OPT	Au OPT	AG DUP OPT	Ag OPT
ANALYTICAL BLANK		-	<0.002	-	<0.02						
ANALYTICAL BLANK		-	<0.002	-	<0.02						
ANALYTICAL BLANK		-	<0.002	-	<0.02						
ANALYTICAL BLANK		-	<0.002	-	<0.02						
ANALYTICAL BLANK		-	<0.002	-	<0.02						
Number of Analyses		-	5	-	5						
Mean Value		-	0.0010	-	0.010						
Standard Deviation		-	0.00000	-	0.0000						
Accepted Value		-	0.002	-	0.02						
PD SYN STD AU/AG		-	0.040	-	0.39						
PD SYN STD AU/AG		-	0.040	-	0.40						
PD SYN STD AU/AG		-	0.037	-	0.38						
PD SYN STD AU/AG		-	0.040	-	0.41						
Number of Analyses		-	4	-	4						
Mean Value		-	0.0393	-	0.395						
Standard Deviation		-	0.00150	-	0.0129						
Accepted Value		-	0.040	-	0.40						

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

REPORT: R91-12473.4 (COMPLETE)

DATE PRINTED: 3-DEC-91
PROJECT: ROSEBUD

SAMPLE NUMBER	ELEMENT UNITS	Au DUP OPT	Au OPT	AG DUP OPT	Ag OPT	SAMPLE NUMBER	ELEMENT UNITS	Au DUP OPT	Au OPT	AG DUP OPT	Ag OPT
Z2 RL249 0-5			<0.002		<0.02	Z2 RL249 195-200			<0.002		<0.02
Z2 RL249 5-10			<0.002		<0.02	P4 BA 278			0.051		0.22
Z2 RL249 10-15			<0.002		<0.02	Z2 RL249 200-205			<0.002		<0.02
Z2 RL249 15-20		<0.002	<0.002	<0.02	<0.02	Z2 RL249 205-210			<0.002		<0.02
Z2 RL249 20-25			<0.002		<0.02	Z2 RL249 210-215			<0.002		<0.02
Z2 RL249 25-30			<0.002		<0.02	Z2 RL249 215-220			<0.002		<0.02
Z2 RL249 30-35			<0.002		<0.02	Z2 RL249 220-225		<0.002	<0.002	<0.02	<0.02
Z2 RL249 35-40			<0.002		<0.02	Z2 RL249 225-230			<0.002		<0.02
Z2 RL249 40-45			<0.002		<0.02	Z2 RL249 230-235			<0.002		<0.02
Z2 RL249 45-50			<0.002		<0.02	Z2 RL249 235-240			<0.002		<0.02
Z2 RL249 50-55		<0.002	<0.002	<0.02	<0.02	Z2 RL249 240-245			<0.002		<0.02
Z2 RL249 55-60			<0.002		<0.02	Z2 RL249 245-250			<0.002		<0.02
Z2 RL249 60-65			<0.002		<0.02	Z2 RL249 250-255			<0.002		<0.02
Z2 RL249 65-70		<0.002	<0.002	<0.02	<0.02	Z2 RL249 255-260			<0.002		<0.02
Z2 RL249 70-75			<0.002		<0.02	Z2 RL249 260-265			<0.002		<0.02
RL249 75-80			<0.002		<0.02	Z2 RL249 265-270			<0.002		<0.02
Z2 RL249 80-85			<0.002		<0.02	Z2 RL249 270-275		<0.002	<0.002	<0.02	<0.02
Z2 RL249 85-90			<0.002		<0.02	Z2 RL249 275-280		<0.002	<0.002	<0.02	<0.02
Z2 RL249 90-95			<0.002		<0.02	Z2 RL249 280-285			<0.002		<0.02
Z2 RL249 95-100			<0.002		<0.02	Z2 RL249 285-290			<0.002		<0.02
P4 BA 277			0.053		0.05	Z2 RL249 290-295			<0.002		<0.02
Z2 RL249 100-105			<0.002		<0.02	Z2 RL249 295-300			<0.002		<0.02
Z2 RL249 105-110			<0.002		<0.02	P4 BA 279			0.050		0.05
Z2 RL249 110-115			<0.002		<0.02	Z2 RL249 300-305			<0.002		<0.02
Z2 RL249 115-120			<0.002		<0.02	Z2 RL249 305-310			<0.002		<0.02
Z2 RL249 120-125		<0.002	<0.002	<0.02	<0.02	Z2 RL249 310-315			<0.002		<0.02
Z2 RL249 125-130			<0.002		<0.02	Z2 RL249 315-320			<0.002		<0.02
Z2 RL249 130-135			<0.002		<0.02	Z2 RL249 320-325			<0.002		<0.02
Z2 RL249 135-140			<0.002		<0.02	Z2 RL249 325-330		<0.002	<0.002	<0.02	<0.02
Z2 RL249 140-145			<0.002		<0.02	Z2 RL249 330-335			<0.002		<0.02
Z2 RL249 145-150			<0.002		<0.02	Z2 RL249 335-340			<0.002		<0.02
Z2 RL249 150-155			<0.002		<0.02	Z2 RL249 340-345			<0.002		<0.02
Z2 RL249 155-160			<0.002		<0.02	Z2 RL249 345-350			<0.002		<0.02
Z2 RL249 160-165			<0.002		<0.02	Z2 RL249 350-355			<0.002		<0.02
Z2 RL249 165-170			<0.002		<0.02	Z2 RL249 355-360			<0.002		<0.02
Z2 RL249 170-175		<0.002	<0.002	<0.02	<0.02	Z2 RL249 360-365			<0.002		<0.02
RL249 175-180			<0.002		<0.02	Z2 RL249 365-370			<0.002		<0.02
Z2 RL249 180-185			<0.002		<0.02	Z2 RL249 370-375			<0.002		<0.02
Z2 RL249 185-190			<0.002		<0.02	Z2 RL249 375-380			<0.002		<0.02
Z2 RL249 190-195			<0.002		<0.02	Z2 RL249 380-385			<0.002		<0.02

Paul Baker by mw

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 3-DEC-91

REPORT: R91-12473.4 (COMPLETE)

PROJECT: ROSEBUD

SAMPLE NUMBER	ELEMENT UNITS	Au DUP OPT	Au OPT	AG DUP OPT	Ag OPT
Z2 RL249 385-390			<0.002		<0.02
Z2 RL249 390-395			<0.002		<0.02
Z2 RL249 395-400			<0.002		<0.02
P4 BA 280			0.034		0.22
Z2 RL249 400-405			<0.002		<0.02
Z2 RL249 405-410			<0.002		<0.02
Z2 RL249 410-415			<0.002		<0.02
Z2 RL249 415-420			<0.002		<0.02
Z2 RL249 420-425			<0.002		<0.02
Z2 RL249 425-430		<0.002	<0.002	<0.02	<0.02
Z2 RL249 430-435			<0.002		<0.02
Z2 RL249 435-440			<0.002		<0.02
Z2 RL249 440-445			<0.002		<0.02
Z2 RL249 445-450			<0.002		<0.02
Z2 RL249 450-455			<0.002		<0.02
RL249 455-460			<0.002		<0.02
Z2 RL249 460-465			<0.002		<0.02
Z2 RL249 465-470			<0.002		<0.02
Z2 RL249 470-475			<0.002		<0.02
Z2 RL249 475-480		<0.002	<0.002	0.05	0.05
Z2 RL249 480-485			0.003		0.07
Z2 RL249 485-490			<0.002		<0.02
Z2 RL249 490-495			<0.002		<0.02
Z2 RL249 495-500			<0.002		0.03
P4 BA 281			<0.002		<0.02
Z2 RL249 500-505			<0.002		<0.02
Z2 RL249 505-510		<0.002	<0.002	<0.02	<0.02
Z2 RL249 510-515			<0.002		<0.02
Z2 RL249 515-520			<0.002		<0.02
Z2 RL249 520-525			<0.002		<0.02
Z2 RL249 525-530			<0.002		<0.02
Z2 RL249 530-535		<0.002	<0.002	<0.02	<0.02
Z2 RL249 535-540			<0.002		<0.02
Z2 RL249 540-545			<0.002		<0.02
Z2 RL249 545-550			<0.002		<0.02
Z2 RL249 550-555			<0.002		<0.02
RL249 555-560			<0.002		<0.02
Z2 RL249 560-565			<0.002		<0.02
Z2 RL249 565-570			<0.002		<0.02
Z2 RL249 570-575			<0.002		<0.02

SAMPLE NUMBER	ELEMENT UNITS	Au DUP OPT	Au OPT	AG DUP OPT	Ag OPT
Z2 RL249 575-580		<0.002	<0.002	<0.02	<0.02
Z2 RL249 580-585			<0.002		<0.02
Z2 RL249 585-590			<0.002		<0.02
Z2 RL249 590-595			<0.002		<0.02
Z2 RL249 595-600			<0.002		<0.02
P4 BA 282			0.053		0.05
Z2 RL249 600-605			<0.002		<0.02
Z2 RL249 605-610			<0.002		<0.02
Z2 RL249 610-615			<0.002		<0.02
Z2 RL249 615-620			<0.002		<0.02
Z2 RL249 620-625			<0.002		<0.02
Z2 RL249 625-630			<0.002		<0.02
Z2 RL249 630-635		<0.002	<0.002	<0.02	<0.02
Z2 RL249 635-640			<0.002		<0.02
Z2 RL249 640-645			<0.002		<0.02
Z2 RL249 645-650			<0.002		<0.02
Z2 RL249 650-655			<0.002		<0.02
Z2 RL249 655-660			<0.002		<0.02
Z2 RL249 660-665			<0.002		<0.02
Z2 RL249 665-670			<0.002		<0.02
Z2 RL249 670-675			<0.002		<0.02
Z2 RL249 675-680			<0.002		<0.02
Z2 RL249 680-685		<0.002	<0.002	<0.02	<0.02
Z2 RL249 685-690			<0.002		<0.02
Z2 RL249 690-695			<0.002		<0.02
Z2 RL249 695-700			<0.002		<0.02
P4 BA 283			<0.002		<0.02
Z2 RL249 700-705			<0.002		<0.02
Z2 RL249 705-710			<0.002		<0.02
Z2 RL249 710-715			<0.002		<0.02
Z2 RL249 715-720			<0.002		<0.02
Z2 RL249 720-725			<0.002		<0.02
Z2 RL249 725-730			<0.002		<0.02
Z2 RL249 730-735			<0.002		<0.02
Z2 RL249 735-740		<0.002	<0.002	<0.02	<0.02
Z2 RL249 740-745			<0.002		<0.02
Z2 RL249 745-750			<0.002		<0.02
Z2 RL249 750-755		<0.002	<0.002	<0.02	<0.02
Z2 RL249 755-760			<0.002		<0.02
Z2 RL249 760-765			<0.002		<0.02

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 3-DEC-91

REPORT: R91-12473.4 (COMPLETE)

PROJECT: ROSEBUD

SAMPLE NUMBER	ELEMENT UNITS	Au DUP OPT	Au OPT	AG DUP OPT	Ag OPT	SAMPLE NUMBER	ELEMENT UNITS	Au DUP OPT	Au OPT	AG DUP OPT	Ag OPT
Z2 RL249 765-770			<0.002		<0.02						
Z2 RL249 770-775			<0.002		<0.02						
Z2 RL249 775-780			<0.002		<0.02						
Z2 RL249 780-785		<0.002	<0.002	<0.02	<0.02						

Bondar-Clegg, Inc.
625 Spice Island Dr.
Building 1, Unit A
Sparks, Nevada 89431
702 (359-9330)

BONDAR-CLEGG

A DIVISION OF INCHCAPE INSPECTION & TESTING SERVICES

Geochemical Lab Report

DATE PRINTED: 3-DEC-91

REPORT: R91-12473.4 (COMPLETE)

PROJECT: ROSEBUD

SAMPLE NUMBER	ELEMENT UNITS	Au DUP OPT	Au OPT	AG DUP OPT	Ag OPT	SAMPLE NUMBER	ELEMENT UNITS	Au DUP OPT	Au OPT	AG DUP OPT	Ag OPT
RL249 15-20		<0.002	<0.002	<0.02	<0.02	Prep Duplicate			<0.002		<0.02
Duplicate			<0.002		<0.02						
RL249 50-55		<0.002	<0.002	<0.02	<0.02	RL249 680-685		<0.002	<0.002	<0.02	<0.02
Prep Duplicate			<0.002		<0.02	Duplicate			<0.002		<0.02
RL249 65-70		<0.002	<0.002	<0.02	<0.02	RL249 735-740		<0.002	<0.002	<0.02	<0.02
Duplicate			<0.002		<0.02	Duplicate			<0.002		<0.02
RL249 120-125		<0.002	<0.002	<0.02	<0.02	RL249 750-755		<0.002	<0.002	<0.02	<0.02
Duplicate			<0.002		<0.02	Prep Duplicate		<0.002	<0.002	<0.02	<0.02
RL249 170-175		<0.002	<0.002	<0.02	<0.02	RL249 780-785		<0.002	<0.002	<0.02	<0.02
Duplicate			<0.002		<0.02	Duplicate			<0.002		<0.02
RL249 220-225		<0.002	<0.002	<0.02	<0.02	Prep Duplicate		<0.002	<0.002	<0.02	<0.02
Duplicate			<0.002		<0.02	Duplicate			<0.002		<0.02
249 270-275		<0.002	<0.002	<0.02	<0.02						
Duplicate			<0.002		<0.02						
RL249 275-280		<0.002	<0.002	<0.02	<0.02						
Prep Duplicate		<0.002	<0.002	<0.02	<0.02						
RL249 325-330		<0.002	<0.002	<0.02	<0.02						
Duplicate			<0.002		<0.02						
Prep Duplicate		<0.002	<0.002	<0.02	<0.02						
Duplicate			<0.002		<0.02						
RL249 425-430		<0.002	<0.002	<0.02	<0.02						
Duplicate			<0.002		<0.02						
RL249 475-480		<0.002	<0.002	0.05	0.05						
Duplicate			<0.002		0.05						
RL249 505-510		<0.002	<0.002	<0.02	<0.02						
Prep Duplicate			<0.002		<0.02						
RL249 530-535		<0.002	<0.002	<0.02	<0.02						
Duplicate			<0.002		<0.02						
RL249 575-580		<0.002	<0.002	<0.02	<0.02						
plicate			<0.002		<0.02						
RL249 630-635		<0.002	<0.002	<0.02	<0.02						
Duplicate			<0.002		<0.02						