

MABEL MINE SERIES
ORE SETTLEMENTS AUG - DEC 1925
LOTS 48 - 53

25

25
Mabel Mine Lots 48-53
One Settlements ^{aug-} Dec 1925

(254) Item 117 25 of 46

4840 0916

formerly

4840 0117

see also 4840

0117, 0911, 0912, 0913,

0914, 0915, 0917, 0918,

0919, 0920, 0921, 0922,

0923, 0924, 0925, and 0926

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTSNAME **West End Con**

SALT LAKE CITY, UTAH,

August 22, 1925LOT NO. **48**SAMPLED BY **Utah Ore**

ASSAY PER TON OF 2,000 POUNDS

GOLD—Ozs.	SILVER—Ozs.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.30 1.28	78.3 78.5	Wet 7.5 7.6			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
73.4 73.0	1.0 1.1	3.8 3.8	6.3 7.1		

CHARGE, \$

5*Black & Deason*

ASSAYERS

Aug. 17, 1925

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah

Gentlemen:-

As advised by wire we shipped to the U. S. Smelting, Refining & Mining Co. at their Midvale plant on August 13th, carload of ore from our Mabel Mine, our lot no. 48, in car U. P. 124157.

This ore is to be sampled once at the plant of the Utah Ore Sampling Co. and crushed to pass one inch mesh.

Will you please watch this sampling for us. Kindly secure one set of pulps from the Utah Ore Sampling Co., the original only to be run by you and used for the purpose of settlement with the U. S. Smelting, Refining & Mining Co. and the duplicate please send to us for the purpose of check in our own assay office.

Yours very truly,

Chief Clerk

OF*FA

Act Mina Weight 94260

Aug. 17, 1925

U. S. Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah

Gentlemen:-

As advised by wire, we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore on August 13th, our lot No. 48, in car U. P. 124157. Bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one inch mesh. One sampling will be sufficient.

Black & Deason of Salt Lake City will watch the sampling of this ore for us. Will you please have the Utah Ore Sampling Co. deliver an original and duplicate pulp to Black & Deason. They will run the original pulp for us to be used in making settlement. The duplicate pulp is to be sent to us for the purpose of check in our own assay office.

This carload of ore was shipped under terms of contract. Please send check with two copies of settlement sheets to our Oakland Office and send four copies of settlement sheets to this office.


Yours very truly,

Chief Clerk

CF:FA
CC-JWS

Check sampling charge refunded on following
lots

<u>Lot no</u>	<u>Date Received at Smelter</u>	<u>Wet Tons</u>	<u>Sampling Charge</u>
44	6/1/25	47.230	21.26
45	6/22/25	46.390	20.88
		93.620	42.14



CLASS OF SERVICE DESIRED	
Telegram	
Day Letter	X
Night Message	
Night Letter	
Patrons should mark an X opposite the class of service desired: OTHERWISE THE MESSAGE WILL BE TRANSMITTED AS A FULL-RATE TELEGRAM	

WESTERN UNION



TELEGRAM

NEWCOMB CARLTON, PRESIDENT

GEORGE W. E. ATKINS, FIRST VICE-PRESIDENT

Receiver's No.
Check
Time Filed

Send the following message, subject to the terms on back hereof, which are hereby agreed to

Tonopah, Nev. Aug. 17, 1925

U. S. Smelting, Refining & Mining Co.,
912 Newhouse Bldg.,
Salt Lake City, Utah.

Shipped thirteenth lot forty eight Mabel mine car UP one twenty four
one fifty seven handle same as previous shipments.

West End Cons. Mining Co.

Charge West End.

CLASS OF SERVICE DESIRED

Telegram	
Day Letter	XX
Night Message	
Night Letter	

Patrons should mark an X opposite the class of service desired: OTHERWISE THE MESSAGE WILL BE TRANSMITTED AS A FULL-RATE TELEGRAM

WESTERN UNION



TELEGRAM

NEWCOMB CARLTON, PRESIDENT

GEORGE W. E. ATKINS, FIRST VICE-PRESIDENT

Receiver's No.

Check

Time Filed

Send the following message, subject to the terms on back hereof, which are hereby agreed to

Tonopah, Nevada, Aug. 17th, 1925

Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Shipped thirteenth Mabel lot forty eight car UP one twenty four
one fifty seven handle same as previous ~~XX~~ lots.

West End Cons. Mining Co.

Charge West End.

Aug. 17, 1925

Utah Ore Sampling Co.,
819 Newhouse Bldg.,
Salt Lake City, Utah

Gentlemen:-

On August 13th we shipped car of ore, our lot No. 48, in car U. P. 124157 from our Mabel Mine at Mina, Nevada, to the U. S. Smelting, Refining & Mining Co. at their Midvale plant. This ore is to be sampled once at your plant and crushed to pass one inch mesh.

Our representative will be Black & Deason who will watch this sampling for us. Will you please deliver to them a set of pulps. They are to run the original for us and send the duplicate to us here for the purpose of check in our own assay office.

Yours very truly,

Chief Clerk

OF*FA

Sept. 1, 1925

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:-

On August 31st we shipped to the U. S.
Smelting, Refining & Mining Co. at their Midvale plant,
carload of ore from our Mabel Mine, our lot No. 49, in
car U. P. 135002.

This ore is to be sampled once at the plant
of the Utah Ore Sampling Co. and crushed to pass one inch
mesh.

Will you please watch this sampling for us.
Kindly secure one set of pulps from the Utah Ore Sampling
Co., the original only to be run by you and used for the
purpose of settlement with the U. S. Smelting, Refining
& Mining Co., and the duplicate please send to us for the
purpose of check in our own assay office.

Yours very truly,

Chief Clerk

OF*FA

Sept. 1, 1925

U. S. Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:-

On August 31st, we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our lot No. 49, in car U. P. 135002. Bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh. One sampling will be sufficient.

Black & Deason of Salt Lake City will watch the sampling of this ore for us. Will you please have the Utah Ore Sampling Co. deliver an original and duplicate pulp to Black & Deason. They will run the original pulp for us to be used in making settlement. The duplicate pulp is to be sent to us for the purpose of check in our own assay office.

This carload of ore was shipped under terms of contract. Please send check with two copies of settlement sheets to our Oakland office and send four copies of settlement sheets to this office.

Yours very truly,

Chief Clerk

OF*FA
CC-JWS

Sept. 1, 1925

Utah Ore Sampling Co.,
819 Newhouse Bldg.,
Salt Lake City, Utah

Gentlemen:-

On August 31st we shipped car of ore, our lot No. 49, in car U. P. 135002 from our Mabel Mine at Mina, Nevada, to the U. S. Smelting, Refining & Mining Co. at their Midvale plant. This ore is to be sampled once at your plant and crushed to pass one inch mesh.

Our representative will be Black & Deason who will watch this sampling for us. Will you please deliver to them a set of pulps. They are to run the original for us and send the duplicate to us here for the purpose of check in our own assay office.

Yours very truly,

Chief Clerk

OF*FA

Actual Mina Weight 85300 lbs

Sept. 25, 1925

U. S. Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah

Gentlemen:-

On September 22nd, we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our Lot No. 50, in car S. P. 18159. Bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh. One sampling will be sufficient.

Black & Deason of Salt Lake City will watch the sampling of this ore for us. Will you please have the Utah Ore Sampling Co. deliver an original and duplicate pulp to Black & Deason. They will run the original pulp for us to be used in making settlement. The duplicate pulp is to be sent to us for the purpose of check in our own assay office.

This carload of ore was shipped under terms of contract. Please send check with two copies of settlement sheets to our Oakland office and send four copies of settlement sheets to this office.

Yours very truly,

Chief Clerk

OF*FA
CC-JWS

86440 actual weight

Sept. 25, 1925

Utah Ore Sampling Co.,
819 Newhouse Building,
Salt Lake City, Utah

Gentlemen:-

On September 22nd we shipped car of ore, our lot No. 50, in car S. P. 18159 from our Mabel Mine at Mina, Nevada, to the U. S. Smelting, Refining & Mining Co. at their Midvale plant. This ore is to be sampled once at your plant and crushed to pass one inch mesh.

Our representative will be Black & Deason who will watch this sampling for us. Will you please deliver to them a set of pulps. They are to run the original for us and send the duplicate to us here for the purpose of check in our own assay office.

Yours very truly,

Chief Clerk

OF*FA

Sept. 25, 1925

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah

Gentlemen:-

On September 22nd we shipped to the U. S. Smelting, Refining & Mining Co. at their Midvale plant, carload of ore from our Mabel Mine, our lot No. 50, in car S. P. 18159.

This ore is to be sampled once at the plant of the Utah Ore Sampling Co. and crushed to pass one inch mesh.

Will you please watch this sampling for us. Kindly secure one set of pulps from the Utah Ore Sampling Co., the original only to be run by you and used for the purpose of settlement with the U. S. Smelting, Refining & Mining Co. and the duplicate please send to us for the purpose of check in our own assay office.

Yours very truly,

Chief Clerk

OF*FA

October 17, 1925.

U. S. Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On October 14th we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our Lot No. 51, in car S.P.27692. Bill of Lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh. One sampling only is necessary.

Black & Deason of Salt Lake City will watch the sampling of this ore for us. Will you please have the Utah Ore Sampling Co. deliver an original and duplicate pulp to Black and Deason. They will run the original pulp for us to be used in making settlement. The duplicate pulp is to be sent to us for the purpose of check in our own assay office.

This carload of ore was shipped under terms of contract. Please send check with two copies of settlement sheets to our Oakland office and send four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

CC-JWS

Wright 82400

October 17, 1925.

Utah Ore Sampling Co.,
819 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On October 14th we shipped car of ore, our lot No. 51, in car S.P.27692, from our Mabel Mine at Mina, Nev., to the U.S.Smelting, Refining & Mining Co. at their Midvale plant. This ore is to be sampled once at your plant and crushed to pass one inch mesh.

Our representatives will be Black & Deason, who will watch this sampling for us. Will you please deliver to them a set of pulps. They are to run the original for us and send the duplicate to us here for the purpose of check.

Yours very truly,

Chief Clerk.

October 17, 1925.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On October 14th we shipped to the U.S. Smelting Refining & Mining Co. at their Midvale plant, carload of ore from our Mabel Mine, out lot No. 51, in car S.P.27692.

This ore is to be sampled once at the plant of the Utah Ore Sampling Co. and crushed to pass one inch mesh.

Will you please watch this sampling for us. Kindly secure one set of pulps from the Utah Ore Sampling Co., the original only to be run by you and used for the purpose of settlement with the U.S. Smelting, Refining & Mining Co., and the duplicate please send to us for the purpose of check.

Yours very truly,

Chief Clerk.

November 19, 1925.

U. S. Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On November 17th we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our Lot No. 52, in car G.H.50868. Bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh. Only sampling only is required.

Black & Deason of Salt Lake City will watch the sampling of this ore for us. Will you please have the Utah Ore Sampling Co. deliver an original and duplicate pulp to Black and Deason. They will run the original pulp for us to be used in making settlement. The duplicate pulp is to be sent to us for the purpose of check in our own assay office.

Please send check with two copies of settlement sheet to our Oakland Office and send four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

CC-JWS

*Est'd weight 86000
Moist Weight 86620*

	<i>an</i>	<i>ag</i>	<i>703</i>
<i>Shovel Sample</i>	<i>1.32</i>	<i>88.00</i>	<i>3.5%</i>

November 19, 1925.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On November 17th we shipped to the U.S. Smelting Refining and Mining Co. at their Midvale plant, carload of ore from our Mabel Mine, our Lot No. 52, in car GH 50868.

This ore is to be sampled once at the plant of the Utah Ore Sampling Co. and crushed to pass one inch mesh.

Will you please watch this sampling for us. Kindly secure one set of pulps from the Utah Ore Sampling Co., the original only to be run by you and used for the purpose of settlement with the U.S. Smelting, Refining & Mining Co., and the duplicate please send to us for the purpose of check.

Yours very truly,

Chief Clerk.

November 19, 1925.

Utah Ore Sampling Co.,
819 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On November 17th we shipped car of ore, our lot No. 52, in car GH 50868, from our Mabel Mine at Mina, Nevada, to the U.S. Smelting, Refining and Mining Co. at their Midvale plant. This ore is to be sampled once at your plant and crushed to pass one inch mesh.

Our representatives will be Black and Deason, who will watch this sampling for us. Will you please deliver to them a set of pulps. They are to run the original for us and send the duplicate to us here for the purpose of check.

Yours very truly,

Chief Clerk.

Dec. 12, 1925.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On December 9th we shipped to the U. S. Smelting Refining and Mining Co. at their Midvale plant, carload of ore from our Mabel Mine, our Lot No. 52, in car Penn.42479.

This lot is to be handled the same as our previous shipments.

Included in this car is a shipment of 140 sacks of ore from the Train and Budelman lease on the Garfield Mine. We have advised the Smelter as to the settlement for this shipment. Will you please watch the sampling on this shipment, the same as you have for the Mabel Ore.

Yours very truly,

Chief Clerk.

Dec. 12, 1925.

Utah Ore Sampling Co.,
819 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On December 12th we shipped car of ore, our lot No. 53, in car Penn. 42479, from our Mabel Mine at Mina, Nevada, to the U. S. Smelting Refining & Mining Co. at their Midvale plant. This ore is to be sampled once at your plant and crushed to pass one inch mesh.

Our representatives will be Black and Deason, and will watch the sampling of this ore for us and handle as heretofore.

Included in this car is a lot of 140 sacks of ore from the Train and Budelman lease. This is to be handled the same as a separate Mabel lot, as to sampling. We have advised the smelter as to disposition of proceeds.

Yours very truly,

Chief Clerk.

Dec. 12, 1925.

U. S. Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On December 9th we shipped to your Midvale plant car of ore from our Mabel and included in the car 140 sacks of ore from lease being operated by Train and Budelman. Shipment was made in car Penn. 42479 and bill of lading covering shipment is enclosed.

The 140 sacks of ore are to be sampled and settled for separately, and handled as a Mabel Lot without number. Check and four copies of settlement sheet are to be mailed to Mr. Walter J. Harris, care Farmers & Merchants Bank, Reno, Nevada, and shown as being on account of Percy Train Lease on the Garfield Mine. Mail two copies of the settlement sheet to the undersigned, who will deliver to Mr. Budelman. Our Oakland Office has nothing to do with this special lot and are not to receive any copy of settlement sheet. The proportion of freight charges are to be deducted from the settlement sheet, in fact the shipment should be handled as if it had come in separately.

Our Mabel Lot No. 53, in the above car, is to be handled the same as previously, as to sampling, etc. Please sench check and two copies of settlement sheets covering Mabel Lot No. 53 to our Oakland Office, and four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

P.S.- Please return the empty sacks to the West End Cons. Mining Co., Mina, Nevada.

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTSNAME **West End Con.**SALT LAKE CITY, UTAH **Dec. 21st 1925**LOT NO. **53**SAMPLED BY **U.O.S.**

ASSAY PER TON OF 2,000 POUNDS

GOLD—Ozs.	SILVER—Ozs.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.525	99.4	7.5			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
60.5	3.0	9.9	10.4		

CHARGE, \$ _____

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

NAME West End Con.

SALT LAKE CITY, UTAH Dec. 21st 1925

LOT NO. 53

SAMPLED BY U.O.S.

ASSAY PER TON OF 2,000 POUNDS

GOLD—Ozs.	SILVER—Ozs.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.505 1.525	99.6 99.4	7.2 7.5			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
60.0 60.5	3.8 3.0	10.4 9.9	10.0 10.4		

CHARGE, \$

Black & Deason ASSAYERS

Stauff
Bradford

DAILY ASSAY REPORT

MABEL-SMELTER ORE CONTROL

TONOPAH, NEVADA, Oct. 30-25 1922

[illegible]

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, Dec. 29 1925

Pay West End Consolidated Mng. Co.

Ore _____ Lot No. 53 Class _____
 Sampled by UOS Received 12-17 Sampled 12-19 Assayed 12-22
 Metal Quotations—Silver .69 Copper, N. Y. _____ Lead, N. Y. 9.25 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co. ✓	<u>1.505</u>	<u>99.6</u>	✓	<u>5.95</u>	<u>60.0</u>	<u>10.0</u>	<u>3.8</u>	<u>10.4</u>	✓	
✓	<u>1.525</u>	<u>99.4</u>		<u>6.25</u>	<u>60.5</u>	<u>10.4</u>	<u>3.0</u>	<u>9.9</u>	✓	
Umpire										
Settlement Assay ✓	<u>1.515</u>	<u>99.5</u>	✓	<u>6.1</u>	<u>60.25</u>	<u>10.2</u>	<u>3.4</u>	<u>10.15</u>	✓	

CAR NOS.	WET WEIGHT	METAL VALUES		WORKING CHARGE	
<u>Pa. 42479</u>		Gold	<u>28 79</u>	Treatment	<u>5 39</u> ✓
		Silver	<u>65 22</u>	Insoluble	<u>6 03</u> ✓
		Copper		Zinc	
		Lead	<u>8 34</u>	Sulphur	<u>2 04</u> ✓
				Speiss	
Total Wet Weight					
Sacks				Total Debit	<u>13 46</u>
Net Weight	<u>101280</u> ✓	Gross Value	<u>102 35</u>	Iron	<u>61</u> ✓
Less H ₂ O <u>2.35</u> %	<u>2380</u>	Less Working Charge	<u>12 85</u>	Net Working Charge	<u>12 85</u>

Dry Weight, lbs. 98900 Payment for 49.45 tons @ 89 50 per ton 4425 78 ✓

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 8.50 per ton 430.44 ✓
 Assay Charges 5.00 ✓
 Sampling Charges Watching 4.00 ✓

Checked by

Approved by

Net Payment

3986 34

UNITED STATES SMELTING, REFINING & MILLING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, Dec. 29 1925

Pay West End Consolidated Mng. Co.

Ore _____ Lot No. 53 Class _____
 Sampled by UOS Received 12-17 Sampled 12-19 Assayed 12-22
 Metal Quotations—Silver .69 Copper, N. Y. _____ Lead, N. Y. 9.25 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co. ✓	1.505	99.6	✓	5.95	60.0	10.0	3.8	10.4	✓	
✓	1.525	99.4		6.25	60.5	10.4	3.0	9.9	✓	
Umpire										
Settlement Assay ✓	1.515	99.5	✓	6.1	60.25	10.2	3.4	10.15	✓	

CAR NOS.	WET WEIGHT	METAL VALUES	WORKING CHARGE
<u>Pa. 42479</u>		Gold <u>28 79</u>	Treatment <u>5 39</u> ✓
		Silver <u>65 22</u>	Insoluble <u>6 03</u> ✓
		Copper	Zinc
		Lead <u>8 34</u>	Sulphur <u>2 04</u> ✓
			Speiss
Total Wet Weight			
Sacks			Total Debit <u>13 46</u>
Net Weight <u>101280</u> ✓		Gross Value <u>102 35</u> ✓	Iron <u>61</u> ✓
Less H ₂ O <u>2.35</u> % <u>2380</u>		Less Working Charge <u>12 85</u>	Net Working Charge <u>12 85</u>

Dry Weight, lbs. 98900 ✓

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Payment for 49.45 tons @ 89 50 / per ton 4425 78 /
 Freight advanced @ 8.50 per ton 430.44 /
 Assay Charges 5.00 /
 Sampling Charges Watching 4.00 / 439 44

Checked by _____

Approved by _____

Net Payment

3986 34

WEST END CONSOLIDATED MINING COMPANY

DAILY ASSAY REPORT

MABEL ORE C ONTROL

TONOPAH, NEVADA, Jan. 5-26 192

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		
53/19 51	12-19 -25	1.58		98.40			Pb. 0.9 %
A/19 52	12-19 -25	1.37		21.65			Pb 15.1 %

J.P.M.
JPM

ASSAYER

Sampler Lot 1951

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 53 West End Cons. Mng Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63886 O. B. End	164120	62840	101280	Pa 42479	
Received Dec. 17, sampled Dec. 19, 1925					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 101280 lbs.

Sampling 45.58

Moisture 2.35 % 2380 lbs.

Dry Weight of Ore, 98900 lbs.

Salt Lake City, Utah Dec. 21, 1925

UTAH ORE SAMPLING COMPANY

Per

[Signature]

Sampler Lot 1951

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 53 West End Cons. Mng Co.

Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63886 O. B. End	164120	62840	101280	Pa 42479	
Received Dec. 17, sampled Dec. 19, 1925					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 101280 lbs.

Moisture 2.35 % 2380 lbs.

Dry Weight of Ore, 98900 lbs.

Salt Lake City, Utah Dec. 21, 1925

Sampling 45.53

UTAH ORE SAMPLING COMPANY

Per 

DAILY ASSAY REPORT

192

1871
JFM ASSAYER

DAILY ASSAY REPORT

TONOPAH, NEVADA, Oct. 30-25 192

[illegible]

DAILY ASSAY REPORT

NABEL-SMELTER ORE CONTROL

[illegible]

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR., GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

Dec. 29, 1925

Mr. Otto Falk
West End Consolidated Mng. Co.
Tonopah, Nevada

Dear Sir:

We were very pleased to receive your letter of December 26th
enclosing B/L on Lot 54, Mabel.

We note your instructions relative to handling settlement.

Thanking you for the shipment and wishing you a Happy and
Prosperous New Year, we remain

Yours very truly,

M. W. Woolley

MWW:M

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah,

Dec. 7 1925

Pay West End Cons. Mng. Co.

Ore _____ Lot No. 52 Class _____
 Sampled by UOS Received 11-24 Sampled 11-27 Assayed 11-30
 Metal Quotations—Silver .6925 Copper, N. Y. _____ Lead, N. Y. 9.75 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.47	118.3		7.35	66.0	8.2	1.4	5.4		
	1.49	118.6		7.65	66.4	8.3	.5	5.4		
Umpire										
Settlement Assay	1.48	118.45		7.5	66.2	8.25	.95	5.4		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE			
<u>GH 50868</u>		Gold <u>2.19⁸⁰</u>	<u>28</u>	<u>12</u>	✓	Treatment	<u>5</u>	<u>25</u>	✓
		Silver <u>9.59⁰</u>	<u>77</u>	<u>93</u>	✓	Insoluble	<u>6</u>	<u>62</u>	✓
		Copper				Zinc			
		Lead <u>1.65</u>	<u>10</u>	<u>94</u>	✓	Sulphur		<u>85</u>	✓
		<u>Quartz</u> <u>909⁰</u>				Speiss			
Total Wet Weight									
Sacks									
Net Weight	<u>37080</u>	Gross Value	<u>116</u>	<u>99</u>	✓	Total Debit	<u>12</u>	<u>72</u>	✓
Less H ₂ O <u>2.6</u> %	<u>2264</u>	Less Working Charge	<u>12</u>	<u>22</u>	✓	Iron		<u>50</u>	✓
						Net Working Charge	<u>12</u>	<u>22</u>	✓

Dry Weight, lbs.

34016✓ Payment for 42.408 tons @ 124 77 ✓ per tonFreight advanced @ 13.00 per ton

Assay Charges

Sampling Charges

Watching566.02 ✓5.005.00444309 ✓57602 ✓

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Checked by _____

Approved by _____

Net Payment

3867 07 ✓

Sampler Lot 1871

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 52 West End Cons. Mng Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63970	133500	46420	87080 ✓	GH 50868	
Received Nov. 24, sampled Nov. 27, 1925					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 87080 ✓ lbs.

Moisture 2.6 % 2264 ✓ lbs.

Dry Weight of Ore, 84816 ✓ lbs.

Salt Lake City, Utah

Nov. 28, 1925

Sampling

39.19

UTAH ORE SAMPLING COMPANY

Per

Lead 9.75 Silver Date of assay.

Sampler Lot

1871

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot **52 West End Cons. Mng Co.** Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63970	133500	46420	87080	GH 50868	
Received Nov. 24, sampled Nov. 27, 1925					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, **87080** lbs.

Moisture **2.6** % **2264** lbs.

Dry Weight of Ore, **84816** lbs.

Salt Lake City, Utah

Nov. 28, 1925

Sampling **39.19**

UTAH ORE SAMPLING COMPANY

Per

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH,

Nov. 30, 1925

NAME West End Con.

LOT NO. 52

SAMPLED BY

Utah Ore

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.47 1.49	118.3 118.6	8.6 8.9			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
66.0 66.4	1.4 0.5	5.4 5.4	8.2 8.3		

CHARGE, \$ 5.00

Black & Deason
ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH,

Nov. 30, 1925

NAME **West End Con.**

LOT No. **52**

SAMPLED BY

Utah Ore

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.49	118.6	8.9			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
66.4	0.5	5.4	8.3		

CHARGE, \$ **5.00**

Black & Deason

ASSAYERS

WEIGHT AND MOISTURE CERTIFICATE

Lot No. 22

SAMPLED BY

SHIPPER

192.....

[illegible]

Cars and Contents O. K. When Received Unless Noted Otherwise

SACKS

No.

Weight

Condition

Total Net Dry Weight

Moisture Per Cent

Total Net Weight

Weather

Remarks :

J. J. Stauffer

Lot No.

51

192

SAMPLED BY

SHIPPER

Weather

Remarks :

O and D Sample

40.294 Jons

Stamper
Bradford

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTSNAME **West End Con**

SALT LAKE CITY, UTAH,

August 22, 1925LOT NO. **48**SAMPLED BY **Utah Ore**

ASSAY PER TON OF 2,000 POUNDS

GOLD—Ozs.	SILVER—Ozs.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.30 1.28	78.3 78.5	Wet 7.5 7.6			
INSOLUBLE—%	ZINC —%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
73.4 73.0	1.0 1.1	3.8 3.8	6.3 7.1		

CHARGE, \$

5*Black & Deason* ASSAYERS

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, Oct. 24 1925

Pay West End Consolidated Mng. Co.

Ore _____ Lot No. 51 ✓ Class _____
 Sampled by U. O. S. Received 10-19 Sampled 10-21 Assayed 10-22 ✓
 Metal Quotations—Silver .715 ✓ Copper, N. Y. _____ Lead, N. Y. 9.50 ✓ Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	<u>2.04</u> ✓	<u>160.6</u> ✓		<u>9.15</u> ✓	<u>56.0</u> ✓	<u>10.3</u> ✓	<u>3.4</u> ✓	<u>8.1</u> ✓		
Umpire	<u>2.07</u> ✓	<u>161.0</u> ✓		<u>9.55</u> ✓	<u>55.2</u> ✓	<u>10.7</u> ✓	<u>2.0</u> ✓	<u>7.6</u> ✓		
Settlement Assay	<u>2.055</u>	<u>160.8</u> ✓		<u>9.35</u> ✓	<u>55.6</u> ✓	<u>10.5</u> ✓	<u>2.7</u> ✓	<u>7.85</u> ✓		

CAR NOS.	WET WEIGHT	METAL VALUES	WORKING CHARGE
<u>SP 27692</u>		Gold <u>39 05</u> ✓	Treatment <u>5 07</u> ✓
		Silver <u>109 22</u> ✓	Insoluble <u>5 56</u> ✓
		Copper	Zinc
		Lead <u>13 21</u> ✓	Sulphur <u>1 46</u> ✓
			Speiss
Total Wet Weight			
Sacks			Total Debit <u>12 09</u> ✓
Net Weight <u>83080</u> ✓		Gross Value <u>161 48</u> ✓	Iron <u>63</u> ✓
Less H ₂ O <u>3.0</u> % <u>2492</u> ✓		Less Working Charge <u>11 46</u> ✓	Net Working Charge <u>11 46</u> ✓

Dry Weight, lbs. 80588 ✓ Payment for 40.294 ✓ tons @ 150 02 ✓ per ton 6044 91 ✓

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 13.30 per ton

Assay Charges

Sampling Charges

Watching

552.48 ✓

5.00 ✓

5.00 ✓

562 48 ✓

Checked by

Approved by

Net Payment

5482 43 ✓

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

c/n a/c Frt.

Salt Lake City, Utah,

Sept. 25 1925

Pay West End Consolidated Mng. Co.

Ore Lot No. 49 Class
 Sampled by Received Sampled Assayed
 Metal Quotations—Silver Copper, N. Y. Lead, N. Y. Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.										
Umpire										
Settlement Assay										

CAR NOS.	WET WEIGHT	METAL VALUES			WORKING CHARGE		
		Gold			Treatment		
		Silver			Insoluble		
		Copper			Zinc		
		Lead			Sulphur		
					Speiss		
Total Wet Weight							
Sacks					Total Debit		
Net Weight	85720 ✓	Gross Value			Iron		
Less H ₂ O 3.3 %	2828 ✓	Less Working Charge			Net Working Charge		

Dry Weight, lbs.	82892 ✓	Payment for	41.446 ✓ tons @	141 71 ✓	per ton	5875 81 ✓
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.		Freight advanced @	11.90 per ton		510.03 ✓	
		Assay Charges			5.00 ✓	
		Sampling Charges	Watching		5.00 ✓	
		Sampling refund			42.14 ✓	477 89 ✓
						5395 42 ✓
Checked by					Paid	5335 41 ✓
Approved by				Net Payment		60 01 ✓

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, Oct. 24 1925

Pay West End Consolidated Mng. Co.

Ore _____ Lot No. 51 _____ Class _____
 Sampled by U. O. S. _____ Received ~~xxx~~ 10-19 _____ Sampled 10-21 _____ Assayed 10-22 _____
 Metal Quotations—Silver .715 _____ Copper, N. Y. _____ Lead, N. Y. 2.50 _____ Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	2.04	160.6		9.15	56.0	13.3	3.4	8.1		
	2.07	161.0		9.55	55.2	10.7	2.0	7.6		
Umpire										
Settlement Assay	2.055	160.8		9.35	55.6	10.5	2.7	7.85		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE			
SP 27692		Gold	39	05		Treatment	5	07	
		Silver	109	22		Insoluble	5	56	
		Copper				Zinc			
		Lead	13	21		Sulphur	1	46	
						Speiss			
Total Wet Weight									
Sacks						Total Debit	12	09	
Net Weight	83080	Gross Value	161	48		Iron		63	
Less H ₂ O 3.0 %	2492	Less Working Charge	11	46		Net Working Charge	11	46	

Dry Weight, lbs. 80588 Payment for 40.294 tons @ 150 02 per ton 6044 91

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 12.30 per ton 552.48
 Assay Charges 5.00
 Sampling Charges 5.00
 Watching 562 48

Checked by

Approved by

Net Payment

5482 43

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 51 West End Con Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62333	129740	46660	83080	SP 27692	
Received Oct. 19, sampled Oct. 21, 1925					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 83080 ✓ lbs.

Moisture 3.0 % 2492 ✓ lbs.


Dry Weight of Ore, 80588 ✓ lbs.

Salt Lake City, Utah Oct. 21, 1925

40.294 tons

Sampling 37.39

UTAH ORE SAMPLING COMPANY

Per 

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 51 West End Con Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62333	129740	46660	83080	SP 27692	
Received Oct. 19, sampled Oct. 21, 1925					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 83080 lbs.


Moisture 3.0 % 2492 lbs.

Dry Weight of Ore, 80588 lbs.

Salt Lake City, Utah Oct. 21, 1925

Sampling 37.39

UTAH ORE SAMPLING COMPANY

Per 

165 S. WEST TEMPLE ST

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH.

Oct 22, 1925

NAME **West End Con.**

LOT No. **51-Original**

SAMPLED BY **Utah Ore**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
2.04	160.6	10.4			
2.07	161.0	10.8			
2.055	160.80	9.35			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
56.0	3.4	8.1	10.3		
55.2	2.0	7.6	10.7		
55.6	2.7	7.85	10.2		

CHARGE, \$ **5.00**

Black & Deason

ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAB. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH,

Oct 22, 1925

NAME **West End Con.**

LOT No. **51-Original**

SAMPLED BY **Utah Ore**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
2.07	161.0	10.8			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
55.2	2.0	7.6	10.7		

CHARGE, \$ **5.00**

Black & Deason

ASSAYERS

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR., GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

October 20th, 1925.

West End Consolidated Mining Co.,

Tonopah, Nevada.

Dear Sirs:-

We beg to acknowledge receipt of your letter of
October 17th, advising as to shipment of your Lot 51. We
will be pleased to handle same according to your instructions.

Yours very truly,

W. H. Eardley

WHE:H

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH. Oct. 9, 1925

NAME West End Con

Lead @ 9.508
ag @ .71

LOT NO. 50

SAMPLED BY Utah Ore

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.56 1.56 1.56	185.2 185.6 185.4	12.1 12.2 10.9	(nil)		
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
62.4 62.2 62.4	2.3 1.5	5.6 4.6 5.1	7.8 8.0 7.9		

CHARGE, \$ 5

Black & Deason

ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH, Oct. 9, 1925

NAME **West End Con**

LOT NO. **50**

SAMPLED BY **Utah Ore**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.56	185.6	12.2			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
62.2	1.5	4.6	8.0		

CHARGE, \$ **5**

Black & Deason ASSAYERS

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEW HOUSE BUILDING

Salt Lake City, Utah, Oct. 16 1925

Pay West End Cons. Mng. Co.

Ore _____ Lot No. 50 Class _____
 Sampled by U. O. S. Received 10-6 Sampled 10-8 Assayed 10-9
 Metal Quotations—Silver .71 Copper, N. Y. _____ Lead, N. Y. 9.508 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	<u>1.56</u> ✓	<u>185.2</u> ✓		<u>10.85</u> ✓	<u>62.6</u> ✓	<u>7.8</u> ✓	<u>2.3</u> ✓	<u>5.6</u> ✓		
	<u>1.56</u> ✓	<u>185.6</u> ✓		<u>10.95</u> ✓	<u>62.2</u> ✓	<u>8.0</u> ✓	<u>1.5</u> ✓	<u>4.6</u> ✓		
Umpire										
Settlement Assay	<u>1.56</u> ✓	<u>185.4</u> ✓		<u>10.9</u> ✓	<u>62.4</u> ✓	<u>7.9</u> ✓	<u>1.9</u> ✓	<u>5.1</u> ✓		

CAR NOS.	WET WEIGHT	METAL VALUES		WORKING CHARGE	
<u>H SP 18159</u>		Gold	<u>29 64</u> ✓	Treatment	<u>4 91</u> ✓
		Silver	<u>125 05</u> ✓	Insoluble	<u>6 24</u> ✓
		Copper		Zinc	
		Lead	<u>15 42</u> ✓	Sulphur	<u>78</u> ✓
				Speiss	
Total Wet Weight				Total Debit	<u>11 93</u> ✓
Sacks				Iron	<u>47</u> ✓
Net Weight	<u>87560</u> ✓	Gross Value	<u>170 11</u> ✓	Net Working Charge	<u>11 46</u> ✓
Less H ₂ O <u>2.9</u> %	<u>2540</u> ✓	Less Working Charge	<u>11 46</u> ✓		

Dry Weight, lbs. <u>85020</u> ✓	Payment for <u>42.51</u> ✓ tons @ <u>158 65</u> ✓ per ton	<u>6744 21</u> ✓
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.	Freight advanced @ <u>13.30</u> per ton	<u>582.27</u> ✓
	Assay Charges <u>5.00</u> ✓	<u>592 27</u> ✓
	Sampling Charges <u>Watching</u>	
Checked by _____	Net Payment	<u>6151 94</u> ✓
Approved by _____		

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEW HOUSE BUILDING

Salt Lake City, Utah, Oct. 16 1925

Pay West End Cons. Mng. Co.

Ore Lot No. 50 Class
 Sampled by U. O. S. Received 10-6 Sampled 10-8 Assayed 10-9
 Metal Quotations—Silver .71 Copper, N. Y. Lead, N. Y. 9.508 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.56	185.2		10.85	62.6	7.8	2.3	5.6		
	1.56	185.6		10.95	62.2	8.0	1.5	4.6		
Umpire										
Settlement Assay	1.56	185.4		10.9	62.4	7.9	1.9	5.1		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE			
H SP 18159		Gold	29	64		Treatment		4	91
		Silver	125	05		Insoluble		6	24
		Copper				Zinc			
		Lead	15	42		Sulphur			78
						Speiss			
Total Wet Weight									
Sacks						Total Debit		11	93
Net Weight	87560	Gross Value	170	11		Iron			47
Less H ₂ O 2.9 %	2540	Less Working Charge	11	46		Net Working Charge		11	46

Dry Weight, lbs. 85020	Payment for 42.51 tons @ 158 65 per ton	6744	21
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.	Freight advanced @ 13.30 per ton	582.27	
	Assay Charges	5.00	
	Sampling Charges Watchdog	5.00	592 27
Checked by			
Approved by	Net Payment	6151	94

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

c/n a/c Frt.

Salt Lake City, Utah, Sept. 25 1925

Pay West End Consolidated Mng. Co.

Ore _____ Lot No. 49 Class _____
 Sampled by _____ Received _____ Sampled _____ Assayed _____
 Metal Quotations—Silver _____ Copper, N. Y. _____ Lead, N. Y. _____ Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.										
Umpire										
Settlement Assay										

CAR NOS.	WET WEIGHT	METAL VALUES			WORKING CHARGE		
		Gold			Treatment		
		Silver			Insoluble		
		Copper			Zinc		
		Lead			Sulphur		
					Speiss		
Total Wet Weight							
Sacks					Total Debit		
Net Weight		Gross Value			Iron		
Less H ₂ O %		Less Working Charge			Net Working Charge		

Dry Weight, lbs.

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Payment for	41.446	tons @	141 71	per ton	5873 31
Freight advanced @	11.90	per ton		510.03	
Assay Charges				5.00	
Sampling Charges	Watching			5.00	
Sampling refund				42.14	477 89
					5395 42
				Paid	5335 41
Checked by					
Approved by				Net Payment	60 01

Lot No.

Lot No.

SHIPPER

SAMPLED BY

192

Weather.

Remarks:

Bradford

Sampler Lot 1673

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 50 West End Cons. Mng Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62625	133920 <i>46360</i> <i>7560</i>	46360	87560	SP 18159	
	Received Oct. 6, sampled Oct. 8, 1925				

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 87560 ✓ lbs.

Moisture 2.9 % 2540 ✓ lbs.

Dry Weight of Ore, 85020 ✓ lbs.

Salt Lake City, Utah Oct. 8, 1925

42.510

Sampling 39.40

UTAH ORE SAMPLING COMPANY

Per

Sampler Lot ' 1673

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 50 West End Cons. Mng Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62625	133920	46360	87560	SP 18159	
Received Oct. 6, sampled Oct. 8, 1925					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 87560 ✓ lbs.


Moisture 2.9 % 2540 ✓ lbs.

Dry Weight of Ore, 85020 ✓ lbs.

Salt Lake City, Utah Oct. 8, 1925

Sampling 39.40

UTAH ORE SAMPLING COMPANY

Per 

Sampler Lot **1577**

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot **49 West End Cons Mng Co.** Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62180	132380	46660	85720	UP 135002	
Received Sept. 5, sampled Sept. 8, 1925					

Total Wet Weight _____ lbs.
 _____ Sacks _____ lbs.

Net Weight of Ore, **85720** lbs.

Moisture **3.3** % **2828** lbs.

Dry Weight of Ore, **82892** lbs.

Salt Lake City, Utah **Sept. 8, 1925**

Sampling **38.57**

UTAH ORE SAMPLING COMPANY

Per 

Sampler Lot 1577

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 49 West End Cons Mng Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62180	132380	46660	85720 ✓	UP 135002	
Received Sept. 5, sampled Sept. 8, 1925					

Total Wet Weight lbs.

_____ Sacks lbs.

Net Weight of Ore, 85720 lbs.

Moisture 3.3 % 2828 lbs.

Dry Weight of Ore, **82892** ✓ lbs.

Salt Lake City, Utah Sept. 8, 1925

Sampling	38.57
----------	-------

UTAH ORE SAMPLING COMPANY

Per

DAILY ASSAY REPORT

MABEL ORE CONTROL

TONOPAH, NEVADA, Oct. 15-25 1922

[illegible]

DAILY ASSAY REPORT

TONOPAH, NEVADA, Oct. 15-25 1922

[illegible]

Lot No. 47

192.....

SAMPLED BY

SHIPPER

Cars and Contents O. K. When Received Unless Noted Otherwise

SACKS

No.

Weight

Condition

Total Net Dry Weight

Moisture 32 Per Cent

Total Net Weight

Weather

Remarks :

$$\begin{array}{r} 2828 \\ \hline 82892 \end{array}$$

0th & 1st Sample

S. B. Stauffer

WEST END CONSOLIDATED MINING COMPANY

DAILY ASSAY REPORT

TONOPAH, NEVADA, Sept. 18-25 192

MABEL ORE CONTROL.

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		
49/1577	9-8-25	1.62		156.80			Pb 9.7 %

JPM

ASSAYER

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH.

Sept. 9, 1925

NAME West End Con

LOT NO. 49-0

SAMPLED BY Utah Ore

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.665	158.0	10.5			
1.69 1.6775	158.5	10.7	little 9.35%		
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
66.6	1.5	3.6	7.8		
66.4	0.5	3.4	7.5		
66-5	1-0	3-5	7-65		

CHARGE, \$

Black & Deason ASSAYERS

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR., GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

Sept. 4 1925

West End Consolidated Mng. Co.

Tonopah, Nevada

Dear Sir: Attention: Mr. Falk

We were very pleased to receive your letter of September 1st enclosing bill of lading on Lot 49, Mabel ore.

We note the instructions relative to disposition of the proceeds, and thanking you for the shipment, remain

Very truly yours,

M. W. Woolley

MWW:M

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, Sept. 12, 1925.

Pay West End Cons. Mining Co.,

Ore _____ Lot No. 49 Class _____
 Sampled by UOS Received 9-5 Sampled 9-8 Assayed 9-10
 Metal Quotations—Silver .72 ✓ Copper, N. Y. _____ Lead, N. Y. 9.517 ✓ Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	<u>1.665</u> ✓	<u>158.0</u> ✓		<u>9.25</u> ✓	<u>66.6</u> ✓	<u>7.8</u> ✓	<u>1.5</u> ✓	<u>3.6</u> ✓		
Umpire	<u>1.69</u> ✓	<u>158.5</u> ✓		<u>9.45</u> ✓	<u>66.4</u> ✓	<u>7.5</u> ✓	<u>.5</u> ✓	<u>3.4</u> ✓		
Settlement Assay	<u>1.6775</u> ✓	<u>158.25</u> ✓		<u>9.35</u> ✓	<u>66.5</u> ✓	<u>7.65</u> ✓	<u>1.0</u> ✓	<u>3.5</u> ✓		

CAR NOS.	WET WEIGHT	METAL VALUES		WORKING CHARGE	
<u>U.P. 135002</u>		Gold	<u>31 87</u> ✓	Treatment	<u>5 07</u> ✓
		Silver	<u>108 24</u> ✓	Insoluble	<u>6 65</u> ✓
		Copper		Zinc	
		Lead	<u>13 24</u> ✓	Sulphur	<u>38</u> ✓
				Speiss	
Total Wet Weight				Total Debit	<u>12 10</u> ✓
Sacks		Gross Value	<u>153 35</u> ✓	Iron	<u>46</u> ✓
Net Weight	<u>85720</u> ✓	Less Working Charge	<u>11 64</u> ✓	Net Working Charge	<u>11 64</u> ✓
Less H ₂ O <u>3.3</u> %	<u>2828</u> ✓				

Dry Weight, lbs. <u>82892</u> ✓	Payment for <u>41.446</u> ✓ tons @ <u>141 71</u> ✓ per ton		
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.	Freight advanced @ <u>13.30</u> per ton	<u>570.04</u> ✓	<u>5873 31</u> ✓
	Assay Charges	<u>5.00</u>	
	Sampling Charges	<u>5.00</u>	
	Watching	<u>42.14</u>	
	Refund sampling lots 44 and 45		<u>537 90</u> ✓

Checked by _____	Net Payment	<u>5335 41</u> ✓
Approved by _____		

721 should be 11 54

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR., GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

Sept. 2nd 1925

Mr. Otto Falk, Chief Clerk
West End Consolidated Mng. Co.
Tonopah, Nevada

Dear Mr. Falk:

Your letter of August 27th relative to Mabel settlements has been received.

On the next lot of Mabel we will make an adjustment on the sampling as per the terms of the contract and trust that this method will be satisfactory.

Thanking you for directing it to our attention, and with kind regards, we remain

Very truly yours,

M. W. Woolley

MWW:M

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, Sept. 12, 1925.

Pay West End Cons. Mining Co.,

Ore Lot No. 49 Class
 Sampled by UOS Received 9-5 Sampled 9-8 Assayed 9-10
 Metal Quotations—Silver .72 Copper, N. Y. Lead, N. Y. 9.517 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.665	158.0		9.25	66.6	7.8	1.5	3.6		
Umpire	1.69	158.5		9.45	66.4	7.5	.5	3.4		
Settlement Assay	1.6775	158.25		9.35	66.5	7.55	1.0	3.5		
CAR NOS.	WET WEIGHT		METAL VALUES				WORKING CHARGE			
U.P. 135002			Gold		31	87	Treatment		5	07
			Silver		108	24	Insoluble		6	65
			Copper				Zinc			
			Lead		13	24	Sulphur			38
							Speiss			
Total Wet Weight										
Sacks										
Net Weight	83720		Gross Value		153	35	Total Debit		12	10
Less H ₂ O 3.3 %	2828		Less Working Charge		11	64	Iron			46
							Net Working Charge		11	64

Dry Weight, lbs.

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Payment for	tons @	per ton	
Freight advanced @ 41.446	per ton	141 71	5873 31
Assay Charges	13.30		
Sampling Charges		576.04	
Watching		5.00	
Refund sampling lots 44 and 45		5.00	
		42.14	537 90

Checked by

Approved by

Net Payment

5335 41

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH.

Sept. 9, 1925

NAME **West End Con**

LOT NO. **49-0**

SAMPLED BY **Utah Ore**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.665	158.0	10.5			
1.69	158.5	10.7			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
66.6	1.5	3.6	7.8		
66.4	0.5	3.4	7.5		

CHARGE, \$ _____

Black & Deason ASSAYERS

8/15/25

Otto -

Am sending the two copies of the bill of Lading of lot #48 - Not having information as to what to do therewith. -
 - No lot number was given the RR at the time - and is not noted on the bill of lading. - Also - the car is to be sampled enroute at Murray - which I presume is the regular procedure - this regardless of the fact that no note to that effect is on our bill of lading. I imagine the freight clerk made the notation on the copy he retained, because he said the car was shipped that way. -

U. P.	124157
Gross	137260
Tare	4300-
Net	94260 [#]

Hot head part arrived today

NINTH FLOOR NEWHOUSE BUILDING

Pay West End Cons. Mining Co.,

Ore		Lot No.		48		Class				
Sampled by		UOS		Received		8-18		Sampled		
						8-21		Assayed		
Metal Quotations—Silver		.705		Copper, N. Y.		Lead, N. Y.		8.958		
								Zinc		
ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
I. S. S. Co.	1.30	78.3		6.25	73.4	6.5	1.0	3.8		
	1.28	78.5		6.35	73.0	7.1	1.1	3.8		
Umpire										
Settlement Assay	1.29	78.4		6.30	73.2	6.8	1.05	3.8		
CAR NOS.	WET WEIGHT									

[illegible]

Sampler Lot 1504

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 48 West End Con. Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62295	141240	46640	94600	UP 124157	
Received August 18, sampled August 21, 1925					

Total Wet Weight lbs.
 _____ Sacks lbs.

Net Weight of Ore, 94600 lbs.


Moisture 2.8 % 2648 lbs.

Dry Weight of Ore, 91952 lbs.

Salt Lake City, Utah August 21, 1925

Sampling 42.57

UTAH ORE SAMPLING COMPANY

Per 

Sampler Lot 1504

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 48 West End Con. Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62295	141240	46640	94600	UP 124157	
Received August 18, sampled August 21, 1925					
for Sample	Sold '97	Taken 60.50	Tested 6.8%		

Total Wet Weight lbs.
Sacks lbs.

Net Weight of Ore, 94600 ✓ lbs.

Moisture 2.8 % 2648 ✓ lbs.

Dry Weight of Ore, 91952 ✓ lbs.

Salt Lake City, Utah August 21, 1925

Sampling 42.57

UTAH ORE SAMPLING COMPANY

Per

WEST END CONSOLIDATED MINING COMPANY

DAILY ASSAY REPORT

TONOPAH, NEVADA, AUG 29 - 25 192

MABEL ORE CONTROL

SAMPLE
NUMBER

WORKING PLACE

GOLD
OUNCES VALUE

SILVER
OUNCES VALUE

TOTAL
VALUE

REMARKS

48 / 1504 8-21-25

1.35

76.65

Pb
7.0 %

JPM

ASSAYER

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR., GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH
August 21 1925

West End Consolidated Mng. Co.

Tonopah, Nevada

Gentlemen:

We were very pleased to receive your letter of August 17th notifying us of the shipment of another car, your Lot #48, from the Mabel.

We note the instructions relative to handling of the ore and will do everything we can to render prompt and satisfactory settlement.

Thanking you for the shipment, we remain

Very truly yours,

M. W. Woolley

MWW:M

Lot No.

Lot No.

SAMPLED BY

SHIPPER

192...

[illegible]

Cars and Contents O. K. When Received Unless Noted Otherwise

SACKS

No.

Weight

Condition

Total Net Dry Weight

Moisture

Per Cent

Total Net Weight

Weather

Remarks :

Stauffer ✓
Bradford