

Mabel Mine Lots 54-65
One Settlement 1926

MABEL MINE SERIES
ORE SETTLEMENTS
LOTS 54 - 65

26

1926

(254)

Item 117

26 of 46

4840 0917

formerly

4840 0117

see also 4840

0117, 0911, 0912, 0913,

0914, 0915, 0916, 0918,

0919, 0920, 0921, 0922,

0923, 0924, 0925, and 0926

October 14, 1926.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On October 13th we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore our lot No. 64, in car SP-86241, bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Company, and is to be crushed to pass one inch mesh.

Black & Deason will watch this sampling for us and handle as heretofore.

Please be advised that the main office of this Company has been moved from Oakland, California, to Tonopah, and the Oakland office discontinued. Kindly send check covering returns, together with four copies of settlement sheet, to West End Consolidated Mining Company, Tonopah, Nevada.

Please acknowledge receipt of this letter and advise if instructions regarding settlement are understood.

Yours very truly,

Mine Superintendent

HDB-FW

October 13, 1926.

Black & Deason,
165 So. West Temple St.,
Salt Lake City, Utah.

Gentlemen:

We are shipping today to the United States Smelting Refining and Mining Company, at their Midvale plant, carload of ore from our Mabel Mine, our Lot No.64, in car SP-86241.

This ore is to be sampled once at the plant of the Utah Ore Sampling Company, and crushed to pass one inch mesh.

Will you please watch this sampling for us and handle as heretofore.

Yours very truly,

Mine Superintendent

HDB-FW

October 13, 1926.

Utah Ore Sampling Company,
914-915 Continental Building,
Salt Lake City, Utah.

Gentlemen:

On October 13th we shipped car of ore,
our Lot No. 64, in car SP-86241, from our Mabel
Mine at Mina, Nevada, to the United States Smelting
& Refining Company at their Midvale plant.

This ore is to be sampled once at your
plant and crushed to pass one inch mesh, and is to
be handled same as heretofore.

Our representatives will be Black & Deason
of Salt Lake City, who will watch this sampling for
us as before.

Yours very truly,

Mine Superintendent

HDB-FW

November 20, 1926.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

We shipped today to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our Lot No. 65, in car SP-24629. Bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Company, and is to be crushed to pass one inch mesh.

Black & Deason will watch this sampling for us and handle as heretofore.

Please send check covering returns together with copy of settlement sheets, to the West End Consolidated Mining Company at Tonopah, Nevada.

Yours very truly,

Secretary.

OF-FW

November 20,,1926.

Messrs. Black & Deason,
165 So. West Temple St.,
Salt Lake City, Utah.

Gentlemen:

We are shipping today to the United States Smelting Refining and Mining Company, at their Midvale plant, carload of ore from our Mabel Mine, our Lot No.65, in car SP-24629.

This ore is to be sampled once at the plant of the Utah Ore Sampling Company, and crushed to pass one inch mesh.

Will you please watch this sampling for us and handle as heretofore.

Yours very truly,

Secretary.

OF-FW

November 20, 1926.

Utah Ore Sampling Company,
914-915 Continental Building,
Salt Lake City, Utah.

Gentlemen:

On November 20th we shipped car of ore,
our Lot. No.65, in car SP-24629, from our Mabel
Mine at Mina, Nevada, to the United States Smelting
& Refining Company at their Midvale plant.

This ore is to be sampled once at your
plant and crushed to pass one inch mesh, and is to
be handled same as heretofore.

Our representatives will be Black & Deason
of Salt Lake City, who will watch this sampling for
us as before.

Yours very truly,

Secretary.

OF-FW

Dec. 26, 1925.

Utah Ore Sampling Co.,
819 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

One December 24th we shipped car of ore, our Lot No. 54, in car S.P. 30124, from our Mabel Mine at Mina, Nevada, to the U.S. Smelting, Refining & Mining Co. at their Midvale plant.

This ore is to be sampled once at your plant and crushed to pass one-inch mesh, and to be handled same as heretofore.

Our representatives will be Black & Deason, who will watch this sampling for us, as before.

Yours very truly,

Chief Clerk.

Dec. 26, 1925.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On December 24th we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our lot No. 54, in car S.P. 30124. Bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh. Only one sampling is required.

Black & Deason of Salt Lake City will watch this sampling for us, and handle same as heretofore.

Please send check with two copies of settlement sheet to our Oakland Office and send four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

CC-JWS

Jan. 23, 1926.

Utah Ore Sampling Co.,
819 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On January 21st we shipped car of ore, our lot No. 55, in car S.P.23380, from our Mabel Mine at Mina, Nevada, to the U.S. Smelting, Refining & Mining Co. at their Midvale plant.

This ore is to be sampled once at your plant and crushed to pass one-inch mesh, and to be handled same as heretofore.

Our representatives will be Black & Deason, who will watch this sampling for us, as before.

Yours very truly,

Chief Clerk.

Jan. 23, 1926.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On January 21st we shipped to the U. S. Smelting Refining and Mining Co. at their Midvale plant, carload of ore from our Mabel Mine, our lot No. 55, in Car S.P. 23380.

This ore is to be sampled once at the plant of the Utah Ore Sampling Co. and crushed to pass one inch mesh.

Will you please watch this sampling for us and handle as heretofore.

Yours very truly,

Chief Clerk.

Dec. 26, 1925.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On December 24th we shipped to the U.S. Smelting Refining and Mining Co. at their Midvale plant, carload of ore from our Mabel Mine, our Lot No. 54, in car S.P.30124.

This ore is to be sampled once at the plant of the Utah Ore Sampling Co. and crushed to pass one inch mesh.

Will you please watch this sampling for us and handle same as heretofore.

Yours very truly,

Chief Clerk.

March 11, 1926.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On March 10th we shipped to the U.S. Smelting,
Refining & Mining Co. at their Midvale plant, carload of
ore from our Mabel Mine, our lot No. 57, in car GHSA 34827.

This ore is to be sampled once at the plant of
the Utah Ore Sampling Co. and crushed to pass one-inch mesh.

Will you please watch this sampling for us and
handle as heretofore.

Yours very truly,

Chief Clerk.

March 11, 1926.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On March 10th we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our lot No. 57, in car GHSA 34827. Bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh.

Black & Deason of Salt Lake City will watch this sampling for us, and handle same as heretofore.

Please send check with two copies of settlement sheet to our Oakland Office and send four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

CC-JWS

Jan. 23, 1926.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On January 21st we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of Ore, our lot No. 55, in car S.P.23380. Bill of Lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh.

Black & Dession of Salt Lake City will watch this sampling for us, and handle same as heretofore.

Please send check with two copies of settlement sheet to our Oakland Office and send four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

CC-JWS

B/L weight 102000#

Feb. 17, 1926.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On February 15th we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our lot No. 56, in car U.P. 13866. Bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh.

Black & Deason of Salt Lake City will watch this sampling for us, and handle same as heretofore.

Please send check with two copies of settlement sheet to our Oakland Office and send four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

C[✓]-JWS

Feb. 17, 1926.

Utah Ore Sampling Co.,
819 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On February 15th we shipped car of ore, our lot No. 56, in car U.P. 13866, from our Mabel Mine at Mina, Nevada, to the U.S. Smelting, Refining & Mining Co. at their Midvale Plant.

This ore is to be sampled once at your plant and crushed to pass one-inch mesh, and to be handled same as heretofore.

Our representatives will be Black & Deason, who will watch this sampling for us, as before.

Yours very truly,

Chief Clerk.

March 11, 1926.

Utah Ore Sampling Co.,
819 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On March 10th we shipped car of ore, our lot No. 57, in car GHSA 34827, from our Mabel Mine at Mina, Nevada, to the U.S. Smelting, Refining & Mining Co. at their Midvale Plant.

This ore is to be sampled once at your plant and crushed to pass one-inch mesh, and to be handled same as heretofore.

Our representatives will be Black & Deason who will watch this sampling for us, as before.

Yours very truly,

Chief Clerk.

APRIL 2, 1926.

UNITED STATES SMELTING, REFINING & MINING CO.,
912 NEWHOUSE BUILDING,
SALT LAKE CITY, UTAH.

GENTLEMEN:

ON APRIL 1ST WE SHIPPED TO YOUR MIDVALE PLANT
FROM OUR MABEL MINE AT MINA, NEVADA, CARLOAD OF ORE, OUR
LOT NO. 58, IN CAR SP 24523. BILL OF LADING COVERING
SHIPMENT IS ENCLOSED.

THIS ORE IS TO BE SAMPLED IN TRANSIT AT THE PLANT
OF THE UTAH ORE SAMPLING CO. AND IS TO BE CRUSHED TO PASS
ONE-INCH MESH.

BLACK & DEASON OF SALT LAKE CITY WILL WATCH THIS
SAMPLING FOR US, AND HANDLE SAME AS HERETOFORE.

PLEASE SEND CHECK WITH TWO COPIES OF SETTLEMENT
SHEET TO OUR OAKLAND OFFICE AND SEND FOUR COPIES OF SETTLE-
MENT SHEET TO THIS OFFICE.

YOURS VERY TRULY,

CHIEF CLERK.

CC-JWS

106 000 #

98 1/2 volutions

APRIL 2, 1926.

MESSRS. BLACK & DEASON,
165 SOUTH WEST TEMPLE ST.,
SALT LAKE CITY, UTAH.

GENTLEMEN:

ON APRIL 1ST WE SHIPPED TO THE U.S.
SMELTING, REFINING & MINING CO. AT THEIR MIDVALE
PLANT, CARLOAD OF ORE FROM OUR MABEL MINE, OUR
LOT NO. 58, IN CAR SP 24523.

THIS ORE IS TO BE SAMPLED ONCE AT THE
PLANT OF THE UTAH ORE SAMPLING CO. AND CRUSHED TO
PASS ONE-INCH MESH.

WILL YOU PLEASE WATCH THIS SAMPLING FOR
US AND HANDLE AS HERETOFORE.

YOURS VERY TRULY,

CHIEF CLERK.

Feb. 17, 1926.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On February 15th we shipped to the U.S. Smelting Refining and Mining Co. at their Midvale plant, carload of ore from our Mabel Mine, our lot No. 56, in car S.P. 13866.

This ore is to be sampled once at the plant of the Utah Ore Sampling Co. and crushed to pass one-inch mesh.

Will you please watch this sampling for us and handle as heretofore.

Yours very truly,

Chief Clerk.

B/L weight 95000 #

April 19, 1926.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On April 18th we shipped to the U.S. Smelting,
Refining & Mining Co. at their Midvale plant, carload
of ore from our Mabel Mine, our Lot No. 59, in car U.P.
15327.

This ore is to be sampled once at the plant
of the Utah Ore Sampling Co. and crushed to pass one-
inch mesh.

Will you please watch this sampling for us
and handle as heretofore.

Yours very truly,

Chief Clerk.

April 19, 1926.

Utah Ore Sampling Co.,
~~819 Newhouse Building,~~
Salt Lake City, Utah.

914-915 Continental Bank Bldg.

Gentlemen:

On April 18th we shipped car of ore,
out lot No. 59, in car U.P.15327, from our Mabel
Mine at Mina, Nevada, to the U.S.Smelting, Refining
& Mining Co. at their Midvale plant.

This ore is to be sampled once at your
plant and crushed to pass one-inch mesh, and is to
be handled same as heretofore.

Our representatives will be Black & Deason,
who will watch this sampling for us, as before.

Yours very truly,

Chief Clerk.

APRIL 2, 1926.

UTAH ORE SAMPLING CO.,
819 NEWHOUSE BUILDING,
SALT LAKE CITY, UTAH.

GENTLEMEN:

ON APRIL 1ST WE SHIPPED CAR OF ORE, OUR
LOT NO. 58, IN CAR SP 24523, FROM OUR MABEL MINE
AT MINA, NEVADA, TO THE U.S. SMELTING, REFINING &
MINING CO. AT THEIR MIDVALE PLANT.

THIS ORE IS TO BE SAMPLED ONCE AT YOUR
PLANT AND CRUSHED TO PASS ONE-INCH MESH, AND IS TO
BE HANDLED SAME AS HERETOFORE.

OUR REPRESENTATIVES WILL BE BLACK & DEASON,
WHO WILL WATCH THIS SAMPLING FOR US, AS BEFORE.

YOURS VERY TRULY,

CHIEF CLERK.

May 12, 1926.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On May 11th we shipped to the U.S. Smelting,
Refining & Mining Co. at their Midvale plant, carload
of ore from our Mabel Mine, our Lot No. 60, in car
S.P.26291.

This ore is to be sampled once at the plant
of the Utah Ore Sampling Co. and crushed to pass one-
inch mesh.

Will you please watch this sampling for us
and handle as heretofore.

Yours very truly,

Chief Clerk.

May 12, 1926.

Utah Ore Sampling Co.,
914-915 Continental Bank Bldg.,
Salt Lake City, Utah.

Gentlemen:

On May 11th we shipped car of ore, our Lot No. 60, in car S.P.26291, from our Mabel Mine at Mina, Nevada, to the U.S.Smelting, Refining & Mining Co. at their Midvale plant.

This ore is to be sampled once at your plant and crushed to pass one-inch mesh, and is to be handled same as heretofore.

Our representatives will be Black & Deason of Salt Lake City, who will watch this sampling for us, as before.

Yours very truly,

Chief Clerk.

April 19, 1926.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On April 18th we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our Lot No. 59, in car U.P.15327. Bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh.

Black & Deason of Salt Lake City will watch this sampling for us, and handle same as heretofore.

Please send check with two copies of settlement sheet to our Oakland Office, and send four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

CC-JWS

100,000 lb - value 80⁰⁰

July 3, 1926.

Utah Ore Sampling Co.,
914-915 Continental Bank Bldg.,
Salt Lake City, Utah.

Gentlemen:

On July 1st we shipped car of ore, our lot No. 62, in car S.P. 34579, from our Mabel Mine at Mina, Nevada, to the U.S. Smelting, Refining & Mining Co. at their Midvale plant.

This ore is to be sampled once at your plant and crushed to pass one-inch mesh, and is to be handled same as heretofore.

Our representatives will be Black & Deason of Salt Lake City, who will watch this sampling for us, as before.

Yours very truly,

Chief Clerk.

June 10, 1926.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On June 8th we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our lot No. 61, in car T&NO 38787. Bill of lading covering shipment is enclosed.

This car is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh.

Black & Deason of Salt Lake City will watch this sampling for us, and handle as heretofore.

Please send check with two copies of settlement sheet to our Oakland Office, and send four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

CC-JWS

May 12, 1926.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On May 11th we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our Lot No. 60, in car S.P.26291. Bill of lading covering shipment is enclosed.

This ore is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one-inch mesh.

Black & Deason of Salt Lake City will watch this sampling for us, and handle same as heretofore.

Please send check with two copies of settlement sheet to our Oakland Office, and send four copies of settlement sheet to this office.

In settling for Lot No. 59, you sent us only two copies of settlement sheet. Please send us two additional copies covering that lot.

Yours very truly,

Chief Clerk.

CC-JWS

July 3, 1926.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On July 1st we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our lot No. 62, in car S.P. 34579. Bill of lading covering shipment is enclosed.

This car is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one inch mesh.

Black & Deason of Salt Lake City will watch this sampling for us, and handle as heretofore.

Please send check with two copies of settlement sheet to our Oakland Office, and send four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

CC-JWS

B/L 86000 100⁵⁰

June 10, 1926.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On June 8th we shipped to the U.S. Smelting,
Refining & Mining Co. at their Midvale plant, carload
of ore from our Mabel Mine, our lot No. 61, in car T&NO
38787.

This ore is to be sampled once at the plant
of the Utah Ore Sampling Co. and crushed to pass one-
inch mesh.

Will you please watch this sampling for us and
handle as heretofore.

Yours very truly,

Chief Clerk.

June 10, 1926.

Utah Ore Sampling Co.,
914-915 Continental Bank Bldg.,
Salt Lake City, Utah.

Gentlemen:

On June 8th we shipped car of ore, our Lot No. 61, in car T&NO 38787, from our Mabel Mine at Mina, Nevada, to the U. S. Smelting, Refining & Mining Co. at their Midvale plant.

This ore is to be sampled once at your plant and crushed to pass one-inch mesh, and is to be handled same as heretofore.

Our representatives will be Black & Deason of Salt Lake City, who will watch this sampling for us, as before.

Yours very truly,

Chief Clerk.

CLASS OF SERVICE DESIRED	
TELEGRAM	
DAY LETTER	
NIGHT MESSAGE	
NIGHT LETTER	
Patrons should mark an X opposite the class of service desired; OTHERWISE THE MESSAGE WILL BE TRANSMITTED AS A FULL RATE TELEGRAM	

WESTERN UNION TELEGRAM

NEWCOMB CARLTON, PRESIDENT

GEORGE W. E. ATKINS, FIRST VICE-PRESIDENT

NO.	CASH OR CHG.
CHECK	
TIME FILED	

Send the following message, subject to the terms on back hereof, which are hereby agreed to

OTTO FALK
~~XXX~~ REDONDO BEACH, CALIF.

YOUR WIRE SETTLEMENT SHEET RECEIVED DATED AUGUST 27

F. C. NINNIS

CHARGE: WEST END

CLASS OF SERVICE	SYMBOL
TELEGRAM	
DAY LETTER	BLUE
NIGHT MESSAGE	NITE
NIGHT LETTER	N L

If none of these three symbols appears after the check (number of words) this is a telegram. Otherwise its character is indicated by the symbol appearing after the check.

WESTERN UNION TELEGRAM

NEWCOMB CARLTON, PRESIDENT

GEORGE W. E. ATKINS, FIRST VICE-PRESIDENT

CLASS OF SERVICE	SYMBOL
TELEGRAM	
DAY LETTER	BLÜE
NIGHT MESSAGE	NITE
NIGHT LETTER	N L

If none of these three symbols appears after the check (number of words) this is a telegram. Otherwise its character is indicated by the symbol appearing after the check.

The filing time as shown in the date line on full-rate telegrams and day letters, and the time of receipt at destination as shown on all messages, is STANDARD TIME.

Received at **TONOPAH, NEV.**

11 F VY 28 COLLECT

REDONDO BEACH CALIF 930AM SEP 4 1926

N C NINNIS

021

CARE WEST END CONS MINING CO TONOPAH NEV

IF SETTLEMENT FOR LAST MABEL LOT NOT YET RECEIVED PLEASE WIRE U S SMELTER
SEND CHECK AND ALL COPIES OF SETTLEMENT SHEETS TO TONOPAH INSTEAD OF
OAKLAND

OTTO FALK

1028A

Settlement sheets dated Aug 27

July, 3, 1926.

Messrs. Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On July 1st we shipped to the U.S. Smelting
Refining & Mining Co. at their Midvale plant, carload
of ore from our Mabel Mine, our lot No. 62, in car S.P.
34579.

This ore is to be sampled once at the plant
of the Utah Ore Sampling Co. and crushed to pass one-
inch mesh.

Will you please watch this sampling for us and
handle as heretofore.

Yours very truly,

Chief Clerk.

Aug. 16, 1926.

Utah Ore Sampling Co.,
914-915 Continental Bank Bldg.,
Salt Lake City, Utah.

Gentlemen:

On August 14th we shipped car of ore, our lot No. 63, in car H&TC 36692, from our Mabel Mine at Mina, Nevada, to the U.S. Smelting, Refining and Mining Co. at their Midvale plant.

This ore is to be sampled once at your plant and crushed to pass one-inch mesh, and is to be handled same as heretofore.

Our representatives will be Black & Deason of Salt Lake City, who will watch this sampling for us, as before.

Yours very truly,

Chief Clerk.

Aug. 14, 1926.

Black & Deason,
165 South West Temple St.,
Salt Lake City, Utah.

Gentlemen:

On August 14th we shipped to the U. S.
Smelting, Refining & Mining Co. at their Midvale
plant, carload of ore from our Mabel Mine, our
lot No. 63, in car H&TC 36692.

This ore is to be sampled once at the
plant of the Utah Ore Sampling Co. and crushed to
pass one-inch mesh.

Will you please watch this sampling for
us and handle as heretofore.

Yours very truly,

Chief Clerk.

August 16, 1926.

United States Smelting, Refining & Mining Co.,
912 Newhouse Building,
Salt Lake City, Utah.

Gentlemen:

On August 14th we shipped to your Midvale plant from our Mabel Mine at Mina, Nevada, carload of ore, our lot No. 63, in car H&TC 36692. Bill of lading covering shipment is enclosed.

This car is to be sampled in transit at the plant of the Utah Ore Sampling Co. and is to be crushed to pass one inch mesh.

Black & Deason will watch this sampling for us, and handle as heretofore.

Please send check with two copies of settlement sheet to our Oakland Office, and send four copies of settlement sheet to this office.

Yours very truly,

Chief Clerk.

CC-JWS

10
13
The main office of this company has been moved from Oakland to Tonopah, so kindly send checks covering returns, together with four copies of settlement sheet to "Post Box One N. G. Tonopah Nevada. Please acknowledge receipt of this letter and advise if instructions regarding settlement are understood.

Lot No.

Lot No.

SHIPPER

SAMPLED BY

192.

CARS AND CONTENTS O. K. WHEN RECEIVED UNLESS NOTED OTHERWISE

SACKS		
NO	WEIGHT	CONDITION

Weather

Remarks:

TOTAL NET WEIGHT

MOISTURE.....PER CENT

TOTAL NET DRY WEIGHT

3078
88782

Staupfer
Bradford

WEIGHT AND MOISTURE CERTIFICATE

Class

Received Nov. 25, sampled Nov. 28, 1926

41.34

Assaying

Dry Weight of Ore, 88782 lbs.

UTAH ORE SAMPLING COMPANY

Per _____

WEIGHT AND MOISTURE CERTIFICATE

Class

Received Nov. 25, sampled Nov. 28, 1926

41.34

Assaying

91860

3.35 %

88782

November 29, 1926

Per

WEST END CONSOLIDATED MINING COMPANY

DAILY ASSAY REPORT

Mabel Ore Control.

TONOPAH, NEVADA, Dec. 8-26 192

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		
65/4166	11-29-26	1.80	36.00	166.20	91.41	127.41	Pb 10.6 % @ 55¢

J. M.
JPM ASSAYER

WEST END CONSOLIDATED MINING COMPANY

DAILY ASSAY REPORT

Mabel Ore Control.

TONOPAH, NEVADA, Dec. 8-26 192

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		
65/4166	11-29-26	1.80		166.20			Pb 10.6 %

J.P.M.
JPM ASSAYER

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, December 2, 1926

Pay West End Con. Mining Co.

Ore Mable Mine Lot No. 65 Class
 Sampled by HQS Received 11-25 Sampled 11-28 Assayed 11-30
 Metal Quotations—Silver .54125 Copper, N. Y. Lead, N. Y. 8.00 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.81 ✓	162.3 ✓	✓	10.8 ✓	69.2 ✓	6.0 ✓	.4 ✓	.35 ✓		
	1.80 ✓	163.0 ✓	✓	11.05 ✓	67.8 ✓	6.1 ✓	.3 ✓	.2 ✓		
Umpire										
Settlement Assay	1.805 ✓	162.65 ✓	✓	10.93 ✓	68.5 ✓	6.05 ✓	.35 ✓	.28 ✓		

CAR NOS.	WET WEIGHT	METAL VALUE	WORKING CHARGE
SP 24629		Gold 34 30 ✓	Treatment 4 91 ✓
		Silver 83 63 ✓	Insoluble 6 85 ✓
		Copper	Zinc
		Lead 12 49 ✓	Sulphur
			Speiss
Total Wet Weight			
Sacks			Total Debit 11 76
Net Weight 91860 ✓		Gross Value 130 42 ✓	Iron 36 ✓
Less H ₂ O 3.35% 3078 ✓		Less Working Charge 11 40 ✓	Net Working Charge 11 40 ✓

Dry Weight, lbs. 88782 ✓

Payment for 44.391 ✓ tons @ 119.02 ✓ per ton

5283.42 ✓

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 11.90 per ton

546.57 ✓

Assay Charges

5.00 ✓

Sampling Charges

watching

5.00 ✓

556.57 ✓

Checked by

Approved by

Net Payment

4726.85 ✓

732

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, December 2, 1926

Pay West End Con. Mining Co.Ore Uable Mine Lot No. 65 Class Sampled by UOS Received 11-25 Sampled 11-28 Assayed 11-30Metal Quotations—Silver .64125 Copper, N. Y. Lead, N. Y. 2.00 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.81	162.3		10.8	69.2	6.0	.4	.35		
	1.80	163.0		11.05	67.9	6.1	.3	.2		
Umpire										
Settlement Assay	1.905	162.65		10.93	69.5	6.05	.35	.28		

CAR NOS.	WET WEIGHT	METAL VALUE	WORKING CHARGE
SP 24629		Gold 34 30	Treatment 4 91
		Silver 82 68	Insoluble 6 85
		Copper	Zinc
		Lead 13 49	Sulphur
			Speiss
Total Wet Weight			
Sacks			
Net Weight 91360		Gross Value 130 42	Total Debit 11 76
Less H ₂ O 3.3% 3070		Less Working Charge 11 40	Iron 36
			Net Working Charge 11 40

Dry Weight, lbs. 88732Payment for 44.391 tons @ 119.02 per ton 5283.42

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 11.90 per tonAssay Charges 545.57Sampling Charges 5.00watching 5.00556.57

Checked by

Approved by

Net Payment

4726.35

732

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, December 2, 1926

Pay West End Con. Mining Co.

Ore Hable Mine Lot No. 65 Class
 Sampled by UOS Received 11-25 Sampled 11-22 Assayed 11-30
 Metal Quotations—Silver 541.25 Copper, N. Y. Lead, N. Y. 8.00 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.81	162.3		10.8	69.2	6.0	.4	.35		
	1.90	163.0		11.05	67.8	6.1	.3	.2		
Umpire										
Settlement Assay	1.805	162.65		10.93	68.5	6.05	.35	.28		

CAR NOS.	WET WEIGHT	METAL VALUE		WORKING CHARGE	
SP 24629		Gold	34 30	Treatment	4 91
		Silver	83 63	Insoluble	6 85
		Copper		Zinc	
		Lead	12 49	Sulphur	
				Speiss	
Total Wet Weight				Total Debit	11 76
Sacks				Iron	36
Net Weight	91860	Gross Value	130 42	Net Working Charge	11 40
Less H ₂ O 3.35%	88782	Less Working Charge	11 40		

Dry Weight, lbs. 88782Payment for 44 391 tons @ 119.02 per ton 5283.42

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 11.90 per ton

Assay Charges

Sampling Charges

watching

546.57

5.00

5.00

556.57

Checked by

Approved by

Net Payment

4726.85

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE NO. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

NAME **West End Con.**

SALT LAKE CITY, UTAH, **Oct. 21, 1926.**

LOT NO. **64 Orig.**

SAMPLED BY **UOS**

ASSAY PER TON OF 2,000 POUNDS

GOLD—Ozs.	SILVER—Ozs.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
2.29	299.3	16.0			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
62.2	0.3	0.8	5.5		

CHARGE, \$ _____

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH, Aug. 21, 1926

NAME West End Con.

LOT No. 63

SAMPLED BY UOS

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.03	181.0	7.7			
1.03	181.4	7.7			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
53.2	4.7	10.6	9.4		
52.2	5.0	10.4	9.3		

CHARGE, \$ 5

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH, Aug. 21, 1926

NAME **West End Con.**

LOT No. **63**

SAMPLED BY **UOS**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.03	181.4	7.7			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
52.2	5.0	10.4	9.3		

CHARGE, \$ **5**

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH, Nov. 29, 1926.

NAME **West End Con.**

LOT NO. **65**

SAMPLED BY **UOS**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.80	163.0	12.3			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
67.8	0.3	0.2	6.1		

CHARGE, \$ _____

Black & Deason ASSAYERS

C. C. CRISMON,
President and Manager,

F. J. NICHOLS
Vice-President

R. R. CASTO,
Secretary-Treasurer

CRISMON & NICHOLS

ASSAYERS AND CHEMISTS

229-231 SO. WEST TEMPLE ST.

Phone Was. 2393

Salt Lake City, Utah, Oct. 22, 1926

NAME West End

WEIGHT

CLASS LOT NO. 64-Orig.

SAMPLED BY Utah Ore Sampling Co.

UMPIRE ASSAY PER TON 2000 POUNDS

GOLD-Ozs.	SILVER-Ozs.	LEAD-Per cent Wet on Fire	COPPER-Per cent
	300.00		
Gold not deducted			
Per cent			
SOLUBLE INSOL.	IRON-Per cent	ZINC-Per cent	SULPHUR-Per cent
63.4			
SPEISS-Per cent	LIME-Per cent	MANGANESE Per cent	Per cent

CHARGES \$ 6.00

Ernest Nichols

C. C. CRISMON,
President and Manager

F. J. NICHOLS,
Vice-President

R. R. CASTO,
Secretary-Treasurer

CRISMON & NICHOLS

ASSAYERS AND CHEMISTS

229-231 SO. WEST TEMPLE ST.

Phone Was, 2393

Salt Lake City, Utah, Oct. 22, 1926

NAME West End

WEIGHT

CLASS LOT NO. 64-Orig.

SAMPLED BY Utah Ore Sampling Co.

UMPIRE ASSAY PER TON 2000 POUNDS

GOLD-Ozs.	SILVER-Ozs.	LEAD-Per cent Wet on Fire	COPPER-Per cent
	300.00		
Gold not deducted			
Per cent 5.00 INSOL.	IRON-Per cent	ZINC-Per cent	SULPHUR-Per cent
63.4			
SPEISS-Per cent	LIME-Per cent	MANGANESE Per cent	Per cent

CHARGES \$ 6.00

Crison & Nichols

WEIGHT AND MOISTURE CERTIFICATE

Lot No. 64

SHIPPER West End Con

SAMPLED BY Utah Ore Co

Oct 21, 1926

RECEIVED	SAMPLED	FROM CARS		LOADED IN CARS		MOISTURE	GROSS WEIGHT			TARE			NET WEIGHT		
		INITIALS	NUMBERS	INITIALS	NUMBERS										
10/19	10/20	SP	86241	UP	63569				120920			46540			74380

CARS AND CONTENTS O. K. WHEN RECEIVED UNLESS NOTED OTHERWISE

SACKS		
NO	WEIGHT	CONDITION

Weather Fair

Remarks:

Old Sampled

TOTAL NET WEIGHT

MOISTURE 24.5 PER CENT

TOTAL NET DRY WEIGHT

1822

72558

Bradford

Sampler Lot 3312

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 63 West End Con Mng Co.

Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63752	134640	46380	88260	H&TC 36692	
Received Aug 19, sampled Aug 20, 1926					

Total Wet Weight lbs.
 _____ Sacks _____ lbs.

Sampling 39.72


Net Weight of Ore, 88260 lbs.

Moisture 3.45 % 3044 lbs.

Dry Weight of Ore, 85216 lbs.

Salt Lake City, Utah August 20, 1926

UTAH ORE SAMPLING COMPANY

Per 

Sampler Lot 3312

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 63 West End Con Mng Co.

Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63752	154640	46380	88260	H&TC 36692	
Received Aug 19, sampled Aug 20, 1926					

Total Wet Weight lbs.
 _____ Sacks lbs.

Sampling 39.72

Net Weight of Ore, 88260 lbs.

Moisture 3.45 % 3044 lbs.

Dry Weight of Ore, 85216 lbs.

Salt Lake City, Utah August 20, 1926

UTAH ORE SAMPLING COMPANY

Per *M*

WM. A. BLACK, PRESIDENT

N. C. BLACK, VICE-PRESIDENT

B. W. DEASON, SEC'Y AND TREAS.

BLACK & DEASON

ASSAYERS AND CHEMISTS

165 SOUTH WEST TEMPLE STREET

SALT LAKE CITY, UTAH, Dec. 1st, 1926

West End Con. Mining Co.
Mr. O. Falk,
Tonopah, Nevada.

Dear Sir:-

The splits we made on this lot on silver and insoluble were a trifle too wide except that the grade was pretty high and we hardly thought we could make much by fighting particularly as we have not noticed any of the umpires getting quite as high on the West End as we do when ever we have umpired the silver. Trusting that this will meet your approval, we remain,

Very truly yours,

Black & Deason

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

#732

Salt Lake City, Utah, August 27, 1926.

Pay West End Cons. Mng. Co.

Ore Mabel Mine Lot No. 63 Class
 Sampled by UOS Received 8-19 Sampled 8-20 Assayed 8-21
 Metal Quotations—Silver .62 Copper, N. Y. Lead, N. Y. 8.90 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.03 ✓	181.0 ✓		6.45	53.2 ✓	9.4 ✓	4.7 ✓	10.6 ✓		
	1.03 ✓	181.4 ✓		6.45	52.2 ✓	9.3 ✓	5.0 ✓	10.4 ✓		
Umpire										
Settlement Assay	1.03 ✓	181.2 ✓		6.45	52.7 ✓	9.35 ✓	4.85 ✓	10.5 ✓		

CAR NOS.	WET WEIGHT	METAL VALUE		WORKING CHARGE	
H&TC 36692		Gold	19 57 ✓	Treatment	5 36 ✓
		Silver	106 73 ✓	Insoluble	5 27 ✓
		Copper		Zinc	
		Lead	8 42 ✓	Sulphur	2 13 ✓
				Speiss	
Total Wet Weight					
Sacks				Total Debit	12 76 ✓
Net Weight	88260 ✓	Gross Value	134 72 ✓	Iron	56 ✓
Less H ₂ O 3.45 %	3044 ✓	Less Working Charge	12 20 ✓	Net Working Charge	12 20 ✓

Dry Weight, lbs. 85216 ✓ Payment for 42.608 tons @ 122 52 per ton 5220 33 ✓

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 11.90 per ton 525.15 ✓
 Assay Charges 5.00 ✓
 Sampling Charges watching 5.00 ✓
 535 15 ✓

Checked by

Approved by

Net Payment

4685 18 ✓

THIS SIDE OF CARD IS FOR ADDRESS



West End Con My Co
Jonapan
Nes

West End Cow M^o

Mina 11/20

Ap 24629 to Midvale ut

11/20/76 Gross 131780

Inre 40700

Net

91080

C. B. Battin
Agent

Lot No. 63

Lot No. 63

SHIPPER

West End Co

SAMPLED BY

Utah Ore Lb.

1926

CARS AND CONTENTS O. K. WHEN RECEIVED UNLESS NOTED OTHERWISE

SACKS

NO

WEIGHT

CONDITION

TOTAL NET WEIGHT

MOISTURE..... PER CENT

TOTAL NET DRY WEIGHT

Weather

Remarks:

O and A sample

3044
85216

Bradford

UTAH ORE SAMPLING COMPANY

WEIGHT AND MOISTURE CERTIFICATE

Shipper **West End Con Mining Co.**

Lot No. **64**

Class

INTO CAR	GROSS	TARE	NET	FROM CAR
UP 63569	120920	46540	74380	SP 86241
	Received Oct. 17, sampled Oct. 19, 1926			

Total Wet Weight lbs.

Sampling 33.47

Sacks lbs.

Net Weight of Ore, 74380 lbs.

Moisture 2.45 % 1822 lbs.

Dry Weight of Ore, 72558 lbs.

Salt Lake City, Utah October 20, 1926

UTAH ORE SAMPLING COMPANY

Per 

UTAH ORE SAMPLING COMPANY

WEIGHT AND MOISTURE CERTIFICATE

Shipper **West End Con Mining Co.**

Lot No. **64**

Class

INTO CAR	GROSS	TARE	NET	FROM CAR
UP 63569	120920	46540	74380	SP 86241
	Received Oct. 17, sampled Oct. 19, 1926			

Total Wet Weight

lbs.

Sampling
Assaying

33.47

Sacks

lbs.

Net Weight of Ore,

74380

lbs.

Moisture **2.45** %

1822

lbs.

Dry Weight of Ore,

72558

lbs.

Salt Lake City, Utah

October 20, 1926

UTAH ORE SAMPLING COMPANY

Per

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

732

Salt Lake City, Utah, October 26, 1926.

Pay West End Con. Mining Co.

Tonopah, Nev.

Ore Mabel Mine Lot No. 64 Class
 Sampled by UOS Received 10-17 Sampled 10-19 Assayed 10-21
 Metal Quotations—Silver .54125 Copper, N. Y. Lead, N. Y. 8.47 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	2.27	294.9		14.45	64.8	6.2	.6	1.4		
	2.29	299.3		14.75	62.2	5.5	.3	.8		
C&M Umpire		297.72 ✓			63.4 ✓					
Settlement Assay	2.28 ✓	297.72 ✓		14.6 ✓	63.4 ✓	5.85	.45	1.1		

CAR NOS.	WET WEIGHT	METAL VALUE	WORKING CHARGE
SP 86241		Gold 43.32 ✓	Treatment 4 54 ✓
		Silver 153.08 ✓	Insoluble 6 34 ✓
		Copper	Zinc
		Lead 18 92 ✓	Sulphur
			Speiss
Total Wet Weight			
Sacks			
Net Weight 74380 ✓		Gross Value 214.32 ✓	Total Debit 10 88
Less H ₂ O 2.45% 1822 ✓		Less Working Charge 10.53 ✓	Iron 35 ✓
			Net Working Charge 10 53 ✓

Dry Weight, lbs. 72558 ✓ Payment for 36.279 tons @ 203.79 ✓ per ton 7393.30 ✓

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 11.90 per ton 476.00 ✓

Assay Charges 5.00 ✓

Sampling Charges watching 5.00 ✓

486.00 ✓

Checked by MFC

Approved by

Net Payment

6907.50 ✓

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

732

Salt Lake City, Utah, October 26, 1926.

Pay West End Con. Mining Co.

Tonopah, Nev.

Ore Mabel Mine Lot No. 64 Class
 Sampled by UOS Received 10-17 Sampled 10-19 Assayed 10-21
 Metal Quotations—Silver .54125 Copper, N. Y. Lead, N. Y. 8.47 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	2.27	294.9		14.45	64.8	6.2	.6	1.4		
	2.29	293.3		14.75	62.2	5.5	.3	.8		
C&M Umpire		297.72			63.4					
Settlement Assay	2.28	297.72		14.6	63.4	5.85	.45	1.1		

CAR NOS.	WET WEIGHT	METAL VALUE		WORKING CHARGE	
SP 86241		Gold	43.32	Treatment	4 54
		Silver	153.08	Insoluble	6 34
		Copper		Zinc	
		Lead	10 92	Sulphur	
				Speiss	
Total Wet Weight					
Sacks				Total Debit	10 88
Net Weight	74380	Gross Value	214.32	Iron	35
Less H ₂ O 2.45%	1822	Less Working Charge	10.53	Net Working Charge	10 53

Dry Weight, lbs. 72558 Payment for 36.279 tons @ 203.79 per ton 7393.30

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 11.90 per ton 476.00

Assay Charges 5.00

Sampling Charges watching 5.00 486.00

Checked by

Approved by

Net Payment

6907.30

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

733

Salt Lake City, Utah, October 26, 1926.

Pay West End Con. Mining Co. Tons sh. Nov.

Ore Mahol Mine Lot No. 64 Class
 Sampled by URS Received 10-17 Sampled 10-19 Assayed 10-21
 Metal Quotations—Silver .64125 Copper, N. Y. Lead, N. Y. 5.47 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	2.27	294.9		14.45	64.8	6.2	.6	1.4		
U. S. S. Co.	2.29	293.3		14.75	62.2	5.5	.3	.8		
U. S. S. Co. Umpire		297.72								
Settlement Assay	2.28	297.72		14.6	63.4	5.85	.45	1.1		

CAR NOS.	WET WEIGHT	METAL VALUE		WORKING CHARGE	
SP 86243		Gold	43.32	Treatment	4 54
		Silver	155.08	Insoluble	6 34
		Copper		Zinc	
		Lead	17 92	Sulphur	
				Speiss	
Total Wet Weight					
Sacks					
Net Weight	74380	Gross Value	214.32	Total Debit	10 88
Less H ₂ O 2.45%	13.2	Less Working Charge	10.53	Iron	35
				Net Working Charge	10 53

Dry Weight, lbs. 72558 Payment for 36,279 tons @ 203 79 per ton 7392.30

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 11.50 per ton 476.00
 Assay Charges 5.00
 Sampling Charges 420.00

Checked by

Approved by

Net Payment

6907.30

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, October 26, 1926.

Pay West End Con. Mining Co. Tonoali, Nev.

Ore. Label Fine Lot No. 44 Class.

Sampled by. 603 Received 10-17 Sampled 10-19 Assayed 10-21

Metal Quotations—Silver .54125 Copper, N. Y. Lead, N. Y. 8.47 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	7.37	294.9		14.45	54.8	6.2	.6	1.4		
U. S. S. Co.	7.29	294.3		14.75	52.2	5.5	.3	.8		
U. S. S. Co. Umpire	7.27	297.72								
Settlement Assay	7.27	297.72		14.6	53.4	6.05	.45	1.1		

CAR NOS.	WET WEIGHT	METAL VALUE	WORKING CHARGE
86241		Gold 43.32	Treatment 4.54
		Silver 150.00	Insoluble 4.54
		Copper	Zinc
		Lead 17.92	Sulphur
			Speiss
Total Wet Weight			
Sacks			
Net Weight 74390		Gross Value 814.32	Total Debit 10.58
Less H ₂ O 2.45% 1822		Less Working Charge 10.53	Iron 35
			Net Working Charge 10.53

Dry Weight, lbs. 72558 Payment for 35.278 tons @ 203.77 per ton 7322.30

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 11.00 per ton 476.00

Assay Charges 5.00

Sampling Charges 486.00

Checked by

Approved by

Net Payment

6807.30

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

732

Salt Lake City, Utah, October 26, 1925.

Pay West End Cons. Mining Co. Pay No. 184.Ore Model Mine Lot No. 64 Class Sampled by 638 Received 10-17 Sampled 10-19 Assayed 10-21Metal Quotations—Silver 84.25 Copper, N. Y. Lead, N. Y. 8.47 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	2.27	294.9		14.45	64.8	6.2	.6	1.4		
Umpire	2.29	290.9		14.75	62.3	5.8	.8	.8		
Settlement Assay	2.25	297.71		14.6	63.4	5.85	.45	1.2		

CAR NOS.	WET WEIGHT	METAL VALUE	WORKING CHARGE
66241		Gold	Treatment
		Silver	Insoluble
		Copper	Zinc
		Lead	Sulphur
			Speiss
Total Wet Weight			Total Debit
Sacks			
Net Weight	74380	Gross Value	Iron
Less H ₂ O 8.41%	1822	Less Working Charge	Net Working Charge

Dry Weight, lbs. 72558

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Payment for 36.275 tons @ 205.73 per ton 7452.30

Freight advanced @ 11.00 per ton 476.03

Assay Charges 5.00

Sampling Charges 499.00

Checked by

Approved by

Net Payment

6907.30

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH,

July 12, 1926

NAME **West End Con.**

LOT No. **62**

SAMPLED BY **UOS**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.06 1.07	140.5 140.2	8.7 8.8			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
43.6 42.6	6.5 6.1	15.9 16.0	12.2 12.7		

CHARGE, \$ **5**

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH,

July 12, 1926

NAME **West End Con.**

LOT NO. **62**

SAMPLED BY

UOS

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.07	140.2	8.8			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
42.6	6.1	16.0	12.7		

CHARGE, \$ **5**

Black & Deason ASSAYERS

Sampler Lot 2968

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 62 West End Con Mng. Co.

Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62140	136280	46880	89400	SP 34579	
Received July 8, Sampled July 10, 1926					

Total Wet Weight lbs.

Sampling 40.23

Sacks lbs.


Net Weight of Ore, 89400 lbs.

Moisture 2.2 % 1966 lbs.

Dry Weight of Ore, 87434 lbs.

Salt Lake City, Utah July 12, 1926

UTAH ORE SAMPLING COMPANY

Per 

Sampler Lot 2968

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 62 West End Con Mng. Co.

Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62140	136280	46880	89400	SP 34579	
Received July 8, Sampled July 10, 1926					

Total Wet Weight lbs.

Sampling 40.23

Sacks lbs.


Net Weight of Ore, 89400 lbs.

Moisture 2.2 % 1966 lbs.

Dry Weight of Ore, 87434 lbs.

Salt Lake City, Utah July 12, 1926

UTAH ORE SAMPLING COMPANY

Per 

DAILY ASSAY REPORT

192

[illegible]

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR. GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

July 7 1926

Mr. Otto Falk, Chief Clerk
West End Cons. Mng. Co.
Tonopah, Nevada

Dear Sir:

Very pleased to receive your letter of July 3rd notifying us of the shipment of Lot 62 from the Mable .

It will be handled in accordance with your instructions.
Thanking you for the shipment and with kind personal regards, I remain

Yours very truly,

MWW:A

M. W. Woolley

DAILY ASSAY REPORT

June 25-28

192

MABEK ORE CONTROL

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		
61/2764	6-15-26	.94		117.46			Pb 2.1%

JPM
ASSAYER

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

#732

Salt Lake City, Utah, July 15, 1926.

Pay West End Cons. Mng. Co.

Ore Lot No. 62 Class
 Sampled by Received 7-8-26 Sampled 7-10-26 Assayed 7-12-26
 Metal Quotations—Silver .65125 Copper, N. Y. Lead, N. Y. 8.255 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.06	140.5		7.45	43.6	12.2	6.5	15.9		
	1.07	140.2		7.55	42.6	12.7	6.1	16.0		
Umpire										
Settlement Assay	1.065	140.35		7.5	43.1	12.45	6.3	15.95		

CAR NOS.	WET WEIGHT	METAL VALUE		WORKING CHARGE	
S.P. 34579		Gold	20 24	Treatment	5 25
		Silver	86 83	Insoluble	4 31
		Copper		Zinc	.39
		Lead	8 92	Sulphur	2 50
				Speiss	
Total Wet Weight					
Sacks				Total Debit	12 45
Net Weight	89400	Gross Value	115 99	Iron	75
Less H ₂ O .2 %	1966	Less Working Charge	11 70	Net Working Charge	11 70

Dry Weight, lbs. 87434 Payment for 43.717 tons @ 104 29 per ton 4559 25

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 11.90 per ton 531.93
 Assay Charges 5.00
 Sampling Charges Watching 5.00 541 93

Checked by

Approved by

Net Payment

4017 32

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

#732

Salt Lake City, Utah, July 15, 1926.

Pay West End Cons. Mng. Co.

Ore Lot No. 62 Class Assayed 7-12-26
 Sampled by Received 7-8-26 Sampled 7-10-26
 Metal Quotations—Silver .65125 Copper, N. Y. Lead, N. Y. 8.255 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.06	140.5		7.45	43.6	12.2	6.5	15.9		
	1.07	140.2		7.55	42.6	12.7	6.1	16.0		
Umpire										
Settlement Assay	1.065	140.35		7.5	43.1	12.45	6.3	15.95		

CAR NOS.	WET WEIGHT	METAL VALUE		WORKING CHARGE	
S.P. 34579		Gold	20 24	Treatment	5 25
		Silver	86 83	Insoluble	4 31
		Copper		Zinc	.39
		Lead	8 92	Sulphur	2 50
				Speiss	
Total Wet Weight				Total Debit	12 45
Sacks				Iron	75
Net Weight	89400	Gross Value	115 99	Net Working Charge	11 70
Less H ₂ O.2 %	1966	Less Working Charge	11 70		

Dry Weight, lbs. 87434 Payment for 43.717 tons @ 104 29 per ton 4559 25

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 11.99 per ton

531.93

Assay Charges

5.00

Sampling Charges Watching

5.00

541 93

Checked by

Approved by

Net Payment

4017 32

WEIGHT AND MOISTURE CERTIFICATE

Lot No. 62 Cr

July 12, 1926

SHIPPER West-End Corp

SAMPLED BY Wahneema Lubiano Co

[illegible]

Cars and Contents O. K. When Received Unless Noted Otherwise

No.	SACKS Weight	Condition
-----	-----------------	-----------

--	--	--

Total Net Weight

Moisture 22..... Per CentPer Cent 1766

Total Net Dry Weight

Weather Stormy

Remarks:

J. Stauffer

Sampler Lot 2764

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 61 West End Con. Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63310	141900	46340	95560	T&NO 38787	
Received June 13, Sampled June 15, 1926					

Total Wet Weight lbs.
 _____ Sacks lbs.

Sampling 43.00


Net Weight of Ore, 95560 lbs.

Moisture 2.95 % 2820 lbs.

Dry Weight of Ore, 92740 lbs.

Salt Lake City, Utah June 16, 1926

UTAH ORE SAMPLING COMPANY

Per 

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR. GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

June 14, 1926 .

West End Consolidated Mining Co.

Tonopah, Nevada

Gentlemen:

We are in receipt of your letter of June 10th notifying us of the shipment of Lot 61 from the Mable Mine.

Thanking you for the shipment, we remain

Yours very truly,

M. W. Woolley

MWW:A

Sampler Lot 2764

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 61 West End Con. Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63310	141900	46340	95560	T&NO 38787	
Received June 13, Sampled June 15, 1926					

Total Wet Weight lbs.
 _____ Sacks _____ lbs.

Sampling 43.00

Net Weight of Ore, 95560 lbs.

Moisture 2.95 % 2820 lbs.

Dry Weight of Ore, 92740 lbs.

Salt Lake City, Utah June 16, 1926

UTAH ORE SAMPLING COMPANY

Per _____

WEST END CONSOLIDATED MINING COMPANY

DAILY ASSAY REPORT

TONOPAH, NEVADA, June 25-26 1926

MABEK ORE CONTROL

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		

61/2764 6-15-26

.94

117.46

Pb 2.1%

ASSAYER

JPM

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR., GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

May 15th, 1926.

West End Consolidated Mining Co.,

Tonopah, Nevada.

Dear Sirs:-

We have your letter of the 12th and note that Lot 60 from the Mabel was shipped on May 11th, in car 26291. We will be pleased to handle according to your instructions.

We enclose you herewith two extra copies of settlement sheet on Lot 59.

Yours very truly,

W. H. Eardley

WHE:H

Encls.

#732

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, June 21 1926

Pay West End Consolidated Mining Co.

Ore _____ Lot No. 61 Class _____
 Sampled by UOS Received 6-13 Sampled 6-15 Assayed 6-16
 Metal Quotations—Silver .65875 Copper, N. Y. _____ Lead, N. Y. 7.653 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	.94	118.4		6.35	45.0	13.5	6.0	17.1		
	.96	118.8		6.65 13 0 0	44.0	13.4	5.8	16.7		
Umpire										
Settlement Assay	✓ .95	118.6 ✓		6.50	44.5	13.45	5.9	16.9		

CAR NOS.	WET WEIGHT	METAL VALUES		WORKING CHARGE	
T&NO 38787		Gold	18 05	Treatment	5 35 ✓
		Silver	74 22	Insoluble	4 45 ✓
		Copper		Zinc	27 ✓
		Lead	7 03	Sulphur	2 50 ✓
				Speiss	
Total Wet Weight					
Sacks				Total Debit	12 57
Net Weight <u>95560</u> ✓		Gross Value	99 30	Iron	81 ✓
Less H ₂ O <u>2.95</u> % <u>2820</u> ✓		Less Working Charge	11 76	Net Working Charge	11 76

Dry Weight, lbs. <u>92740</u> ✓	Payment for <u>46.37</u> tons @ <u>87 54</u> ✓ per ton	<u>4059 23</u> ✓
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.	Freight advanced @ <u>8.50</u> per ton	<u>406.13</u> ✓
	Assay Charges	<u>5.00</u> ✓
	Sampling Charges <u>Watching</u>	<u>5.00</u> ✓ <u>416 13</u> ✓

Checked by _____	Net Payment	<u>3643 10</u> ✓
Approved by _____		

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, June 21 1926

Pay West End Consolidated Mining Co.

Ore _____ Lot No. 61 Class _____
 Sampled by UOS Received 6-13 Sampled 6-15 Assayed 6-16
 Metal Quotations—Silver .65875 Copper, N. Y. _____ Lead, N. Y. 7.658 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	.94	118.4		6.35	45.0	13.5	6.0	17.1		
	.96	118.8		6.65	44.0	13.4	5.8	16.7		
Umpire										
Settlement Assay	.95	118.6		6.56	44.5	13.45	5.9	16.9		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE	
T&NO 38787		Gold	18	05		Treatment	5 35
		Silver	74	22		Insoluble	4 45
		Copper				Zinc	27
		Lead	7	03		Sulphur	2 50
						Speiss	
Total Wet Weight							
Sacks						Total Debit	12 57
Net Weight 95560		Gross Value	99	30		Iron	81
Less H ₂ O 2.95 % 2820		Less Working Charge	11	76		Net Working Charge	11 76

Dry Weight, lbs. 92740 Payment for 46.37 tons @ 87 54 per ton 4059 23

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 8.50 per ton

406.13

Assay Charges

5.00

Sampling Charges

Watching

5.00

416 13

Checked by

Approved by

Net Payment

3643 10

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH,

June 16, 1926

NAME **West End Con.**

LOT NO. **61**

SAMPLED BY

UOS

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
0.96	118.8	7.9			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
44.0	5.8	16.7	13.4		

CHARGE, \$ _____

Black & Deason

ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH, June 16, 1926

NAME West End Con.

LOT NO. 61

SAMPLED BY

UOS

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
<u>0.94</u> 0.96	<u>118.4</u> 118.8	<u>7.6</u> 7.9			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
<u>45.0</u> 44.0	<u>6.0</u> 5.8	<u>17.1</u> 16.7	<u>13.5</u> 13.4		

CHARGE, \$ _____

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH.

June 16, 1926

NAME **West End Con.**

LOT NO. **61**

SAMPLED BY

UOS

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
0.96	118.8	7.9			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
44.0	5.8	16.7	13.4		

CHARGE. \$ _____

Black & Deason ASSAYERS

WEIGHT AND MOISTURE CERTIFICATE

Lot No. 61

1926

SHIPPER West End Co

SAMPLED BY Utah Ore S Co

Received	Sampled	FROM CARS		LOADED IN CARS		Moisture	Gross Weight			Tare	Net Weight		
		Initials	Numbers	Initials	Numbers								
6/15	6/16	JNO	38787	UP	63310				141900		46340		95560

Sampler Lot 2525

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 60 West End Cons. Mng Co. Ore Mabel Mine

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62429	161120	46660	114460	SP 26291	
Received May 15, sampled May 17, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 114460 lbs.


Moisture 1.75 % 2004 lbs.

Dry Weight of Ore, 112456 lbs.

Salt Lake City, Utah May 18, 1926

Sampling 51.51

UTAH ORE SAMPLING COMPANY

Per 

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH, May 18th, 1926

NAME **West End Con.**

LOT NO. **60**

SAMPLED BY **UOS**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
0.95	113.6	8.9			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
40.4	8.0	Roast	12.6		

CHARGE, \$ _____

Black & Deason ASSAYERS

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, May 21, 1926

Pay Vent and Cons, Hbg. Co.

Ore **Mabel** Lot No. **60** Class
 Sampled by **UOS** Received **5-15-26** Sampled **5-17-26** Assayed **5-19-26**
 Metal Quotations—Silver **.65** Copper, N. Y. Lead, N. Y. **7.817** Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	.95	114.0		7.25	40.4	11.8	8.6	19.2		
	.95	113.6		7.65	40.4	12.6	8.6	R		
Umpire										
Settlement Assay	.95	113.8		7.45	40.4	12.2	8.2	19.2		

CAR NOS.	WET WEIGHT	METAL VALUES			WORKING CHARGE	
S.P. 25291		Gold	18	05	Treatment	5 26
		Silver	70	27	Insoluble	4 04
		Copper			Zinc	99
		Lead	8	27	Sulphur	2 50
					Speiss	
Total Wet Weight						
Sacks					Total Debit	12 79
Net Weight	114460	Gross Value	96	59	Iron	73
Less H ₂ O 1.75%	2004	Less Working Charge	12	06	Net Working Charge	12 06

Dry Weight, lbs.	112456	Payment for	56.228	tons @	84 53	per ton	4752 95
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.	Freight advanced @ 8.50 per ton						486.40
	Assay Charges						5.00
	Sampling Charges watching						5.00
							496 46
Checked by							
Approved by	Net Payment						4256 49

UNITED STATES SMELTING, REFINING & MORGAN COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, May 21, 1936

#732

Pay West End Cons, Mfg. Co.

Ore Mabel Lot No. 60 Class
 Sampled by UOS Received 5-15-26 Sampled 5-17-26 Assayed 5-19-26
 Metal Quotations—Silver .65 Copper, N. Y. Lead, N. Y. 7.817 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	.95 /	114.0 /		7.25 /	40.4 /	11.8 /	8.6 /	19.2 /		
	.95 /	113.6 /		7.65 /	40.4 /	12.6 /	8.0 /	R /		
Umpire										
Settlement Assay	.95 /	113.8 /		7.45 /	40.4 /	12.2 /	8.3 /	19.2 /		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE			
S.P. 26291		Gold	18	05 /		Treatment	5	26 /	
		Silver	70	27 /		Insoluble	4	04 /	
		Copper				Zinc		99 /	
		Lead	8	27 /		Sulphur	2	50 /	
						Speiss			
Total Wet Weight									
Sacks						Total Debit	12	79 /	
Net Weight	114460	Gross Value	96	59 /		Iron		73 /	
Less H ₂ O 1.75%	2004	Less Working Charge	12	06 /		Net Working Charge	12	06 /	

Dry Weight, lbs.	112456	Payment for	56.228	tons @	84	53 /	per ton	4752	95 /
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.		Freight advanced @	8.50	per ton		486.46	/		
		Assay Charges				5.00	/		
		Sampling Charges	watching			5.00	/	496	46 /
Checked by									
Approved by		Net Payment						4256	49 /

DAILY ASSAY REPORT

MABEK ORE CONTROL

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		
60/2525	5-18-26	.90		109.85			Pb 1.1%
							J.P.M. JPM ASSAYER

WEST END CONSOLIDATED MINING COMPANY

DAILY ASSAY REPORT

WABE ORE CONTROL

TONOPAH, NEVADA, May 31-26 192

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		

60/2525

5-18-26

.90

109.85

Pb 1.1%

J.P.M.
JPM

ASSAYER

Sampler Lot 2525

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 60 West End Cons. Mng Co. Ore Mabel Mine

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62429	161120	46660	114460	SP 26291	
Received May 15, sampled May 17, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 114460 lbs.


Sampling 51.51

Moisture 1.75 % 2004 lbs.

Dry Weight of Ore, 112456 lbs.

Salt Lake City, Utah May 18, 1926

UTAH ORE SAMPLING COMPANY

Per 

TELEPHONE WASATCH 1199

Con. Serial 78751-

ASSAY CERTIFICATE

UMPIRE ASSAY

UNION ASSAY OFFICE, INC.

Mine West End

M. S. HANAUER, Pres.
J. V. SADLER, V.-Pres. & Tres.
A. C. SELBY, Secretary

Salt Lake City, Utah

RESULTS PER TON OF 2000 POUNDS

April 30, 1926

LOT	CLASS	GOLD Ozs. per Ton	SILVER Ozs. per Ton	LEAD Wet on Ore	COPPER Per Cent. Wet	INSOL. Per Cent.	ZINC Per Cent.	SULPHUR Per Cent.	SPEISS Per Cent.	IRON Per Cent.	LIME Per Cent.	Per Cent.
59-		Gold deducted	92.3									

Remarks

Sampled By UOSCo.

Charges \$ 3.00

M. S. Hanauer

WEIGHT AND MOISTURE CERTIFICATE

Lot No. 59

No. 29
SHIPPER West End Con

APRIL 27, 1926
SAMPLED BY Utah Ore SB

[illegible]

Cars and Contents O. K. When Received Unless Noted Otherwise

No.	SACKS Weight	Condition
-----	-----------------	-----------

Total Net Weight

Moisture 2 Per Cent 26.58

Total Net Dry Weight

Weather Fair

Remarks:

O and S Sample

Bradford

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

PHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH. April 27, 1926

NAME West End Con.

LOT NO. 59

SAMPLED BY U.O.S.

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.01 1.03	92.0 93.2	6.7 6.8			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
42.4 42.4	7.4 7.0	19.1 19.1	14.8 14.2		

CHARGE, \$ 5

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

PHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH. April 27, 1926

NAME West End Con.

LOT No. 59

SAMPLED BY U.O.S.

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.03	93.2	6.8			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
42.4	7.0	19.1	14.2		

CHARGE, \$ 5

Black & Deason ASSAYERS

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR., GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

April 22nd, 1926.

West End Consolidated Mining Co.,
Tonopah, Nevada.
Gentlemen:-

We beg to acknowledge receipt of your letter
of April 19th, enclosing bill of lading for Lot 59. The same
will be handled as per your request.

Yours very truly,

W. H. Eardley

WHE:H

DAILY ASSAY REPORT


TONOPAH, NEVADA, May 8-26 1926

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		
59/2393		.98		89.20			Pb Wet 3.6 %
							JPM ASSAYER

DAILY ASSAY REPORT

TONOPAH, NEVADA, April 22-26 1922

MABEL ORE CONTROL

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		
58/2355	4-9-26	1.00		112.70			Pb 4.5 %
<div style="text-align: right;">  JPM ASSAYER </div>							

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

#732

Salt Lake City, Utah, May 4, 1926.

Pay West End Cons. Mng. Co.

Ore Mabel Mine Lot No. 59 Class
 Sampled by UOS Received 4-23-26 Sampled 4-26-26 Assayed 4-28-26
 Metal Quotations—Silver Copper, N. Y. Lead, N. Y. Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.01	92.0		5.45	42.4	14.8	7.4	19.1		
	1.03	93.2		5.55	42.4	14.2	7.0	19.1		
Union Umpire		92.3								
Settlement Assay	1.02	92.3		5.5	42.4	14.5	7.2	19.1		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE			
U.P. 15327		Gold	19	38		Treatment	5	45	
		Silver	56	12		Insoluble	4	24	
		Copper				Zinc		66	
		Lead	6	18		Sulphur	2	50	
						Speiss			
Total Wet Weight									
Sacks									
Net Weight	110740	Gross Value	81	68		Total Debit	12	85	
Less H ₂ O.4 %	2658	Less Working Charge	11	98		Iron		87	
						Net Working Charge	11	98	

Dry Weight, lbs. 108082 Payment for 54.041 tons @ 69 70 per ton 3766 66

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 7.10 per ton 393.13
 Assay Charges 5.00
 Sampling Charges watching 5.00
 umpire 3.00

406 13

Checked by

Approved by

Net Payment

3360 53

Sampler Lot 2393

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 59 West End Cons Mining Co. Ore Mabel Mine

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62744	157320	46580	110740	UP 15327	
Received April 23, sampled April 26, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 110740 lbs.


Sampling 49.83

Moisture 2.4 % 2658 lbs.

Dry Weight of Ore, 108082 lbs.

UTAH ORE SAMPLING COMPANY

Salt Lake City, Utah April 26, 1926

Per 

Sampler Lot 2393

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 59 West End Cons Mining Co. Ore Mabel Mine

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62744	157320	46580	110740	UP 15327	
Received April 23, sampled April 26, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 110740 lbs.


Moisture 2.4 % 2658 lbs.

Dry Weight of Ore, 108082 lbs.

Salt Lake City, Utah April 26, 1926

Sampling 49.83

UTAH ORE SAMPLING COMPANY

Per 

TELEPHONE WASATCH 1199

UMPIRE ASSAY

Mine West End

Cor. Serial 78751-

ASSAY CERTIFICATE

UNION ASSAY OFFICE, INC.

M. S. HANAUER, Pres.
J. V. SADLER, V.-Pres. & Tres.
A. C. SELBY, Secretary

Salt Lake City, Utah

RESULTS PER TON OF 2000 POUNDS

April 30, 1926

LOT	CLASS	GOLD Ozs. per Ton	SILVER Ozs. per Ton	LEAD Wet on Ore	COPPER Per Cent. Wet	INSOL. Per Cent.	ZINC Per Cent.	SULPHUR Per Cent.	SPEISS Per Cent.	IRON Per Cent.	LIME Per Cent.	Per Cent.
59-		Gold deducted										
			92.3									

Remarks _____

Sampled By UO S Co.

Charges \$ 3.00

M. S. Hanauer

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, May 3 1926

Pay West Ind Cons. Mng. Co.

Ore Mabel Mine Lot No. 59 Class
 Sampled by UOS Received 4-23 Sampled 4-26 Assayed 4-28
 Metal Quotations—Silver .64 Copper, N. Y. Lead, N. Y. 7.096 Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.01	92.0		5.45	42.4	14.0	7.4	19.1		
	1.03	93.2		5.55	42.4	14.2	7.0	19.1		
Union Umpire		92.3								
Settlement Assay	1.02	92.3		5.5	42.4	14.5	7.2	19.1		

CAR NOS.	WET WEIGHT	METAL VALUES	WORKING CHARGE
WP 15327		Gold 19 30	Treatment 5 45
110	7896	Silver 56 12	Insoluble 4 24
99	1646	Copper 6 18	Zinc 66
	6246	Lead	Sulphur 2 50
			Speiss
Total Wet Weight			
Sacks			Total Debit 12 05
Net Weight 110740		Gross Value 91 68	Iron 87
Less H ₂ O 2.4 % 2650		Less Working Charge 11 98	Net Working Charge 11 98

Dry Weight, lbs.

108082

Payment for 54.041 tons @ 69 70 per ton

3766 66

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 7.10 per ton

393.13

Assay Charges

5.00

Sampling Charges

Watch.

5.00

Upp.

3.00

406 13

Checked by

Approved by

Net Payment

3360 53

WEST END CONSOLIDATED MINING COMPANY

DAILY ASSAY REPORT

TONOPAH, NEVADA, April 22-26 192

MAPET. ORE CONTROL.

SAMPLE
NUMBER

WORKING PLACE

GOLD

OUNCES

VALUE

SILVER

OUNCES

VALUE

TOTAL
VALUE

REMARKS

58 / 2355

4-9-26

1.00

112.70

Pb 4.5 %

JPM

ASSAYER

WEST END CONSOLIDATED MINING COMPANY

DAILY ASSAY REPORT

TONOPAH, NEVADA, April 22-26 192

~~WABEL ORE CONTROL~~

SAMPLE
NUMBER

WORKING PLACE

GOLD

OUNCES

VALUE

SILVER

OUNCES

VALUE

TOTAL
VALUE

REMARKS

58/2355

4-9-26

1.00

112.70

Pb 4.5 %

JPM

ASSAYER

Sampler Lot 2355

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 58 West End Con. Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62048	132500	46760	85740	SP 24523	
Received April 7, sampled April 9, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 85740 lbs.


Moisture 2.3 % 1972 lbs.

Dry Weight of Ore, 83768 lbs.

Salt Lake City, Utah April 9, 1926

Sampling 38.58

UTAH ORE SAMPLING COMPANY

Per 

Sampler Lot 2355

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 58 West End Con. Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62848	132500	46760	85740	SP 24523	
Received April 7, sampled April 9, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 85740 lbs.


Moisture 2.3 % 1972 lbs.

Dry Weight of Ore, 83768 lbs.

Salt Lake City, Utah April 9, 1926

Sampling 38.58

UTAH ORE SAMPLING COMPANY

Per 

WEIGHT AND MOISTURE CERTIFICATE

Lot No.

SHIPPER

West End Con

SAMPLED BY

Utah Ore A. G.

192.6

[illegible]

Cars and Contents O. K. When Received Unless Noted Otherwise

No.	SACKS Weight	Condition
-----	-----------------	-----------

Total Net Weight

Moisture _____ Per Cent _____

Total Net Dry Weight

Weather Rain

Remarks:

O and R Sample

Stauff
Bradford

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, April 13 1926

Pay West End Cons. Mng. Co.

Ore _____ Lot No. 58 Class _____
 Sampled by UOS Received 4-7 Sampled 4-9 Assayed 4-10
 Metal Quotations—Silver .65 Copper, N. Y. _____ Lead, N. Y. 8.208 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	.96 ✓	113.2 ✓		5.45 ✓	45.5 ✓	11.6 ✓	5.0 ✓	17.1 ✓		
	.95 ✓	113.6 ✓		5.95 ✓	45.2 ✓	12.5 ✓	6.0 ✓	16.9 ✓		
Umpire				11.48						
Settlement Assay	.955 ✓	113.4 ✓		5.7 ✓	45.35 ✓	12.05 ✓	5.5 ✓	17.0 ✓		

CAR NOS.	WET WEIGHT	METAL VALUES		WORKING CHARGE	
SP 24523		Gold 19.10	18 15	Treatment	5 43 ✓
		Silver 73.71	70 02	Insoluble	4 54 ✓
		Copper		Zinc	15 ✓
		Pb. 9.35	6 73	Sulphur	2 50 ✓
		107.16		Speiss	
Total Wet Weight					
Sacks				Total Debit	12 62 ✓
Net Weight 85740 ✓		Gross Value	94 90	Iron	72 ✓
Less H ₂ O 2.3 % 1972 ✓		Less Working Charge	11 90	Net Working Charge	11 90 ✓

Dry Weight, lbs. 83768 ✓ Payment for 41.884 ✓ tons @ 83 00 ✓ per ton 3476 37 ✓

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 8.50 per ton 364.40 ✓
 Assay Charges 5.00
 Sampling Charges 1 Watch. 5.00

374 40 ✓

Checked by

Approved by

Net Payment

3101 97 ✓

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, Apr 11 13 1926

Pay West End Cons. Mng. Co.

Ore UOS Lot No. 58 Class 4-9
 Sampled by UOS Received 4-7 Sampled 4-9 Assayed 4-10
 Metal Quotations—Silver .65 Copper, N. Y. 8.208 Lead, N. Y. 8.208 Zinc 4-10

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	.96	113.2		5.45	45.5	11.6	5.0	17.1		
	.95	113.6		5.95	45.2	12.5	6.0	16.9		
Umpire										
Settlement Assay	.955	113.4		5.7	45.35	12.05	5.5	17.0		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE			
SP 24523		Gold	18	15		Treatment	5	43	
		Silver	70	02		Insoluble	4	54	
		Copper				Zinc		15	
		Pb.	6	73		Sulphur	2	50	
						Speiss			
Total Wet Weight									
Sacks						Total Debit	12	62	
Net Weight	85740	Gross Value	94	90		Iron		72	
Less H ₂ O 2.3 %	1972	Less Working Charge	11	90		Net Working Charge	11	90	

Dry Weight, lbs. 85768 Payment for 41.884 tons @ 83 00 per ton 3476 37

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 8.50 per ton 364.40
 Assay Charges 5.00
 Sampling Charges 2 Watch. 5.00 374 40

Checked by

Approved by

Net Payment

3101 97

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR., GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

April 5, 1926

West End Cons. Mng. Co.

Tonopah, Nevada

Gentlemen:

We note from your letter of April 2nd that you are forwarding Lot #58 from the Mabel Mine.

We will be glad to comply with your instructions relative to handling of the shipment and thanking you for same, remain

Yours very truly,

M. W. Woolley

MWW:A

DAILY ASSAY REPORT

TONOPAH, NEVADA, March 12-26 1926

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		
56/2195	2 -23-26	.94		113.80			PB 3.9 %
							J.P.M. JPM ASSAYER

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTSNAME West End Con.SALT LAKE CITY, UTAH April 10th, 1926LOT NO. 58SAMPLED BY U.O.S.

ASSAY PER TON OF 2,000 POUNDS

GOLD—Ozs.	SILVER—Ozs.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
<u>0.96</u> 0.95	<u>113.2</u> 113.6	<u>6.7</u> 7.2			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
<u>45.5</u> 45.2	<u>5.0</u> 6.0	<u>17.1</u> 16.9	<u>11.6</u> 12.5		

CHARGE, \$ 5Black & Deason ASSAYERS

Lot No. 56

Lot No. 36

SAMPLED BY

Utah Ore & Co.

SHIPPER

West End Con

1926

[illegible]

Cars and Contents O. K. When Received Unless Noted Otherwise

SACKS

No.

Weight

Condition

Total Net Dry Weight

Moisture

Per Cent

Total Net Weight

Weather

Remarks :

S. J. Stauffer

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR., GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

February 20th, 1926.

West End Consolidated Mining Co.,
Tonopah, Nevada.

Dear Sirs:-

We beg to acknowledge receipt of your letter of
February 17th, enclosing bill of lading for a car of Mabel
ore. The same will be handled as per your instructions.

Yours very truly,

W. H. Eardley

WHE:H

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH.

Feb. 26, 1926

NAME **West End Con**

LOT NO. **56**

SAMPLED BY **Utah Ore**

re

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
	113.4				
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%

CHARGE, \$ _____

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH. Feb. 26, 1926

NAME **West End Con**

LOT NO. **56**

SAMPLED BY **Utah Ore**

re ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
	113.0 113.4				
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%

CHARGE, \$ _____

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH,

Feb. 23, 1926

NAME **West End**

LOT No. **56**

SAMPLED BY **Utah Ore**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.00	112.7	7.2			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
54.6	5.2	12.1	10.3		

CHARGE, \$ _____

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH.

Feb. 23, 1926

NAME **West End**

LOT NO. **56**

SAMPLED BY **Utah Ore**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
0.99 1.00	114.2 112.7	6.7 7.2			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
54.6 54.6	6.0 5.2	12.1 12.1	9.5 10.3		

CHARGE, \$ _____

Black & Deason ASSAYERS

Lot No.

Lot No. 37

SAMPLED BY

SHIPPER

1926

Remarks:

Moisture 17.5 Per Cent 19.10

Total Net Weight 107270

Weather

Remarks:

Total Net Dry Weight

Moisture 12 Per Cent


Total Net Weight

Weather

Remarks:

DAILY ASSAY REPORT

MABEL ORE CONTROL

SAMPLE NUMBER	WORKING PLACE	GOLD		SILVER		TOTAL VALUE	REMARKS
		OUNCES	VALUE	OUNCES	VALUE		
57/2303	3-25-26	1.00		105.80			Pb 1.3 %
<div style="text-align: right;">  JPM ASSAYER </div>							

Sampler Lot 2195

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 56 West End Cons. Mng Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63392	138660	46400	92260	UP 13866	
Received Feb. 21, sampled Feb. 22, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 92260 lbs.


Moisture 2.15 % 1984 lbs.

Dry Weight of Ore, 90276 lbs.

Salt Lake City, Utah Feb. 23, 1926

Sampling 41.52

UTAH ORE SAMPLING COMPANY

Per 

Sampler Lot 2195

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 56 West End Cons. Mng Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63392	138660	46400	92260	UP 13866	
Received Feb. 21, sampled Feb. 22, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 92260 lbs.


Moisture 2.15 % 1984 lbs.

Dry Weight of Ore, 90276 lbs.

Salt Lake City, Utah Feb. 23, 1926

Sampling 41.52

UTAH ORE SAMPLING COMPANY

Per 

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, March 1st 1926

Pay West End Cons. Mng. Co.

Ore _____ Lot No. 56 Class _____
 Sampled by UOS Received 2-21 Sampled 2-22 Assayed 2-24
 Metal Quotations—Silver .665 Copper, N. Y. _____ Lead, N. Y. 9.138 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	.99	113.0	.5	5.45	54.6	9.5	6.0	12.1		
	.100	113.4		4.95	54.6	10.3	5.2	12.1		
Umpire										
Settlement Assay	.995	113.2	.5	5.7	54.6	9.9	5.6	12.1		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE			
<u>UP 13868</u>		Gold	18	91		Treatment	5	43	
		Silver	71	51		Insoluble	5	46	
		Copper				Zinc		18	
		Lead	7	68		Sulphur	2	50	
						Speiss			
Total Wet Weight									
Sacks						Total Debit	13	57	
Net Weight	92260	Gross Value	98	10		Iron		59	
Less H ₂ O 2.15 %	1984	Less Working Charge	12	98		Net Working Charge	12	98	

Dry Weight, lbs.	90276	Payment for	45.138	tons @	85 12	per ton	3842	15
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.		Freight advanced @	8.50	per ton	392.11			
		Assay Charges			5.00			
		Sampling Charges	Watching		5.00		402	11

Checked by _____								
Approved by _____		Net Payment	3440	04				

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, March 1st 1926

Pay West End Cons. Mng. Co.

Ore _____ Lot No. 56 Class. _____
 Sampled by UOS Received 2-21 Sampled 2-22 Assayed 2-24
 Metal Quotations—Silver .665 Copper, N. Y. _____ Lead, N. Y. 9.138 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	.99	113.0	.5	5.45	54.6	9.5	6.0	12.1		
	.100	113.4		4.95	54.6	10.3	5.2	12.1		
Umpire										
Settlement Assay	.995	113.2	.5	5.7	54.6	9.9	5.6	12.1		

CAR NOS.	WET WEIGHT	METAL VALUES		WORKING CHARGE	
<u>UP 13868</u>		Gold	<u>18 91</u>	Treatment	<u>5 43</u>
		Silver	<u>71 51</u>	Insoluble	<u>5 46</u>
		Copper		Zinc	<u>18</u>
		Lead	<u>7 68</u>	Sulphur	<u>2 50</u>
				Speiss	
Total Wet Weight					
Sacks				Total Debit	<u>13.57</u>
Net Weight	<u>92260</u>	Gross Value	<u>98 10</u>	Iron	<u>59</u>
Less H ₂ O <u>2.15</u> %	<u>1984</u>	Less Working Charge	<u>12 98</u>	Net Working Charge	<u>12 98</u>

Dry Weight, lbs.	<u>90276</u>	Payment for	<u>45.138</u> tons @	<u>85 12</u> per ton	<u>3842 15</u>
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.		Freight advanced @	<u>8.50</u> per ton	<u>392.11</u>	
		Assay Charges		<u>5.00</u>	
		Sampling Charges	<u>Watching</u>	<u>5.00</u>	<u>402 11</u>
Checked by					
Approved by		Net Payment			<u>3440 04</u>

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah,

March 1st 1926

Pay West End Cons. Mng. Co.

Ore _____ Lot No. 56 Class _____
 Sampled by UOS Received 2-21 Sampled 2-22 Assayed 2-24
 Metal Quotations—Silver .665 Copper, N. Y. _____ Lead, N. Y. 9.138 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	.99	113.0	.5	5.45	54.6	9.5	6.0	12.1		
	.100	113.4		4.95	54.6	10.3	5.2	12.1		
Umpire										
Settlement Assay	.995	113.2	.5	5.7	54.6	9.9	5.6	12.1		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE			
<u>UP 13868</u>		Gold	18	91		Treatment	5	43	
		Silver	71	51		Insoluble	5	46	
		Copper				Zinc		18	
		Lead	7	68		Sulphur	2	50	
						Speiss			
Total Wet Weight									
Sacks						Total Debit		13.57	
Net Weight	92260	Gross Value	98	10		Iron		59	
Less H ₂ O 2.15 %	1984	Less Working Charge	12	98		Net Working Charge		12	98

Dry Weight, lbs.	90276	Payment for	45.138	tons @	85 12	per ton	3842	15
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.		Freight advanced @	8.50	per ton		392.11		
		Assay Charges				5.00		
		Sampling Charges	Watching			5.00	402	11

Checked by _____								
Approved by _____		Net Payment					3440	04

Sampler Lot 2105

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 55 West End Cons Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62290	143640	47000	96640	SP 28380	
Received Jan. 26, sampled Jan. 30, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 96640 lbs.


Moisture 2.5 % 2416 lbs.

Dry Weight of Ore, 94224 lbs.

Salt Lake City, Utah Feb. 1, 1926

Sampling 43.49

UTAH ORE SAMPLING COMPANY

Per 

Sampler Lot 2105

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 55 West End Cons Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62290	143640	47000	96640	SP 28380	
Received Jan. 26, sampled Jan. 30, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 96640 lbs.


Moisture 2.5 % 2416 lbs.

Dry Weight of Ore, 94224 lbs.

Salt Lake City, Utah Feb. 1, 1926

Sampling 43.49

UTAH ORE SAMPLING COMPANY

Per 

Sampler Lot 2303

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 57 West End Con Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62691	155540	46360	109180	GHSA 34827	
Received March 21, sampled March 24, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 109180 lbs.

Moisture 1.75 % 1910 lbs.

Dry Weight of Ore, 107270 lbs.

Salt Lake City, Utah March 25, 1926

Sampling 49.13

UTAH ORE SAMPLING COMPANY

Per

Sampler Lot 2303

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 57 West End Con Mining Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 62691	155540	46360	109180	GHSA 34827	
Received March 21, sampled March 24, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 109180 lbs.

Moisture 1.75 % 1910 lbs.

Dry Weight of Ore, 107270 lbs.

Salt Lake City, Utah March 25, 1926

Sampling 49.13

UTAH ORE SAMPLING COMPANY

Per

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH, March 26, 1926

NAME West End Con.

LOT No. 57

SAMPLED BY U.O.S.

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
<u>0 98</u> 0.985	<u>107.8</u> 108.3	<u>8 0</u> 8.3			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
<u>43 8</u> 43.0	<u>7.5</u> 7.7	<u>16.5</u> 16.7	<u>11.6</u> . 12.3		

CHARGE, \$ 5

Black & Deason ASSAYERS

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah,

March 30 1926

Pay West End Cons. Mng. Co.

Ore _____ Lot No. 57 Class _____
 Sampled by _____ Received 3-21 Sampled 3-24 Assayed 3-26
 Metal Quotations—Silver .65625 Copper, N. Y. _____ Lead, N. Y. 8.242 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	.98	107.8		6.75	43.8	11.6	7.5	16.5		
	.985	103.3		7.05	43.0	12.3	7.7	16.7		
Umpire										
Settlement Assay	.9825	108.05		6.9	43.4	11.95	7.6	16.6		

CAR NOS.	WET WEIGHT	METAL VALUES		WORKING CHARGE	
CHSA 34827		Gold	18 67	Treatment	5 31
		Silver	67 36	Insoluble	4 34
		Copper		Zinc	78
		Pb.	8 19	Sulphur	2 50
				Speiss	
Total Wet Weight					
Sacks				Total Debit	12 93
Net Weight	169180	Gross Value	94 22	Iron	72
Less H ₂ O 1.75 %	1910	Less Working Charge	12 12	Net Working Charge	12 21
			12.21		

Dry Weight, lbs. 107270 Payment for 53.635 tons @ 82 01 per ton 4398 61

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 3.50 per ton 464.02
 Assay Charges 5.00
 Sampling Charges Watching 5.00 474 02

Checked by _____

Approved by _____

Net Payment

3924 59

UNITED STATES SMELTING, REFINING AND MINING COMPANY
MIDVALE SMELTER AND MILLS

DOWNIE D. MUIR, JR., GENERAL MANAGER
W. H. EARDLEY, ASSISTANT MANAGER
E. R. GIBSON, CASHIER
M. W. WOOLLEY, ORE BUYER

SALT LAKE CITY, UTAH

Jan. 27 1926

West End Consolidated Mng. Co.

Tonopah, Nevada

Gentlemen:

We are in receipt of your letter of the 23rd advising as
to shipment of your car #22380.

Same will be handled as per your instructions.

Yours very truly,

W. H. Eardley

WHE:M

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah, Feb. 4 1926

Pay West End Cons. Mng. Co.

Ore _____ Lot No. 55 Class _____
 Sampled by UOS Received 1-26 Sampled 1-30 Assayed 2-2
 Metal Quotations—Silver .6725 Copper, N. Y. _____ Lead, N. Y. 9.254 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.27	131.2	.7	7.25	54.6	9.3	5.7	12.0		
	1.26	130.7	.65	7.65	54.6	10.3	4.6	11.0		
Umpire										
Settlement Assay	1.265	130.95	.68	7.45	54.6	9.8	5.15	11.5		

CAR NOS.	WET WEIGHT	METAL VALUES		WORKING CHARGE	
55-62292 SP 28380		Gold	24 04	Treatment	5 26
		Silver	83 66	Insoluble	5 46
		Copper		Zinc	05
		Lead	10 20	Sulphur	2 38
				Speiss	
Total Wet Weight					
Sacks				Total Debit	13 15
Net Weight	96640	Gross Value	117 90	Iron	59
Less H ₂ O 2.5 %	2416	Less Working Charge	12 56	Net Working Charge	12 56

Dry Weight, lbs.	94224	Payment for	47.112 tons @	105 34	per ton	4962 78
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.		Freight advanced @	13.00 per ton	628.16		
		Assay Charges		5.00		
		Sampling Charges	Watching	5.00		638 16

Checked by _____						
Approved by _____		Net Payment				4324 62

DAILY ASSAY REPORT

TONOPAH, NEVADA, Feb. 15-26 1922

[Signature]
ASSAYER

JPM

Lot No. 33

SAMPLED BY

SHIPPER

1926

Cars and Contents O. K. When Received Unless Noted Otherwise

No.

Weight

Condition

Total Net Dry Weight

Moisture

Per Cent

Total Net Weight

Weather

Remarks:

A. L. Stauffer

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE NO. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTSNAME **West End Con**

SALT LAKE CITY, UTAH,

Jan. 4, 1926

LOT NO. **54**SAMPLED BY **Utah Ore**

ASSAY PER TON OF 2,000 POUNDS

GOLD—Ozs.	SILVER—Ozs.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.26	94.2	8.4			
1.32	95.9	8.6			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
54.0	5.0	12.5	10.4		
54.0	4.5	11.9	11.0		

CHARGE, \$ **5.00**

 ASSAYERS

Phone Was. 2393

Salt Lake City, Utah, Jan. 6, 1926

NAME West End

WEIGHT

CLASS

LOT NO, 54-Orig.SAMPLED BY Utah Ore Sampling Co.**UMPIRE ASSAY PER TON 2000 LBS.**

GOLD-Ozs.	SILVER-Ozs.	LEAD-Per cent Wet on Fire	COPPER-Per cent
1.33	95.20		
Per cent SILICA INSOL.	IRON-Per cent	ZINC-Per cent	SULPHUR-Per cent
SPEISS-Per cent	LIME-Per cent	MANGANESE Per cent	Per cent

CHARGES \$ 5.00*Frederick Nichols*

Sampler Lot 2001

UTAH ORE SAMPLING COMPANY

MURRAY PLANT

WEIGHT AND MOISTURE CERTIFICATE

Lot 54 West End Cons. Mng Co. Ore

Class

INTO CAR	GROSS	TARE	NET	FROM CAR	
UP 63747	145680	46400	99280	SP 30124	
Received Dec. 30, 1925, sampled Jan. 2, 1926					

Total Wet Weight lbs.

Sacks lbs.

Net Weight of Ore, 99280 lbs.


Moisture 2.5 % 2482 lbs.

Dry Weight of Ore, 96798 lbs.

Salt Lake City, Utah Jan. 4, 1926

Sampling 44.68

UTAH ORE SAMPLING COMPANY

Per 

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

PHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH. Feb. 1, 1926

NAME **West End Con**

LOT NO. **55**

SAMPLED BY **Utah Ore**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.27 1.26	131.2 130.7	8.5 8.9	0.70 0.65		
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
54.6 54.6	5.7 4.6	12.0 11.0	9.3 10.3		

CHARGE, \$ _____

Black & Deason

ASSAYERS

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah,

Jan. 11 1926

Pay West End Cons. M. Co.

Ore _____ Lot No. 54 Class _____
 Sampled by UOS Received 12-30 Sampled 1-2 Assayed 1-5
 Metal Quotations—Silver .685 Copper, N. Y. _____ Lead, N. Y. 9.25 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.26 ✓	94.2 ✓		7.15 ✓	54.0 ✓	10.4 ✓	5.0 ✓	12.5 ✓		
	1.32 ✓	95.9 ✓		7.35 ✓	54.0 ✓	11.0 ✓	4.5 ✓	11.9 ✓		
CN Umpire	1.33 ✓	95.2 ✓								
Settlement Assay	1.32 ✓	95.2 ✓		7.25 ✓	54.0 ✓	10.7 ✓	4.75 ✓	12.2 ✓		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE			
SP 30124		Gold	25	08		Treatment	5	28	✓
		Silver	61	95		Insoluble	5	40	✓
		Copper				Zinc			
		Lead	9	92		Sulphur <i>should be 2.50</i>	2	50	✓
						Speiss <i>2.50</i>			
						<i>Settlement on lot #24</i>			
Total Wet Weight						Total Debit	13	18	
Sacks						Iron		64	✓
Net Weight	99280	Gross Value	96	95		Net Working Charge	12	54	
Less H ₂ O 2.5 %	2482	Less Working Charge	12	54					

Dry Weight, lbs. 96798	Payment for 48.399 / tons @ 84 41 per ton	4085 36 /
A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.	Freight advanced @ 8.50 per ton	421.94 /
	Assay Charges	5.00 /
	Sampling Charges Watching	5.00 /
	C/n a/c Freight Freightlot 52 13.06 /	445 00 /
Checked by	Net Payment	3640 36
Approved by		

UNITED STATES SMELTING, REFINING & MINING COMPANY

NINTH FLOOR NEWHOUSE BUILDING

Salt Lake City, Utah,

Jan. 11 1926

Pay West End Cons. M. Co.

Ore _____ Lot No. 54 Class _____
 Sampled by UOS Received 12-30 Sampled 1-2 Assayed 1-5
 Metal Quotations—Silver .685 Copper, N. Y. _____ Lead, N. Y. 9.25 Zinc _____

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT	PER CENT
U. S. S. Co.	1.26	94.2		7.15	54.0	10.4	5.0	12.5		
	1.32	95.9		7.35	54.0	11.0	4.5	11.9		
CN Umpire	1.33	95.2								
Settlement Assay	1.32	95.2		7.25	54.0	10.7	4.75	12.2		

CAR NOS.	WET WEIGHT	METAL VALUES				WORKING CHARGE			
<u>SP 30124</u>		Gold	25	08		Treatment	5	28	
		Silver	61	95		Insoluble	5	40	
		Copper				Zinc			
		Lead	9	92		Sulphur	2	50	
						Speiss			
Total Wet Weight									
Sacks						Total Debit	13	18	
Net Weight	99280	Gross Value	96	95		Iron		64	
Less H ₂ O 2.5 %	2482	Less Working Charge	12	54		Net Working Charge	12	54	

Dry Weight, lbs. 96798 Payment for 48.399 tons @ 84 41 per ton 4085 36

A charge of Five Dollars made for sampling on all lots of ore containing less than ten tons, dry weight. Rates subject to change without notice when not under contract or for specified tonnage.

Freight advanced @ 8.50 per ton 421.94
 Assay Charges 5.00
 Sampling Charges Watching 5.00

C/n a/c Freight Freightlot 52 13.06 445 00

Checked by _____

Approved by _____

Net Payment

3640 36

1926

Lot No. 54 Jan 4 1926
SAMPLED BY Utah Ore Co. SHIPPER West End Con.

Wm. H. Stauffer
Bradford

DAILY ASSAY REPORT

TONOPAH, NEVADA, Feb. 5-26 1922

[illegible]

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE WAS. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

SALT LAKE CITY, UTAH, Nov. 29, 1926.

NAME **West End Con.**

LOT No. **65**

SAMPLED BY **UOS**

ASSAY PER TON OF 2,000 POUNDS

GOLD—OZS.	SILVER—OZS.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
1.81 1.80	162.3 163.0	12.05 12.3			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
69.2 67.8	0.4 0.3	0.35 0.2	6.0 6.1		

CHARGE, \$ _____

Black & Deason ASSAYERS

165 S. WEST TEMPLE ST.

CERTIFICATE OF ASSAY

TELEPHONE NO. 1214

BLACK & DEASON

ASSAYERS AND CHEMISTS

NAME West End Con.

SALT LAKE CITY, UTAH, Oct. 21, 1926.

LOT NO. 64 Orig.

SAMPLED BY

UOS

ASSAY PER TON OF 2,000 POUNDS

GOLD—Ozs.	SILVER—Ozs.	LEAD—%	COPPER—%	SPEISS—%	SILICA—%
2.27 2.29	294.9 299.3	15.7 16.0			
INSOLUBLE—%	ZINC—%	SULPHUR—%	IRON—%	LIME—%	MANGANESE—%
64.8 62.2	0.6 0.3	1.4 0.3	6.2 5.5		

CHARGE. \$ _____

Black & Deason ASSAYERS