

4990 0012

SHAMROCK MINES CO.  
Ione, Nye Co. Nevada258-A  
Item 12

DUMP SALES - - - - - August and September, 1924.

CROWN CLAIM DUMPSPart of Whole.Gold &Silver Oz.

## Dump "A"

Fines  
2nd Fines  
Coarse Ore  
Average of Dump1/3  
1/3  
1/32.17  
2.60  
1.95  
2.242.74  
3.48  
7.57  
4.59*all in dollars  
at \$20.67  
Silver in Oz.*

## Dump "B"

Fines  
2nd Fines  
Coarse Ore  
Average of dump1/3  
"  
"  
"2.17  
1.30  
.87  
1.445.30  
9.06  
8.48  
7.61

## Dump "C"

Cut No. 1  
Fines  
2nd Fines  
Coarse Ore  
Average of cut1/6  
1/2  
1/31.51  
1.30  
.87  
1.093.13  
10.82  
2.32  
6.70Cut No. 2  
All

1.08

1.95

Cut No. 3  
Fines  
2nd Fines  
Coarse Ore  
Average of cut1/6  
1/2  
1/31.30  
2.17  
1.08  
1.667.10  
21.22  
13.99  
16.45*7.10  
4.97  
2.13*Cut #4  
Fines  
2nd Fines  
Average of cut1/3  
2/31.30  
3.03  
2.458.74  
9.46  
9.22Cut No. 5  
Fines  
2nd fines  
Coarse Ore  
Average of cut1/6  
2/3  
1/6.87  
.65  
4.33  
1.307.62  
6.69  
5.76  
6.69*2.27  
4.97  
7.14*

## Dump "D"

Cut No. 1  
Fines  
2nd Fines  
Coarse Ore  
Average of cut1/3  
2/3  
1/3.43  
1.73  
.43  
.862.38  
23.88  
3.94  
10.06Cut No. 2  
Fines  
2nd Fines  
Coarse Ore  
Average of cut1/3  
"  
"3.47  
1.30  
1.30  
2.0257.44  
3.30  
3.18  
4.64Cut No. 3  
Fines  
2nd Fines  
Coarse Ore  
average of cut1/3  
"  
"4.33  
1.73  
1.08  
2.387.36  
3.52  
2.91  
4.59Cut No. 4  
Fines  
2nd Fines  
Coarse Ore  
Average of cut1/3  
"  
"1.52  
1.73  
1.08  
1.442.25  
5.08  
4.08  
3.78Cut No. 5  
Fines  
2nd Fines  
Coarse Ore  
Average for cut1/3  
1/2  
1/6.86  
.86  
1.30  
.932.36  
1.96  
3.66  
2.37



	<u>Part of Whole</u>	<u>Gold &amp;</u>	<u>Silver Oz.</u>
Dump "E"			
Cut No. 1			
Fines	1/3	5.30	27.32
2nd Fines	1/2	3.91	27.02
Coarse Ore	1/6	2.60	12.74
Average cut cut		4.15	26.40
Cut No. 2			
Fines	1/3	3.91	24.94
2nd Fines	"	3.91	29.82
Coarse Ore	"	2.60	11.80
Average for cut		3.44	22.18
Cut No. 3			
Fines	1/3	3.04	21.86
2nd Fines	"	3.47	20.92
Coarse Ore	"	2.17	12.78
Average for Cut		2.89	18.52
Dump "F"			
Cut No. 1			
Fines	1/3	3.90	13.42
2nd Fines	"	3.03	10.90
Coarse Ore	"	3.47	35.84
Average for cut		3.46	20.08
Cut No. 2			
Fines	1/6	2.17	4.90
2nd Fines	1/2	.22	1.69
Coarse Ore	1/3	.43	1.92
Average for cut		.615	2.30
Dump "G"			
Cut No. 1			
Fines	1/3	.43	3.02
2nd Fines	1/2	.43	1.26
Coarse Ore	1/6	.86	12.78
Average for cut		.50	3.76
Dump "H"			
Cut No. 1			
Fines	1/3	1.30	1.14
2nd Fines	1/2	1.30	2.30
Coarse Ore	1/6	Trace	.92
Average for cut		1.083	1.68
Cut No. 2			
Fines	1/3	.43	1.14
2nd Fines	"	.43	7.82
Coarse Ore	"	.22	1.01
Average for cut		.36	3.32
Dump "I"			
Cut No. 1			
Fines	1/3	2.60	10.72
2nd Fines	"	2.60	15.68
Coarse Ore	"	3.47	44.76
Average for cut		2.89	23.72
Dump "J"			
Cut No. 1			
Fines	1/6	.87	5.48
2nd Fines	1/3	2.17	20.86
Coarse Ore	1/2	2.17	53.48
Average for cut		1.95	34.59
Dump "K"			
All		.87	1.36



	<u>Part of Whole</u>	<u>Gold &amp;</u>	<u>Silver Oz.</u>	
<b>Dump "L"</b>				
Cut No. 1				
Fines	1/2	trace	2.24	
2nd Fines	1/3	.22	3.63	
Coarse Ore	1/6	2.80	5.20	
Average for cut		.54	3.19	
<b>Dump "M"</b>				
Cut No. 1				
Fines	1/3	.40	2.00	
2nd Fines	"	1.20	10.06	
Coarse Ore	"	trace	6.20	
Average for cut		.53	6.08	
Cut No. 2				
Fines	1/3	trace	.60	
2nd Fines	"	.40	2.48	
Coarse Ore	"	.20	3.28	
Average for cut		.20	2.12	
<b><u>VIOLET DUMPS</u></b>				
Cut No. 1				
Fines	1/6	3.20	29.04	71
2nd Fines	1/2	2.00	11.74	15
Coarse Ore	1/3	3.20	19.06	35.5
Average for cut		2.60	17.06	71
				10.65
Cut No. 2				
Fines	1/2	.80	11.16	
2nd Fines	1/6	1.60	4.42	
Coarse Ore	1/3	2.40	11.68	
Average for cut		1.46	10.21	
Cut No. 3				
Fines	1/3	2.80	21.30	
2nd Fines	1/2	2.40	8.08	
Coarse Ore	1/6	2.40	11.68	
Average for cut		2.53	12.28	6.88
Cut No. 4				
Fines	1/2	2.40	4.60	
2nd Fines	1/3	.80	7.88	
Coarse Ore	1/6	.80	29.76	
Average for cut		1.60	9.85	
<b><u>KEYSTONE DUMPS</u></b>				
Cut No. 5				
Fines	1/3	1.00	9.63	
2nd Fines	1/2	2.00	39.50	
Coarse Ore	1/6	2.40	38.84	
Average for cut		1.73	29.43	320
Cut No. 6				
Fines	1/3	3.20	15.80	110
2nd Fines	1/2	4.00	68.80	440
Coarse Ore		2.00	27.70	1050
Average for cut		3.40	44.28	1520
Cut No. 7				
Fines	1/3	.20	4.54	15
2nd Fines	"	.40	3.26	30
Coarsx Ore	"	1.60	18.32	1050
Average for cut		.73	8.70	
Cut No. 8				
Fines	1/2	1.60	5.36	
2nd Fines	1/3	.80	10.36	
Coarse Ore	1/6	.80	25.36	
Average for cut		1.20	10.36	



	<u>Part of Whole</u>	<u>Gold &amp;</u>	<u>Silver Oz.</u>
Cut No. 9			
Fines and 2nd Fines	2/3	1.60	13.92
Coarse Ore	1/3	1.60	13.94
Average for cut		1.60	13.926
Cut No. 10			
Fines and 2nd Fines	1/2	trace	10.24
Coarse Ore	1/2	3.60	41.84
Average for cut		1.80	26.04

Sampling in Wild Emigrant Shaft.

<u>No.</u>	<u>Description</u>	<u>Gold &amp;</u>	<u>Silver Ounce</u>
1.	First Level - North	Trace	3.08
2nd	First Level - North	1.20	5.90
3rd.	First Level - North	Trace	1.04
4th	First Level - North	.40	.74
5th	First Level - North	.40	3.58
6th	Second Level - North	Trace	7.88
7th	Second Level - North	5.60	16.00
8th	Second Level - North	1.20	6.00
9th	Second Level - North	2.40	5.14
10th.	Second Level - North	.40	6.26
11th.	Second Level - North	2.40	9.20
12th	Second Level - North	4.80	25.84
13th.	Second level - North	Trace	6.14
14th	Second level - North	8.80	7.96
	Average	1.96	7.48